


JUBILEE COAL COMPANY

COAL SEAM

5 cm



SAMPLE	COAL	MOISTURE %	ASH %	CALORIFIC VALUE B.T.U.s.	REMARKS
1	5' 2"	5.2	24.2	9660	COAL MARKETED
2	1' 8"	4.1	30.4	8700	
3	3' 6"	4.4	21.0	10270	
4	3' 3"	4.0	20.5	10590	
5	6' 9"	5.0	20.8	10310	
SLACK		4.0	30.9	8640	LOWERED CALORIFIC VALUE DUE TO INCREASES IN MOISTURE AND ASH IN COMPOSITE SAMPLE. SAMPLE TAKEN FROM BINS.

82

1058