


1843





872

5 cm



INTERSECTION	% CORE RECOVERY	% Fe HCl SOL.	IMPURITIES					
			SiO <sub>2</sub> %	TiO <sub>2</sub> %	Mn%	P <sub>2</sub> O <sub>5</sub> %	S%	Al <sub>2</sub> O <sub>3</sub> %
95 - 114	-	54.5	6.6	0.68	0.05	0.02	3.38	2.3
124 - 276	-	52	7.3	0.5	0.1	0.25	4.68	2.5
293 - 303	-	53	8.7	0.63	0.1	0.27	2.25	2.5
318 - 331	83	45	12.9	0.57	0.1	0.37	2.77	3.0
359 - 438	91	46	12.8	0.67	0.1	0.3	4.0	3.8
2 - 53		58.7						
53 - 72'3"		8.39						
72'3" - 105'3"		49.8						
105'3" - 221'6"		28.65						
221'6" - 239'		22.12						
239' - 292'6"		43.4						

N.B. NO SURVEY OF DIPS.

-  MEDIUM GRADE IRON ORE
-  LOW GRADE IRON ORE
-  BARREN COUNTRY ROCK
-  IRON ORE - OUTCROP

SAVAGE RIVER AREA  
 MAIN SOUTH IRON DEPOSIT  
 D.D.H. 10 & 23

0 100 200 FT.

DEPT. OF MINES  
 1843-35