


809

5 cm

R 653 RAZORBACK ORE TEST N° 4



PRIMARY
 S1 - (9, 2.0, 26)
 S2 - (3, 0.86, 4)
 S3 - (8, 0.53, 6)
 O/F - (27, 0.22, 8)

SECONDARY
 S1 - (6, 1.0, 10)
 S2 - (1, 0.66, 1)
 S3 - (3, 0.46, 2)
 O/F - (8, 0.29, 3)

FINAL TIN CONC. (1, 54, 55)
 MAGNETIC CONC. M/A2 (1, 3.4, 8)
 MAGNETIC CONC. M/A1 (5, 0.55, 4)
 TABLE MIDDLING (6, 0.64, 5)
 TABLE TAILING (87, 0.22, 28)

(X, Y, Z) X = PER CENT WEIGHT
 Y = PER CENT TIN
 Z = PER CENT TIN DISTRIBUTION

DEPT. OF MINES 3749-M

DEPARTMENT OF MINES - TASMANIA