

ASSAY VALUES					
Sample No.	length ft.	Zn %	Pb %	Ag oz.	Au oz.
252	15	11	7	4.47	0.3
253	9	0.55	1.5	1.2	0.7
254	4	22	0.1	0.6	7
255	8	18.75	6.4	13.91	0.9
256	4.5	11.2	5.4	9.64	0.6
257	6	14.5	8.05	15.01	0.9
258	4	10.55	5.45	12.46	0.4
259	4	17.55	7.8	12.36	0.4
260	4	10	0.15	3.68	0.2
261	4	0.38	0.05	0.5	7
262	6	25.05	5.2	6.14	0.6
263	2	30.8	4.75	4.46	0.6
264	5	16.7	8.1	7.55	0.7
265	4	18.5	5.75	5.67	0.5
266	3.5	10.55	5.1	4.55	0.5
267	4.5	16.2	7.6	5.85	0.7
268	5	5.7	1.7	1.5	0.1
269	4	7.4	4.15	2.18	0.2
270	5	9.4	4.85	6.64	0.6
271	1.5	16.85	11.05	4.47	0.5
272	5	7.4	1.75	1.87	0.5
273	6.5	5.95	5.05	7.55	0.5
274	7	29.5	9.5	9.52	0.6
275	7	20.75	4.9	5.22	0.8
276	5	28.6	6.1	7.55	0.5
277	5	25.25	6.8	10.0	1.0
278	5	25.4	5.55	6.64	0.6
279	5	26.5	8.4	10.32	0.8
280	9	28.5	4.4	4.25	0.5
281	2.5	13.2	6.45	8.14	0.6
282	2	15.1	4.0	5.66	0.4

NORTH TAS. COPPER CO.

The Mount Lyell M. & R. Company, Ltd.
 Mine Department.
 GENERAL PLAN
 TASMANIAN COPPER COMPANY'S MINE.
 SCALE. 1" = 100'.

8-455

455/51

