


5 cm

## BLUE TIER FLOWSHEET



*T Discarded*

*M/A Combined magnetics  
form 820989*

*F 1-9 Made on screens  
500,425,355,300,250,  
212,180,150um 8 U/S  
Each tabled separately*

**C** *Nine concentrates made  
were:*

+ 500 um	820886
+ 425um	820887
+ 355 um	820888
+ 300 um	820889
+ 250 um	820890
+ 212 um	820891
+ 180 um	820892
+ 150 um	820893
+ 150 um	820894

**M** *Middling from + 355 um  
tabling yielded 820988*