


SECTION	CORE RECOVERY %	VALUE % Fe. HCL SOLUBLE
313'-0" - 351'-0"	94.5	47.2
358'-6" - 408'-6"	73.3	51.4
420'-6" - 457'-0"	97.9	50.4
462'-0" - 502'-0"	99.6	47.4
512'-0" - 605'-0"	93.5	50.0
617'-0" - 651'-0"	98.8	52.0
669'-0" - 689'-0"	97.9	51.3
696'-0" - 718'-6"	94.8	44.5
313'-0" - 718'-6"	93.9	44.1

IMPURITIES

FROM - TO	SiO ₂ %	TiO ₂ %	Mn %	P ₂ O ₅ %	S %
313' - 718.5'	14.88	1.78	0.12	0.08	0.48



RIO TINTO AUSTRALIAN EXPLORATION PTY. LIMITED

**SAVAGE RIVER DRILLING
MAIN NORTH IRON DEPOSIT
SECTION SHOWING LOCATION
OF D.D.H. No 2**

SCALE : 1 INCH TO 100 FEET

DATE : APRIL , 1958.

GEOLOGIST : W ATKINSON

DRAFTSMAN : D LAWFORD

AUTHORITY P&F 7/100

PLAN No T. 320