

SAMPLE NO.	SiO ₂	MgO
3	16	21.25
4	14	21.14
5	14	21.68
6	10	21.44
7	10	21.12
8	12	21.10
9	3.0	21.02
10	4.0	21.03
11	1.0	20.76
12	7.1	20.66
13	3.16	20.73
14	4.20	19.71
15	2.72	20.31
16	2.80	20.31
17	4.16	19.40
18	2.24	20.48
32	30	20.59



SMITHTON DOLOMITE - TAS.

OUTLINE FOR BORING
 BASED ON PLAN BY D.E. THOMAS, D. SC.
 DEC. 1943

