

UNPUBLISHED REPORT 1966/22

Samples of concentrates from Boobyalla

by G. B. Everard

Four samples of concentrates from Boobyalla No. 6 bore have been examined with the following results.

Sample No. 6, 25–30', 15 grams	55% marcasite 45% quartz trace topaz trace tourmaline trace cassiterite
---------------------------------------	---

Sample No. 7, 30–35', 9.4 grams 0.3 grams residue	marcasite 60% quartz 35% zircon 5% tourmaline trace garnet trace cassiterite
---	---

Sample No. 8, 35–40', 11.6 grams 0.6 grams residue	marcasite 90% quartz 8% zircon 2% cassiterite
--	--

Sample 120', 2 grams total	60% quartz 20% zircon 15% ilmenite 5% augite trace cassiterite
-----------------------------------	--

[24 November 1966]