AMDEX MINING LIMITED - NORTH EAST TASMANIA DRILL LOG

Area: STH.MT. CAMERON-BONSER CREEK Hole No: B.C.4 Collar Co-ordinates: ..... mN ..... mE Drilling Method: Percussion

Surface R.L.: 52.1 m Basement R.L.: 43.1 m Cutting Shoe / Bit diameter: 16.02cm. Theoretical Volume: 40.3 litres

Date: 10/9/81 Driller: G. Selby Assistant: B. Blake Sample Washer: S. Moore Geologist: R. Munro

Section From	Metres To	Sample No.	Recovered Volume (l)	Weight Conc. (g)	Conc. Assay (%Sn)	Recovered Tin (g SnO_2)	Grade * g SnO_2/m^3	Grade + g SnO_2/m^3	Description of Sample
0	2	5471	25½LTRS	120.1	0.09	0.15	6.0	4.8	Black mud, c & f sand. Ilmenite, pyrite.
2	4	5472	14½"	156.1	0.03	0.07	4.6	2.1	C & f sand, black mud, heavy drift. Pyrite.
4	6	5473	26 "	104.2	0.09	0.13	5.1	4.2	C & f sand, heavy drift. Pyrite.
6	8	5474	22 "	94.9	0.14	0.19	8.6	6.1	C & f sand, heavy drift, med. wash. Tr. of tin, pyrite.
8	9	5475	14½"	118.2	0.87	1.47	101.3	91.1	C & f sand, med. wash, decomposed granite. Sm. amount tin, pyrite.
9	10	5476	10 "	102.1	0.34	0.50	49.6	30.8	Decomposed granite. Tr. of tin, pyrite.
10	11	5477	14 "	141.5	0.12	0.24	17.2	15.0	Decomposed granite. Pyrite.

648016

* Grade calculated by relating recovered volume to recovered tin + Grade calculated by relating Radford factored theoretical volume to recovered tin Rad.F = 80%

Drillers reported basement at 9 m. Grade from surface to inferred basement at ..... m ..... g SnO_2/m^3 *

Total recovered volume, surface to basement ..... l. at 9 m 19 g SnO_2/m^3 +