

AMDEX MINING LIMITED - NORTH EAST TASMANIA DRILL LOG

Area: STH.MT.CAMERON- Hole No.: B.C.7 Collar Co-ordinates: mN mE Drilling Method: Percussion
BONSER CREEK

Surface R.L.: 50.7 m Basement R.L.: 29.2 m Cutting Shoe / Bit diameter: 16.02 Theoretical Volume: 40.3 litres.

Date: 17/9/81 Driller: G. Selby Assistant: B. Blake Sample Washer: S. Moore Geologist: R. Munro

Section		Metres	Sample No.	Recovered Volume (l)	Weight Conc. (g)	Conc. Assay (%Sn)	Recovered Tin (gSnO ₂)	Grade * (gSnO ₂ /m ³)	Grade + (gSnO ₂ /m ³)	Description of Sample
From	To									
0	2		5701	28½LTRS	103.4	0.14	0.21	7.2	6.4	Black mud, c & f sand, heavy drift. Ilmenite, pyrite.
2	4		5702	24 "	155.6	0.19	0.42	17.6	13.1	C & f sand, sm. & med. wash, grey clay. Tr. of tin, ilmenite, pyrite.
4	6		5703	25 "	103.6	2.22	3.29	131.4	101.9	C & f sand, med. wash, white & brown clay. Sm. amount tin, ilmenite, pyrite.
6	8		5704	26 "	91.9	0.16	0.21	8.1	6.5	C & f sand, grey clay. Tr. of tin, pyrite.
8	10		5705	29 "	116.0	0.15	0.25	8.5	7.7	C & f sand, grey & brown clay. Pyrite, tr. of ilmenite.
10	12		5706	32½"	103.9	0.06	0.09	2.7	2.7	C & f sand, organic silt, pyrite lumps, wood. Pyrite.
12	14		5707	27½"	169.6	B.L.D. 0.01	0	0	0	C & f sand, organic silt, wood. Pyrite.
14	16		5708	29½"	131.9	B.L.D. 0.01	0	0	0	C & f sand, organic silt, wood, pyrite lumps. Pyrite.
16	18		5709	35 "	120.1	B.L.D. 0.01	0	0	0	C & f sand, organic silt, wood. Pyrite.
18	20		5710	25 "	261.8	B.L.D.	0	0	0	C & f sand, organic silt. Pyrite.
20	22		5711	24 "	569.1	0.26	2.11	88.0	65.6	C & f sand, sm, med. & lge. wash, organic silt, decomposed granite. Lge. amount pyrite.
22	23		5712	11 "	143.0	0.05	0.10	9.3	6.3	Decomposed granite. Pyrite.
23	24		5713	21½"	433.2	B.L.D. 0.01	0	0	0	Decomposed granite. Pyrite.
										648019

* Grade calculated by relating recovered volume to recovered tin + Grade calculated by relating Radford factored theoretical volume to recovered tin. Rad F = 80%
 Drillers reported basement at 21.50 m. Grade from surface to inferred basement at m
 Total recovered volume, surface to basement l. at 21.5 m 19 g SnO₂ / m³ *