

# AMDEX MINING LIMITED - NORTH EAST TASMANIA DRILL LOG

Area: 5TH. MT. CAMERON Hole No.: B.C. 10 Collar Co-ordinates: mN mE Drilling Method: Percussion  
BONSER CREEK

Surface R.L.: 44.7 m Basement R.L.: 28.2 m Cutting Shoe / Bit diameter: 16.02cm. Theoretical Volume: 40.3 litres.

Date: 23/9/81 Driller: G. Selby Assistant: B. Blake Sample Washer: S. Moore Geologist: R. Munro

Section	Metres	Sample No.	Recovered Volume (l)	Weight Conc. (g)	Conc. Assay (%Sn)	Recovered Tin (gSnO <sub>2</sub> )	Grade * (gSnO <sub>2</sub> /m <sup>3</sup> )	Grade + (gSnO <sub>2</sub> /m <sup>3</sup> )	Description of Sample
From 0	To 2	5737	20½LTRS	86.0	BLD 0.01	0	0	0	Black mud, c & f sand. Ilmenite.
2	4	5738	23 "	96.3	2.12	2.92	126.8	90.5	C & f sand, sm. & med. wash, organic silt, wood. Tin, pyrite.
4	6	5739	24½"	97.2	0.08	0.11	4.5	3.4	C & f sand, organic silt, wood. Pyrite.
6	8	5740	25 "	93.0	0.23	0.31	12.2	9.4	C & f sand, organic silt, wood, sm. & med. wash. Pyrite.
8	10	5741	28 "	290.7	0.66	2.74	97.9	85.0	C & f sand, sm, med. & lge. wash, white clay. V.f. tr. of tin, pyrite.
10	12	5742	15½"	93.7	0.18	0.24	15.5	7.4	C & f sand, sm. & med. wash, grey & white sandy clay. Pyrite.
12	14	5743	18 ""	94.8	0.07	0.09	5.2	2.8	C & f sand, sm. & med. wash, grey sandy clay. Pyrite.
14	16	5744	23 ""	91.5	0.11	0.14	6.2	4.4	C & f sand, med. wash, grey clay. Pyrite.
16	17	5745	11½""	154.5	BLD 0.02	0	0	0	C & f sand, sm. & med. wash, grey clay, granite. Pyrite.
17	18	5746	11 ""	107.2	0.05	0.07	6.9	4.7	C & f sand, sm. & med. wash, granite. Pyrite.
18	19	5747	11½""	94.6	0.04	0.05	4.8	3.3	C & f sand, med. wash, decomposed granite. Pyrite.
									648022

\* Grade calculated by relating recovered volume to recovered tin + Grade calculated by relating Radford factored theoretical volume to recovered tin Rad.F = 80%  
 Drillers reported basement at 16.50 m. Grade from surface to inferred basement at ..... m ..... g SnO<sub>2</sub> / m<sup>3</sup> +  
 Total recovered volume, surface to basement ..... l. at 16.5 m ..... 25 ..... g SnO<sub>2</sub> / m<sup>3</sup> +  
 Total recovered tin ..... gSnO<sub>2</sub>