

920466

AMDEX MINING LIMITED - NORTH EAST TASMANIA DRILL LOG

Area: STR. MT. CAMERON Hole No: E.P. 43 Collar Co-ordinates: mN mE Drilling Method: Percussion

Surface R.L.: 73.5 m Basement R.L.: 57.5 m Cutting Shoe / Bit diameter: 16.03 cm. Theoretical Volume: 40.3 litres

Date: 19.2.81 Driller: G. Selby Assistant: B. Blake Sample Washer: S. Moore Geologist: R. Munro

Section		Sample No.	Recovered Volume (l)	Weight Conc. (g)	Conc. Assay (%Sn)	Recovered Tin (gSnO2)	Grade * gSnO2/m ³	Grade + gSnO2/m ³	Description of Sample
From	To								
0	2	5402	5LTRS	251.0	2.39	8.57	37.97	C & f sand, heavy drift (tailings). Tr. of tin, pyrite.	
2	4	5403	19½"				37.97	C & f sand, heavy drift, black mud. Tr. of tin, ilmenite, pyrite.	
4	6	5404	15 "				37.97	C & f sand, grey sandy clay. Ilmenite, pyrite.	
6	8	5405	25 "				37.97	C & f sand, white sandy clay. Tr. of tin, pyrite.	
8	10	5406	21½"				37.97	C & f sand, brown silty clay. Pyrite.	
10	12	5407	22½ "				37.97	C & f sand, heavy drift, sm. wash. Lge. amount ilmenite, pyrite.	
12	14	5408	20 "				37.97	C & f sand, white clay, pyrite lumps. Ilmenite, pyrite.	
14	16	5409	16 "	171.3	0.67	1.64	50.86	C & f sand, granite. Pyrite, v. fine tr. tin.	
16	18	5410	17½"	264.3	0.28	1.06	32.79	Decomposed granite. Pyrite.	
18	19	5411	21½"	254.5	0.08	0.29	13.53	Decomposed granite. Pyrite.	
19	20	5412	20½"	141.0	0.06	0.12	5.90	Decomposed granite. Pyrite.	

* Grade calculated by relating recovered volume to recovered tin + Grade calculated by relating Radford factored theoretical volume to recovered tin Rad F = 80.
 Drillers reported basement at 16 m. Grade from surface to inferred basement at m g SnO2 / m³ *
 Total recovered volume, surface to basement 144.5 l. at 16 m 45 g SnO2 / m³ +
 Total recovered tin 11.88 gSnO2