

997031

# AMDEX MINING LIMITED - NORTH EAST TASMANIA DRILL LOG

Area **STH. MT. CAMERON** Hole No. **E.P.45** Date of Coordinates **1981** Drilling Method **Percussion**  
 Surface RL: **73.1** m Basement RL: **52.6** m Cutting Shoe / Bit diameter: **16.03cm.** Total Volume: **40.3** litres  
 Date: **6/3/81** Driller: **G. Selby** Assistant: **B. Blake** Sample Washer: **R. Munro**

Section	Metres	Sample No	Recovered Volume (l)	Weight Conc (g)	Conc Assay (%Sn)	Recovered Tin (g SnO <sub>2</sub> )	Grade * (g SnO <sub>2</sub> /m <sup>3</sup> )	Grade * (g SnO <sub>2</sub> /m <sup>3</sup> )	Description of Sample
From	To								
0	2	5421	2½ LTRS	102.0	0.84	1.22		12.7	C & f sand (tailings) Tr. of pyrite.
2	4	5422	4 "					12.7	C & f sand. Ilmenite, pyrite.
4	6	5423	18½ "					12.7	Black mud, c & f sand, sm. wash. Tr. of tin, pyrite.
6	8	5424	26½ "	125.4	0.96	1.72		53.3	C & f sand, heavy drift, brown clay. Sm. amount tin, pyrite.
8	10	5425	17 "	168.8	1.93	4.65		36.1	C & f sand, heavy drift, brown clay. Pyrite.
10	12	5426	28 "					36.1	C & f sand, heavy drift, white clay. Ilmenite, pyrite.
12	14	5427	25½ "					36.1	C & f sand, heavy drift. Ilmenite, pyrite.
14	16	5428	22 "					36.1	C & f sand, heavy drift, brown clay. Tr. of tin, ilmenite, pyrite.
16	18	5429	22 "	266.7	11.71	44.6		1383.8	C & f sand, heavy drift, white clay, 3 pieces of med. wash. Tin, ilmenite, pyrite.
18	19	5430	12½ "	445.8	7.17	45.7		2832.7	C & f sand, heavy drift, brown clay, med. wash, pyrite lumps. Tin, pyrite.
19	20	5431	13 "	360.6	16.99	87.5		5429.4	C & f sand, med. wash, pyrite lumps, heavy drift. Tin, pyrite.
20	21	5432	15 "	222.9	11.64	37.1		2299.3	C & f sand, sm. wash, brown clay, decomposed granite. Tin, pyrite.

\* Grade calculated by relating recovered volume to recovered tin. \* Grade calculated by relating Recovered tin to recovered volume.  
 Drillers reported basement at 20.20 m. Grade from surface to intended basement at 20.2 m.  
 Total recovered volume, surface to basement: **194.5** litres. Total recovered tin: **222.5** g SnO<sub>2</sub>.  
 Total recovered volume, surface to intended basement: **20.2** litres. Total recovered tin: **683** g SnO<sub>2</sub>.