ELECTROLYTIC ZINC COMPANY OF A'ASIA LTD.
MINERAL RESOURCES DIVISION — TASMANIA

DIAMOND DRILL CORE GEOCHEMICAL ANALYSES RECORD

HOLE No. DDH STP 217
SHEET No. 1

GRID CO-ORDS: 4280 N ; 4565 E Stg V.
A.M.G. CO-ORDS: 5, 374 393 m N ; 384 190 m E
COLLAR R.L.: 176 m
COLLAR DIP: −60°
AZIMUTH: 108°
TOTAL DEPTH: 249.1m

					LABORATORY	ANALABS													
					ANALYTICAL TECHNIQUE	309		108	114	118	FUSION	108	108	108					
						FIRE ASSAY		AAS	AAS	AAS	XRF	AAS	AAS	AAS					
					DETECTION LIMIT	0.008		0.5	1	1	10	5	5	5					
Sample No.	Sample Type	From	To	Core Rec'd	Sample Length	METAL CONTENT (ppm unless specified)													COMMENTS
						Au		Ag	As	Sn	Sn	Cu	Pb	Zn					
33081	CHIP	0.	5.0	2.7	5.0			x	8	9		25	10	30					
82	"	5.0	10.0	0.4	5.0			x	10	1		5	15	30					
83	"	10.0	15.0	0.1	5.0			1.0	16	9		5	10	25					
84	"	15.0	20.0	0.1	5.0			x	46	1		30	50	165					
85	"	20.0	25.0	0.2	5.0			x	10	9		25	15	125					
86	"	25.0	30.0	3.3	5.0			x	7	2		115	10	140					
87	"	30.0	35.0	3.1	5.0			x	10	1		80	10	105					
88	"	35.0	40.0	3.0	5.0			0.5	4	1		80	5	140					
89	"	40.0	45.0	4.5	5.0			1.0	15	2		50	15	125					
33090	"	45.0	50.0	5.0	5.0			x	7	4		200	10	135					
91	"	50.0	55.0	5.0	5.0			x	6	2		145	15	115					
33092	"	55.0	60.0	4.8	5.0			x	6	5		305	10	180					
37954	SPLIT	60.0	61.0	0.8	1.0	0.02		x	10	2		140	5	145					
55	"	61.0	62.0	0.9	1.0	0.01		1.0	10	2		60	x	150					
56	"	62.0	63.0	0.9	1.0	x		1.0	13	210	490	35	x	150					
57	"	63.0	64.0	1.0	1.0	x		x	3	3		55	x	140					
58	"	64.0	65.0	1.0	1.0	x		0.5	4	4		105	20	130					
59	"	65.0	66.0	1.0	1.0	x		x	4	6		220	10	105					
37960	"	66.0	67.0	1.0	1.0	x		x	2	5		110	10	160					
61	"	67.0	68.0	1.0	1.0	x		x	4	8		65	15	215					
62	"	68.0	69.0	1.0	1.0	x		x	8	4		160	20	140					
63	"	69.0	70.0	1.0	1.0	x		x	8	4		10	20	105					
64	"	70.0	71.0	0.7	1.0	0.02		2.5	620	1500	2000	1600	40	175					
65	"	71.0	72.0	0.4	1.0	0.02		x	20	10		30	15	160					
66	"	72.0	73.0	0.5	1.0	x		x	21	11		70	15	165					
67	"	73.0	74.0	1.0	1.0	0.02		0.5	44	4		40	10	215					
68	"	74.0	75.0	1.0	1.0	0.02		1.0	4	6		80	25	170					
37969	"	75.0	76.0	0.9	1.0	x		1.0	4000	520	860	150	50	180					

A 18623

ELECTROLYTIC ZINC COMPANY OF A'ASIA LTD.
MINERAL RESOURCES DIVISION — TASMANIA

DIAMOND DRILL CORE GEOCHEMICAL ANALYSES RECORD

HOLE No. DDH STP 217
SHEET No. 2

Sample No.	Sample Type	From	To	Core Rec'd	Sample Length	METAL CONTENT (ppm unless specified) Au		Ag	As	Sn	Sn	Cu	Pb	Zn						COMMENTS
37970	SPLIT	76·0	77·0	0·9	1·0	x		x	24	15	45	50	10	155						? Arsenic Zone 'C'
71	"	77·0	78·0	0·9	1·0	x		0·5	24	112	270	90	30	180						
72	"	78·0	79·0	0·9	1·0	x		1·5	4000	760	1000	155	20	100						
73	"	79·0	80·0	0·9	1·0	0·03		2·5	70	40	x	310	30	600						
74	"	80·0	81·0	1·0	1·0	0·01		1·3	12	18	25	100	35	185						
75	"	81·0	82·0	1·0	1·0	x		1·5	14	76	270	40	30	200						
76	"	82·0	83·0	1·0	1·0	x		1·0	4	2	x	15	10	110						
77	"	83·0	84·0	1·0	1·0	x		1·5	10	34	80	25	20	135						
78	"	84·0	85·0	1·0	1·0	x		1·0	8	88	310	45	50	230						
79	"	85·0	86·0	1·0	1·0	x		x	22	200	630	180	40	200						
37980	"	86·0	87·0	1·0	1·0	x		0·5	12	68	330	100	20	180						
81	"	87·0	88·0	1·0	1·0	x		x	5	x		15	20	135						
37982	"	88·0	89·0	1·0	1·0	0·01		x	4	x		20	15	110						
33099	"	89·0	90·0	1·0	1·0	0·02		x	580	5		420	25	185						
33100	"	90·0	90·65	0·65	0·65	x		1·0	8	1		70	20	230						
33066	"	90·65	92·35	1·3	1·70	0·18		0·5	136	9	x	470	5	130						
67	"	92·35	93·35	0·8	1·0	0·21		3·5	1·80%	6400	4950	1550	535	440						Arsenic Zone 'A'
68	"	93·35	94·35	1·0	1·0	x		1·0	305	42	60	900	35	165						
69	"	94·35	95·35	1·0	1·0	x		0·5	160	58	170	325	5	200						
33070	"	95·35	96·35	1·0	1·0	x		x	112	22	60	400	10	210						
71	"	96·35	97·35	1·0	1·0	x		x	76	10	30	350	15	155						
72	"	97·35	98·65	1·3	1·30	0·01		0·5	920	450	360	380	5	155						
73	"	98·65	99·65	1·0	1·0	0·91		4·5	6·00%	3300	3700	2360	40	115						Gold in Polished Section
74	"	99·65	100·70	1·05	1·05	4·01		4·5	15·00%	2000	1550	2250	140	125						Arsenic Zone 'A'
75	"	100·70	101·65	0·95	0·95	0·09		1·5	2700	270	360	465	25	170						
76	"	101·65	102·55	0·90	0·90	0·25		3·0	3·50%	1700	1500	1200	20	1050						
77	"	102·55	103·55	1·0	1·0	0·03		x	560	108	170	285	5	170						
78	"	103·55	104·55	1·0	1·0	0·52		x	6000	920	1050	230	15	130						Related to Arsenic Zone 'A'
79	"	104·55	105·45	0·9	0·9	2·26		1·0	9400	1120	1500	515	45	130						
33080	SPLIT	105·45	106·45	1·0	1·0	0·09		x	250	12	45	40	10	190						
37983	CHIP	106·45	110·0	3·55	3·55			x	6	x		10	20	185						
84	"	110·0	115·0	5·0	5·0			1·0	4	x		100	10	150						
37985	CHIP	115·0	121·0	6·0	6·0			x	14	108	390	60	20	200						

A 18625

ELECTROLYTIC ZINC COMPANY OF A'ASIA LTD.
MINERAL RESOURCES DIVISION — TASMANIA

DIAMOND DRILL CORE GEOCHEMICAL ANALYSES RECORD

HOLE No. DDH STP 217
SHEET No. 3

Sample No.	Sample Type	From	To	Core Rec'd	Sample Length	METAL CONTENT (ppm unless specified)													COMMENTS
						Au		Ag	As	Sn	Sn	Cu	Pb	Zn					
37910	SPLIT	121·0	122·0	1·0	1·0			x	27	3	x	145	15	175					
911	"	122·0	123·6	1·6	1·6			x	8000	610	1200	900	20	160					
37912	SPLIT	123·6	124·6	1·0	1·0			x	23	6	6	5	25	130					
37986	CHIP	124·6	130·0	5·3	5·4			1·5	8	36	140	95	10	155					
987	"	130·0	135·0	4·8	5·0			2·0	8	100	340	75	220	710					
37988	CHIP	135·0	140·1	5·1	5·1			0·5	4	92		145	70	190					
37913	SPLIT	140·1	141·1	1·0	1·0			x	10	1		30	10	125					
14	"	141·1	142·1	1·0	1·0			x	230	31	200	355	15	105					
15	"	142·1	143·1	1·0	1·0			x	680	21	70	340	5	85					
16	"	143·1	144·1	1·0	1·0			x	14	3	15	45	10	95					
17	"	144·1	145·1	1·0	1·0			1·5	46	26	130	180	10	170					
18	"	145·1	146·6	1·6	1·6			2·5	6	220	440	140	140	370					
19	"	146·6	147·6	1·0	1·0	0·05		2·5	960	330	920	670	80	275					
37920	"	147·6	148·6	1·0	1·0	x		1·5	9	400	740	100	150	400					
21	"	148·6	149·6	1·0	1·0	x		1·0	4	150	470	230	5	170					
22	"	149·6	150·6	1·0	1·0	0·05		1·0	7400	2800	3950	410	10	70					
23	"	150·6	151·6	1·0	1·0	x		1·0	500	920	2250	360	20	180					
24	"	151·6	152·6	1·0	1·0	x		0·5	20	2		5	5	120					
25	"	152·6	153·6	1·0	1·0	x		1·0	18	6		275	15	165					
26	"	153·6	154·6	1·0	1·0	0·01		3·0	840	4		1000	10	260					
27	"	154·6	155·6	1·0	1·0	0·02		3·0	1·40%	x		900	15	150					} Arsenic Zone 'B'
28	"	155·6	156·6	1·0	1·0	0·11		2·5	5·60%	x		900	20	120					
29	"	156·6	157·6	1·0	1·0	0·16		1·5	1·40%	x		525	20	145					
37930	"	157·6	158·6	1·0	1·0	0·02		0·5	7400	56	490	210	5	130					
31	"	158·6	159·6	1·0	1·0	0·02		0·5	5200	36	75	320	5	180					
32	"	159·6	160·6	1·0	1·0	0·95		2·0	4400	14	20	700	10	95					} Related to Arsenic Zone 'B'
33	"	160·6	162·1	1·5	1·5	0·18		2·0	7800	27	150	1300	10	110					
379 34	SPLIT	162·1	163·1	1·0	1·0	x		0·5	180	8	x	50	10	220					
37989	CHIP	163·1	165·0	1·9	1·9			0·5	4	x		15	25	150					
37990	"	165·0	170·0	5·0	5·0			x	2	x		5	10	150					
91	"	170·0	175·0	5·0	5·0			0·5	16	x		10	20	180					
37992	CHIP	175·0	179·3	4·2	4·3			2·5	10	22		15	330	190					
37935	SPLIT	179·3	180·3	1·0	1·0	X		1·0	90	180	650	205	260	560					

A 18625

ELECTROLYTIC ZINC COMPANY OF A'ASIA LTD.
MINERAL RESOURCES DIVISION — TASMANIA

DIAMOND DRILL CORE GEOCHEMICAL ANALYSES RECORD

HOLE No. DDH STP 217
SHEET No. 4.

Sample No.	Sample Type	From	To	Core Rec'd	Sample Length	METAL CONTENT (ppm unless specified) Au		Ag	As	Sn	Sn	Cu	Pb	Zn						COMMENTS
37936	SPLIT	180·3	181·3	0·9	1·0	x		1·0	760	72	450	420	30	150						
37	"	181·3	182·3	0·9	1·0	x		1·0	700	76	500	800	30	115						
38	"	182·3	183·3	0·9	1·0	0·08		1·0	1120	460	920	230	35	135						
39	"	183·3	184·3	1·0	1·0	x		1·0	26	128	550	385	30	120						
37940	"	184·3	185·3	1·0	1·0	0·02		1·0	350	6		405	35	110						
41	"	185·3	186·3	0·9	1·0	0·01		2·0	38	x		470	25	100						
37942	SPLIT	186·3	187·3	1·0	1·0	x		3·5	10	x		280	35	85						
37993	CHIP	187·3	190·0	2·5	2·7			1·5	32	x		80	15	100						
94	"	190·0	195·0	5·0	5·0			1·0	40	x		130	20	75						
95	"	195·0	200·0	4·8	5·0			1·0	22	2		140	15	55						
96	"	200·0	205·0	5·0	5·0			x	14	x		30	5	50						
97	"	205·0	210·0	5·0	5·0			1·0	920	x		70	50	200						
98	"	210·0	215·0	5·0	5·0			1·5	20	x		25	10	45						
37999	CHIP	215·0	219·1	5·0	4·1			1·0	30	6		45	10	55						
37943	SPLIT	219·1	220·1	1·0	1·0	x		2·0	3400	8		100	15	75						
44	"	220·1	221·1	1·0	1·0	x		1·0	38	16		10	15	70						
45	"	221·1	222·1	1·0	1·0	x		2·5	24	x		205	25	80						
46	"	222·1	223·1	1·0	1·0	x		2·0	25	x		10	10	60						
47	"	223·1	224·1	1·0	1·0	x		1·0	60	x		15	10	55						
48	"	224·1	225·1	1·0	1·0	0·14		x	114	x		225	10	85						
37949	SPLIT	225·1	226·1	1·0	1·0	0·29		2·0	1160	x		280	15	90						
36701	CHIP	226·1	231·1	5·0	5·0			x	46	3		40	20	85						
37953	SPLIT	231·1	232·1	1·0	1·0	0·03		1·0	24	4		10	20	90						
952	"	232·1	233·1	1·0	1·0	1·04		2·0	36	4		135	25	140						
951	"	233·1	234·1	1·0	1·0	0·36		0·5	18	x		80	20	95						Strong qtz - carb - ~~py~~ py veining.
37950	SPLIT	234·1	235·1	1·0	1·0	0·17		0·5	40	x		90	25	135						Possibly correlate of Arsenic Zone 'D'
36702	CHIP	235·1	240·0	4·9	4·9			x	128	3		50	60	310						
03	"	240·0	245·0	5·0	5·0			x	28	2		25	45	100						
36704	CHIP	245·0	249·1	4·1	4·1			x	34	3		70	70	85						

A 18625