

DIAMOND DRILL CORE GEOCHEMICAL ANALYSES RECORD

LABORATORY						ANALABS											GRID CO-ORDS:		
ANALYTICAL TECHNIQUE						309	AQUA REGIA	108	114	118		108	108	108	108	108			A.M.G. CO-ORDS: 5, 374, 728 SmN 384, 395 BmE
DETECTION LIMIT						FIRE ASSAY	AAS	AAS	AAS	AAS		AAS	AAS	AAS	AAS	AAS		COLLAR R.L.: 174m	
						0.008	0.008	0.5	1	1		5	5	5	50	5		COLLAR DIP: -60°	
																		AZIMUTH: 108° AMG.	
																		TOTAL DEPTH: 198.2m	
Sample No.	Sample Type	From	To	Core Rec'd	Sample Length	METAL CONTENT (ppm unless specified)											COMMENTS		
						Au	Au	Ag	As	Sn		Cu	Pb	Zn	Fe%	Mn			
41624	Grind	63.0	65.0	2.0	2.0		x	0.5	58	x		25	435	100	2.00	560			
41625	Grind	65.0	70.0	5.0	5.0		x	3.5	92	x		130	605	510	6.20	2250			
48404	SPLIT	67.0	68.0	1.0	1.0	0.21		1.0	31	3100		325	15	80	5.05	875		Stringers of Po+Py	
41626	Grind	70.0	75.0	5.0	5.0		x	3.0	240	68		180	280	1850	6.50	2750			
41627	Grind	75.0	80.0	5.0	5.0		x	1.0	47	x		200	5	145	7.10	1850			
48405	SPLIT	74.7	75.7	1.0	1.0	0.01		1.5	16	5		370	30	220	5.50	855			
48407	SPLIT	75.7	76.7	1.0	1.0	0.02		2.0	200	45		485	15	105	6.45	825			
48408	SPLIT	76.7	77.7	1.0	1.0	0.03		1.5	14	10		365	5	85	6.70	730			
48409	SPLIT	77.7	78.7	1.0	1.0	0.01		0.5	6	18		325	10	80	5.85	710			
41628	Grind	80.0	85.0	5.0	5.0		x	0.5	210	x		20	30	120	3.50	2550			
29	Grind	85.0	90.0	5.0	5.0		x	1.0	86	10		40	90	215	5.30	1400			
30	Grind	90.0	95.0	5.0	5.0		x	0.5	38	x		20	30	70	3.05	1300			
41631	Grind	95.0	100.0	5.0	5.0		x	1.0	68	x		45	50	120	4.55	2650			
48410	SPLIT	98.9	99.9	1.0	1.0	0.05		0.5	44	30		125	25	135	8.90	1200			
48411	SPLIT	99.9	100.9	1.0	1.0	0.02		0.5	35	x		75	35	135	9.80	1400			
48632	Grind	100.0	105.0	5.0	5.0		x	2.0	1500	x		85	50	110	5.20	1050			
48412	SPLIT	104.6	104.9	0.3	0.3	0.05		14.5	4.5%	x		845	365	115	5.55	685		50% Stringers Po+Py+Asp	
4863	Grind	105.0	110.0	5.0	5.0		x	0.5	80	x		20	35	150	2.95	1750			
4863	Grind	110.0	115.0	5.0	5.0		x	1.0	280	x		95	200	630	4.75	2350			

DIAMOND DRILL CORE GEOCHEMICAL ANALYSES RECORD

Sample No.	Sample Type	From	To	Core Rec'd	Sample Length	METAL CONTENT (ppm unless specified)											COMMENTS
						Au	Au	Ag	As	Sn		Cu	Pb	Zn	Fe%	Mn	
48413	SPLIT	112.0	113.2	1.2	1.2	0.12		1.5	520	1		160	100	190	4.90	1550	
48635	Grind	115.0	120.0	5.0	5.0		0.008	0.5	160	10		55	145	2250	6.0	2650	Blebs and wispy stringers sph. + py
36	'	120.0	125.0	5.0	5.0		X	X	39	X		10	15	160	5.0	1500	
37	'	125.0	130.0	5.0	5.0		0.008	X	58	X		20	220	2000	3.0	1450	
38	'	130.0	135.0	5.0	5.0		X	X	74	X		20	65	185	2.85	1900	
39	'	135.0	140.0	5.0	5.0		X	X	24	X		10	20	35	2.10	705	
48640	'	140.0	145.0	5.0	5.0		X	X	37	X		40	75	105	3.50	2200	
41	'	145.0	150.0	5.0	5.0		X	X	47	X		45	20	30	3.25	1900	
42	'	150.0	155.0	5.0	5.0		0.008	X	49	X		35	45	90	3.75	3100	
43	'	155.0	160.0	5.0	5.0		X	X	41	X		35	105	195	3.10	2200	
44	"	160.0	165.0	5.0	5.0		X	X	26	X		35	25	55	2.15	1100	
45	"	165.0	170.0	5.0	5.0		X	X	7	X		35	45	180	2.30	755	
46	"	170.0	175.0	5.0	5.0		X	X	21	X		25	55	100	1.95	590	
47	"	175.0	180.0	5.0	5.0		X	0.5	21	X		25	20	25	1.85	565	
48	"	180.0	185.0	5.0	5.0		X	X	41	X		65	25	365	3.05	1000	
49	"	185.0	190.0	5.0	5.0		X	X	22	X		230	20	35	2.50	1000	
48650	"	190.0	195.0	5.0	5.0		X	X	73	X		70	195	4.15	2.90	1400	
48651	Grind	195.0	198.2	3.2	3.2		X	X	30	X		70	30	25	2.20	500	