











































CLEVELAND TIN - GEOLOGY DEPT.

**SAMPLE ASSAY DATA**

FINAL ASSAY REPORT

COST CODE: 955 B

COMPILATION DATE:

COMPILED BY: E. BROOKE

ASSAY DATES: 22.4.82

PAGE 1 OF 1

SAMPLE NUMBER	D.D.H. NUMBER	FACE/STOPE			FROM	TO	LENGTH	ROCK TYPE	%SnT	%SnS	%Cu	%WO <sub>3</sub>	%MoS <sub>2</sub>	%Bi	%CaF <sub>2</sub>	SG
		LENS	LEVEL	DATE												
303 469	C1741	FOLEY		22.4.82	0	2.5	2.5		0.05		0.01	0.020	0.005	0.015	3.45	2.91
470					2.5	5.0	"		0.01		<0.01	0.020	0.005	0.010	2.20	2.86
471					5.0	7.5	"		0.01		<0.01	0.025	0.010	0.005	3.15	2.91
472					7.5	10.0	"		0.01		<0.01	0.020	<0.005	0.005	2.95	2.88
473					10.0	12.5	"		0.02		<0.01	0.050	<0.005	0.015	2.75	2.87
474					12.5	15.0	"		0.03		0.01	0.065	0.010	0.025	3.60	2.91
475					15.0	17.5	"		0.04		0.01	0.035	0.005	0.015	4.60	2.94
476					17.5	20.0	"		0.04		0.02	0.230	0.040	0.105	3.10	2.95
477					20.0	22.5	"		0.03		0.04	0.025	0.005	0.020	1.95	2.91
478					22.5	25.0	"		0.04		0.02	0.070	0.015	0.045	2.10	2.92
479					25.0	27.5	"		0.01		0.01	0.050	0.020	0.015	6.50	2.88
480					27.5	30.0	"		0.03		0.11	0.060	0.190	0.075	5.25	2.93
481					30.0	32.5	"		0.05		0.03	0.015	0.005	0.010	6.35	2.95
482					32.5	35.0	"		0.02		0.01	0.015	<0.005	0.015	1.10	2.89
483					35.0	37.5	"		<0.01		0.01	0.055	0.015	0.020	2.50	2.88
484					37.5	40.0	"		0.03		0.01	0.020	0.010	0.015	3.05	2.88
485					40.0	42.5	"		0.01		0.01	0.070	0.010	0.025	10.3	2.93
486					42.5	45.0	"		0.04		0.02	0.010	0.120	0.015	3.30	2.98
487					45.0	47.5	"		0.01		0.01	0.025	0.015	0.010	5.20	2.92
303 488					47.5	50.0	"		<0.01		<0.01	0.065	0.020	0.015	1.40	2.87

**SAMPLE ASSAY DATA**

FINAL ASSAY REPORT

SAMPLE NUMBER	D.D.H. NUMBER	FACE/SLOPE			Σ	FROM	TO	LENGTH	ROCK TYPE	%SnT	%SnS	%Cu	%WO <sub>3</sub>	%MoS <sub>2</sub>	%Bi	%CaF <sub>2</sub>	S.G.
		LENS	LEVEL	DATE													
303 507A	C1741	FACE				50-0	52-5	2.5		0.01		<0.01	0.015	0.005	0.010	1.40	2.82
508A						52.5	55-0			0.01		0.01	0.055	0.005	0.005	1.25	2.85
509						55-0	57-5			0.01		<0.01	0.025	0.010	0.020	1.05	2.86
510						57-5	60-0			0.01		0.01	0.025	<0.005	0.015	1.60	2.87
511						60-0	62-5			0.01		<0.01	0.035	0.025	0.015	3.30	2.88
512						62.5	65-0			0.02		0.01	0.150	0.045	0.020	2.90	2.85
513						65-0	67-5			0.06		0.02	0.115	0.015	0.040	2.30	2.90
514						67-5	70-0			0.04		0.01	0.255	0.015	0.025	2.60	2.89
515						70-0	72-5			0.06		0.46	0.120	0.010	0.035	2.55	3.01
516						72-5	75-0			0.04		0.01	0.150	0.025	0.025	2.55	2.92
517						75-0	77-5			0.01		0.02	0.215	0.015	0.015	2.70	2.86
518						77.5	80-0			<0.01		<0.01	0.420	0.045	0.020	2.65	2.85
519						80-0	82-5			0.01		<0.01	0.170	0.030	0.020	2.20	2.85
520						82.5	85-0			<0.01		<0.01	0.275	0.050	0.020	2.60	2.88
521						85-0	87-5			<0.01		0.01	0.190	0.015	0.010	1.55	2.87
522						87-5	90-0			<0.01		<0.01	0.205	0.035	0.025	1.25	2.87
523						90-0	92-5			0.01		0.01	0.140	0.030	0.010	1.75	2.88
524						92.5	95-0			0.01		<0.01	0.245	0.015	0.010	1.70	2.87
525						95-0	97-5			<0.01		0.02	0.385	0.030	0.025	2.10	2.89
526						97.5	100-0			0.02		0.01	0.090	0.010	0.005	1.70	2.85

44 158

CLEVELAND TIN - GEOLOGY DEPT.

**SAMPLE ASSAY DATA**

FINAL ASSAY REPORT

COST CODE: 955A

COMPILATION DATE: 11-5-82

COMPILED BY: E. Brooke

PAGE 4 OF 4

ASSAY DATES:

SAMPLE NUMBER	D.D.H. NUMBER	FACE/SLOPE			FROM	TO	LENGTH	ROCK TYPE	%SnT	%SnS	%Cu	%WO <sub>3</sub>	%MoS <sub>2</sub>	%Bi	%CaF <sub>2</sub>	S.G.
		LENS	LEVEL	DATE												
303580	C1741				150-0	152.5	2.5		0.03		0.05	0.155	0.010	0.005	4.75	2.95
581					152.5	155.0	"		0.03		0.26	0.160	0.010	0.010	1.60	2.76
582					155-0	157.5	"		0.06		0.04	0.190	0.005	0.010	1.50	2.79
583					157.5	160.0	"		0.03		0.04	0.175	0.015	0.010	1.40	2.78
584					160-0	162.5	"		0.02		0.03	0.165	0.005	0.010	2.85	2.85
585					162.5	165.0	"		0.04		0.01	0.520	0.010	0.010	2.65	2.82
586					165.0	167.5	"		0.01		0.01	0.200	0.030	0.020	2.75	2.80
587					167.5	170.0	"		0.02		0.01	0.175	0.010	0.020	4.30	2.82
588					170.0	172.5	"		0.01		0.01	0.215	0.005	0.050	16.3	3.02
589					172.5	175.0	"		0.01		0.01	0.085	0.005	0.010	1.25	2.78
590					175.0	177.5	"		0.01		0.01	0.390	0.040	0.015	1.25	2.81
591					177.5	180.0	"		0.01		0.02	0.090	0.005	0.035	1.55	2.83
592					180.0	182.5	"		0.15		0.01	0.070	0.005	0.010	1.40	2.84
593					182.5	185.0	"		0.01		0.01	0.070	0.020	0.025	2.35	2.84
594					185.0	187.5	"		0.02		0.01	0.150	0.025	0.025	3.25	2.85
595					187.5	190.0	"		0.01		0.05	0.080	0.010	0.010	2.55	2.82
596					190.0	192.5	"		0.01		0.01	0.065	0.005	0.015	3.10	2.85
597					192.5	195.0	"		0.01		0.01	0.225	0.040	0.030	3.50	2.83
598					195.0	197.5	"		0.02		0.02	0.065	0.040	0.030	3.90	2.89
599					197.5	200.0	"		0.02		0.02	0.265	0.030	0.050	4.60	2.89

CLEVELAND TIN - GEOLOGY DEPT.

## SAMPLE ASSAY DATA

FINAL ASSAY REPORT

COST CODE: 955B

COMPILATION DATE: 4.5.82

COMPILED BY: F. BROOME PAGE 3 OF 3

ASSAY DATES: .....

SAMPLE NUMBER	D.D.H. NUMBER	FACE/SLOPE			Σ	FROM	TO	LENGTH	ROCK TYPE	%SnT	%SnS	%Cu	%WO <sub>3</sub>	%MoS <sub>2</sub>	%Bi	%CaF <sub>2</sub>	S.G.
		LENS	LEVEL	DATE													
303489	C17111	FLKYS				100-0	102.5	2.5		0.04		40.01	0.380	0.020	0.010	2.25	2.80
490						102.5	105-0	"		0.02		0.01	0.125	0.010	0.015	2.85	2.80
491						105-0	107.5	"		0.01		0.04	0.290	0.020	0.015	2.65	2.80
492						107.5	110-0	"		0.03		0.01	0.210	0.015	0.015	2.20	2.79
493						110-0	112.5	"		0.02		0.01	0.375	0.020	0.010	2.20	2.80
494						112.5	115-0	"		0.01		40.01	0.055	0.005	0.010	1.80	2.76
495						115-0	117.5	"		0.02		0.01	0.265	0.010	0.010	2.05	2.79
496						117.5	120-0	"		0.03		0.04	0.210	0.005	0.010	1.75	2.80
497						120-0	122.5	"		0.03		0.02	0.380	0.010	0.010	2.10	2.78
498						122.5	125-0	"		0.10		0.05	0.325	0.005	0.010	0.80	2.89
499						125-0	127.5	"		0.04		0.02	0.270	0.005	0.005	0.80	2.85
500						127.5	130-0	"		0.05		0.02	0.390	0.010	0.005	1.75	2.78
501						130-0	132.5	"		0.06		0.04	0.325	0.010	0.010	4.45	2.77
502						132.5	135-0	"		0.04		0.03	0.440	0.010	0.015	1.50	2.81
503						135-0	137.5	"		0.03		0.03	0.375	0.010	0.015	1.15	2.76
504						137.5	140-0	"		0.05		0.02	0.25	0.015	0.010	1.25	2.77
505						140-0	142.5	"		0.05		0.06	0.27	0.025	0.020	1.55	2.79
506						142.5	145-0	"		0.05		0.03	0.525	0.005	0.015	3.45	2.85
507						145-0	147.5	"		0.02		0.03	0.445	0.005	0.005	2.10	2.80
508						147.5	150-0	"		0.07		0.03	0.525	0.015	0.025	5.90	2.88