































**SAMPLE ASSAY DATA**

FINAL ASSAY REPORT

SAMPLE NUMBER	D.D.H. NUMBER	FACE/STOPE			Σ	FROM	TO	LENGTH	ROCK TYPE	%SnT	%SnS	%Cu	%WO <sub>3</sub>	%MoS <sub>2</sub>	%Bi	%CaF <sub>2</sub>	S.G.
		LENS	LEVEL	DATE													
304 037	C1811	FOLLEY				50-0	52.5	2.5		0.05		0.01	0.075	0.015	0.025	2.20	2.82
038						52.5	55-0	"		0.11	0.01	0.03	0.115	0.050	0.010	2.10	2.84
039						55-0	57.5	"		0.02		0.02	0.105	0.020	0.015	2.40	2.83
040						57.5	60-0	"		0.01		0.01	0.050	0.025	0.025	2.20	2.83
041						60-0	62.5	"		0.02		0.01	0.230	0.030	0.015	2.80	2.82
042						62.5	65-0	"		0.01		0.01	0.290	0.025	0.020	2.45	2.82
043						65-0	67.5	"		0.01		10.01	0.115	0.015	0.020	2.50	2.78
044						67.5	70-0	"		0.01		0.02	0.320	0.040	0.025	3.75	2.84
045						70-0	72.5	"		0.01		10.01	0.080	0.030	0.010	1.75	2.84
046						72.5	75-0	"		0.01		0.01	0.240	0.015	0.015	1.95	2.84
047						75-0	77.5	"		0.02		0.01	0.130	0.015	0.010	2.15	2.88
048						77.5	80-0	"		0.01		10.01	0.055	0.035	0.010	2.15	2.84
049						80-0	82.5	"		0.01		0.01	0.140	0.015	0.010	1.75	2.87
050						82.5	85-0	"		0.03		0.01	0.085	0.015	0.015	2.10	2.91
051						85-0	87.5	"		0.22	0.01	0.03	0.225	0.020	0.020	8.55	2.97
052						87.5	90-0	"		0.06		0.03	0.380	0.070	0.025	3.45	2.91
053						90-0	92.5	"		0.10	0.01	0.03	0.275	0.030	0.025	5.00	2.92
054						92.5	95-0	"		0.11	0.02	0.12	0.680	0.135	0.020	7.40	3.00
055						95-0	97.5	"		0.02		0.01	0.265	0.025	0.015	2.60	2.89
056						97.5	100-0	"		0.02		0.01	0.165	0.050	0.025	2.90	2.93

**SAMPLE ASSAY DATA**

FINAL ASSAY REPORT

SAMPLE NUMBER	D.D.H. NUMBER	FACE/STOPE			Σ	FROM	TO	LENGTH	ROCK TYPE	%SnT	%SnS	%Cu	%WO <sub>3</sub>	%MoS <sub>2</sub>	%Bi	%CaF <sub>2</sub>	S.G
		LENS	LEVEL	DATE													
304057	E1811	FULEY				100-0	102.5	2.5		0.04		10.01	0.195	0.020	0.020	3.85	2.94
058						102.5	105-0	11		0.02	0.01	0.01	0.170	0.095	0.050	2.75	2.93
059						105-0	107.5	11		0.03		0.01	0.410	0.060	0.020	2.90	2.90
060						107.5	110-0	11		0.02		0.01	0.255	0.055	0.010	2.95	2.93
061						110-0	112.5	11		0.03		0.01	0.730	0.130	0.035	3.05	2.99
062						112.5	115-0	11		0.01		0.02	0.085	0.050	0.015	3.70	2.87
063						115-0	117.5	11		0.01		0.01	0.345	0.075	0.055	3.00	2.87
064						117.5	120-0	11		0.02		0.02	0.185	0.035	0.005	2.45	2.89
065						120-0	122.5	11		0.02		0.03	0.280	0.035	0.025	2.60	2.85
066						122.5	125-0	11		0.01		0.01	0.120	0.020	0.015	2.45	2.86
067						125-0	127.5	11		0.01		10.01	0.075	0.020	0.005	1.95	2.82
068						127.5	130-0	11		0.03		0.01	0.165	0.025	0.025	2.75	2.86
069						130-0	132.5	11		0.03		0.02	0.090	0.010	0.050	13.2	3.05
070						132.5	135-0	11		0.02		0.01	0.150	0.010	0.045	11.0	2.97
071						135-0	137.5	11		0.02	0.01	0.01	0.270	0.060	0.050	11.8	2.96
072						137.5	139-0	1.5		0.03		0.01	0.225	0.030	0.035	13.3	3.03
											0.01						
											0.02						