

SAMPLE NUMBER	D.D.H. NUMBER	FACE/STOPE			Σ	FROM	TO	LENGTH	ROCK TYPE	%SnT	%SnS	%Cu	%WO ₃	%MoS ₂	%Bi	%CaF ₂
		LENS	LEVEL	DATE												
402, 288	C/1902					50.1	51.1	1.0 ^{0.4} CH	L	0.99	0.21	0.60				
289						51.1	52.1	1.0	L	0.89	0.11	0.79				
290						52.1	53.1	1.0	L	0.86	0.14	0.50				
291						53.1	53.6	0.5	L	0.89	0.08	0.95				
		LUCKS.			Σ	50.1	53.6	3.5		0.91	0.14	0.68				
402, 292			46-68-5	2M CORE LOSS		67.2	68.2	1.0	L	0.81	0.01	0.09				
293				2.3M		68.2	69.2	1.0	L	2.19 ^{1.15}	0.05	0.11				
294				LOSS		69.2	70.2	1.0	L	0.92	0.03	0.09				
295						70.2	71.2	1.0	L	3.87 ^{1.15}	0.07	0.09				
296				0.5M		71.2	72.2	1.0	L	2.49 ^{1.15}	0.13	0.16				
297				CORE		72.2	73.2	1.0	L	0.89	0.11	0.37				
298				LOSS		73.2	74.2	1.0	L	2.38 ^{1.15}	0.13	0.42				
299						74.2	75.2	1.0	L	1.52	0.14	0.34				
300				1.1M		75.2	76.2	1.0	L	1.45	0.11	0.27				
301				CORE LOSS		76.2	77.2	1.0	L	1.35	0.03	0.22				
402, 302			0.8	LOSS		77.2	78.4	1.2	1/4 CH	0.83	0.02	0.21				
		KHAKI.E			Σ	67.2	78.4	11.2		1.68	0.07	0.22				
		Khaki E (adjust locke grade in loss)			Σ			11.2		1.12	0.07	0.22				

