

SAMPLE ASSAY DATA

FINAL ASSAY REPORT

COST CODE: 105:22.....
 COMPILATION DATE: 28-11-83.....
 COMPILED BY: *AL*.....
 ASSAY DATES:.....

SAMPLE NUMBER	D.D.H. NUMBER	FACE/STOPE			Σ	FROM	TO	LENGTH	% SnT	% SnS	% Cu	% WO ₃	% MoS ₂	% Bi	% CaF ₂
		LENS	LEVEL	DATE											
403, 154	c2011				01	0.6	0.5	L	1.40	40.01	0.05				
55					12.1	13.2	1.1	L	0.13	0.01	0.06				
56					13.2	14.5	1.3	L	0.39	0.01	0.15				
57					14.5	15.7	1.2	L	0.79	0.02	0.10				
58					16.5	17.7	1.2	L	0.76	0.02	0.10				
59					17.7	18.9	1.2	L	0.76	0.02	0.13				
60					19.2	19.8	0.6	L	1.31	40.01	0.20				
61					20.0	20.7	0.7	L	1.22	0.01	0.24				
62					20.9	21.4	0.5	L	1.19	0.03	0.16				
63					21.8	22.4	0.6	L	0.56	0.02	0.14				
64					22.4	23.1	0.7	L	0.47	0.02	0.09				
65					23.1	24.2	1.1	L	0.52	0.62	0.11				

12.1

0.0137

SAMPLE ASSAY DATA

FINAL ASSAY REPORT

SAMPLE NUMBER	D.D.H. NUMBER	FACE/SLOPE			Σ	FROM	TO	LENGTH	ROCK TYPE	%SnT	%SnS	%Cu	%WO ₃	%MoS ₂	%Bi	%CaF ₂
		LENS	LEVEL	DATE												
403, 166	C2011					26.4	26.9	0.5	L	0.52	0.02	0.09				
67						28.4	29.5	1.1	L	2.58	40.01	0.15				
68						29.5	30.9	1.4	L	3.39	40.01	0.09				
69						30.9	31.8	0.9	ch	0.05	40.01	0.01				
		HBBT			Σ	12.1	30.9	18.8		0.78		0.09				
70						36.9	37.4	0.5	ch	0.25	40.01	0.03				
71						38.2	39.1	0.9	L	1.87	40.01	0.07				
		HAE			Σ	38.2	39.1	0.9		1.87		0.07				
72						42.7	43.8	1.1	L	1.16	40.01	0.14				
73						43.8	44.9	1.1	L	0.72	40.01	0.14				
74						44.9	46.1	1.2	L	1.00	20.01	0.20				
75						46.4	47.1	0.7	L	0.25	40.01	0.06				
		HAW			Σ	42.7	47.1	0.44		0.78		0.13				

44 508

