

1 0290

2589

CABRIA MINENO. 1 D/D HOLEASSAY RESULTS - SPLIT CORE

<u>METRES</u>	<u>Sn</u>	<u>SnO₂</u>
55.95 - 56.50	0.09	0.11
57.50 - 57.90	0.44	0.55
58.31 - 58.71	0.22	0.27
67.00 - 69.70	0.34	0.42
105.30 - 105.65	0.82	1.02
107.28 - 107.80	0.079	0.10
107.80 - 110.20	0.041	0.05

(Personal hand from H.D. Bellidon)
9/1/75 *AB*

1248

D of M	A.O.	CG	CC & M	D.S. & E
RECEIVED				Registrar
15 JUL 1974				E & IL
ANSWERED				
DEPT OF MINES				
REF. No.				

1 0291

2589

8th July, 1974

c.c. to- H. T. Reardon,
BOTHWELL. TAS. 7411

Ringarooma Mining Pty. Ltd.,
22 Dynon Road,
SOUTH KENSINGTON. VIC. 3031

Dear Sirs,

741238 - 741275

Please find below results from assaying diamond drill
sludge samples from the Cambria Mine.

As instructed samples 741246, 741257, 741258 and
741259 being over 0.06% Sn are being assayed for Cu, Fe
and As. These results will be forwarded later.

<u>Reg. No.</u>	<u>Your No.</u>	<u>Footage (metres)</u>	<u>Assay (% Sn)</u>	
741238	CS 1	0 - 2.78	<0.01	
239	CS 2	2.78 - 6.45	<0.01	
240	CS 3	6.45 - 10.71	<0.01	
241	CS 4	10.71 - 15.62	<0.01	
242	CS 5	15.62 - 18.53	<0.01	
243	CS 6	18.53 - 21.38	0.01	
244	CS 7	21.38 - 24.70	0.02	
245	CS 8	24.70 - 27.74	0.04	pink granite & gresen.
246	CS 9	27.74 - 30.78	0.07	
247	CS10	30.78 - 35.05	0.05	
248	CS11	35.05 - 38.44	0.02	
249	CS12	38.44 - 41.26	0.03	
250	CS13	41.26 - 44.34	0.02	
251	CS14	44.34 - 48.80	0.01	
252	CS15	48.80 - 52.00	0.01	
253	CS16	52.00 - 58.11	0.03	Gresens
254	CS17	58.11 - 61.09	0.05	
255	CS18	61.09 - 64.05	0.04	
256	CS19	64.05 - 67.00	0.03	
257	CS20	67.00 - 70.00	0.13	pink granite.
258	CS21	70.00 - 72.85	0.11	
259	CS22	72.85 - 75.20	0.09	
260	CS23	75.20 - 77.82	0.05	
261	CS24	77.82 - 80.73	0.03	
262	CS25	80.73 - 83.76	0.03	

<u>Ref. No.</u>	<u>Your No.</u>	<u>Footage (metres)</u>	<u>Assay (% Sn)</u>
741263	CS26	83.76 - 86.55	0.02
264	CS27	86.55 - 89.55	0.01
265	CS28	89.55 - 92.52	0.02
266	CS29	92.52 - 95.48	0.01
267	CS30	95.48 - 101.47	0.01
268	CS31	101.47 - 104.99	0.01
269	CS32	104.99 - 106.95	0.04
270	CS33	106.95 - 109.58	0.05
271	CS34	109.58 - 114.06	0.04
272	CS35	114.06 - 117.08	0.04
273	CS36	117.08 - 122.00	0.02
274	CS37	122.00 - 125.10	0.02
741275	CS38	125.10 - 127.80	0.01

Griesens. & pink granite

Analyses by: *JE*

Fee Charged: \$38.00

Yours faithfully,

(H. K. Wellington),
Chief Chemist & Metallurgist.

HKW:RA

Enc.

1 0293

410/185

D of M	A.O.	CG	CC & M	D.S.M.E
				Registrar
RECEIVED				E & IL
15 JUL 1974				
ANSWERED				
DEPT OF MINES				
REF. No.				

9th July, 1974

Ringarooma Mining Pty. Ltd.,
22 Dynon Road,
SOUTH KENSINGTON. VIC. 3031

Dear Sirs,

Please find below the additional assays requested on samples above 0.06% Sn.

<u>Reg. No.</u>	<u>Your No.</u>	<u>% Cu</u>	<u>% As</u>	<u>% Fe</u>
741246	CS 9	0.02	0.01	3.6
741257	CS20	0.01	0.01	3.3
741258	CS21	0.01	0.01	2.9
741259	CS22	0.01	0.01	3.2

Analyses by: *J.F.*

Fee Charged: \$12.00

Yours faithfully,

(H. K. Wellington),
Chief Chemist & Metallurgist.

HKW:RA

Enc.