WELL TAROOK-1

357006

IV	CASING - LINER - TUBING RECORD						
Type	Size	Weight	Grade	Thread	No. Joints	Amount	Depth
Rotary	Bushing to	16¾" x 30"	Casing Housing				287.00
30"/20"	Pile Joint				1	33.75	320.75
	20"	106.5 #	X52 LP	JV	10 + Float Shoe	381.81	702.56
Rotary	Bushing to	13⅜" Casing	Housing				293.00
	13⅜"	72 #	C75	Butt	64 + Hanger	2432.59	2725.59
	13⅜"	72 #	C75	8RD	1 + Float Collar	39.17	2764.76
	13⅜"	72 #	C75	Butt	1 + Float Shoe	38.75	2803.51
Pile Joint & Wellhead Recovered							

V	CEMENT RECORD		
String	30"/20" Pile Joint	20" Casing	13⅜" Casing
Type of Cement	45 sx Aust. 'N' neat with 2% $CaCl_2$	550 sx Aust. 'N' with 6% Gel	920 sx Aust. 'N' neat
Number of FT^3	53 cu.ft.	930 cu. ft.	1086 cu. ft.
Average weight of slurry	15.6 ppg	13.7 ppg	15.6 ppg
Cement Top	-	Sea Floor	± 1500' est.
Casing Tested with	-	500 psi	1500 psi
Number of Centralizers	-	6	10
Number of Scratchers	-	-	-
Stage Collar etc.	-	-	-
Remarks	-	Tail with 350 sx neat with 2% $CaCl_2$	Tail with 180 sx neat with 1% $CaCl_2$

B A S I C

E.M. Case
Engineer