


ANALYSIS REPORT FOR STELLAR RESOURCES

REPORT NO / NAME	KM 07/3
REPORT DATE	8 th August 2007
FROM	SGR-1 12-15
TO	SGR-7 124-127
METHOD CODES AND DETECTION LIMITS	AAS-1 Cu, Zn 5ppm AAS-1 Fe 0.01% XRF-1 Sn 10ppm FA-1 Au 0.01ppm
CHIEF CHEMIST	RICKY GELSTON
SIGNATURE	



Burnie RESEARCH LABORATORY

A Division of AMMTEC Ltd

ABN: 40 396 637 856

*Hydrometallurgy Consultants &
Flotation Technology Specialists*

39 River Road, Wivenhoe, PO Box 952, Burnie, TAS 7320 Tel: 61 3 6431 6333 Fax: 61 3 6431 6896

Sample	Cu	Fe	Zn	Sn	Au
	ppm	ppm	ppm	ppm	ppm
SGR-1 12-15	55	7.75	128	110	0.03
SGR-1 15-18	56	8.30	96	100	0.02
SGR-1 18-21	42	8.07	81	50	0.01
SGR-1 21-24	13	4.92	39	20	<0.01
SGR-1 24-27	10	3.98	36	50	0.01
SGR-1 27-30	26	3.73	35	30	<0.01
SGR-1 30-33	6	3.09	37	10	0.01
SGR-1 33-36	47	3.02	44	30	0.01
SGR-1 36-39	90	3.94	53	30	0.01
SGR-1 39-42	26	3.48	37	40	0.01
SGR-1 42-45	101	3.28	69	70	0.01
SGR-1 45-48	87	4.80	79	40	<0.01
SGR-1 48-51	112	6.41	51	60	0.01
SGR-1 51-54	18	5.17	31	30	<0.01
SGR-1 54-57	11	5.33	30	20	0.01
SGR-1 57-60	117	35.4	82	30	<0.01
SGR-1 60-63	39	5.20	34	110	<0.01
SGR-1 63-66	21	4.62	41	130	<0.01
SGR-1 66-69	35	6.13	44	80	<0.01
SGR-1 69-72	34	4.31	33	110	<0.01
SGR-1 72-75	425	7.42	34	70	<0.01
SGR-1 75-78	3217	32.0	40	70	<0.01
SGR-1 78-81	271	6.92	20	70	<0.01
SGR-1 81-84	8605	10.5	35	80	<0.01
SGR-1 84-87	200	7.64	21	40	<0.01
SGR-1 87-90	66	6.40	19	20	<0.01
SGR-1 90-93	36	5.96	19	30	<0.01
SGR-1 93-96	26	5.55	22	30	<0.01
SGR-1 96-99	51	5.55	23	30	0.01
SGR-1 99-102	120	6.16	23	30	<0.01
SGR-1 102-105	273	7.47	19	70	<0.01
SGR-1 105-108	11	6.01	21	20	<0.01
SGR-1 108-111	8	7.73	20	20	<0.01
SGR-1 111-114	132	6.27	41	20	<0.01
SGR-1 114-117	820	6.22	25	10	<0.01
SGR-1 117-120	337	6.73	25	50	0.03
SGR-1 120-123	33	10.1	20	40	<0.01
SGR-1 123-126	24	7.71	19	20	<0.01
SGR-1 126-129	14	7.62	20	20	<0.01
SGR-1 129-132	300	7.81	20	10	<0.01
SGR-1 132-135	113	7.31	24	60	<0.01
SGR-1 135-138	62	5.31	22	80	<0.01
SGR-1 138-141	20	4.78	22	40	<0.01



Burnie RESEARCH LABORATORY

A Division of AMMTEC Ltd

ABN: 40 396 637 856

*Hydrometallurgy Consultants &
Flotation Technology Specialists*

39 River Road, Wivenhoe, PO Box 952, Burnie, TAS 7320 Tel: 61 3 6431 6333 Fax: 61 3 6431 6896

Sample	Cu	Fe	Zn	Sn	Au
	ppm	ppm	ppm	ppm	ppm
SGR-1 141-144	57	3.93	20	20	0.01
SGR-1 144-147	21	3.76	19	40	<0.01
SGR-1 147-150	2954	4.38	25	30	0.01
SGR-1 150-153	110	4.80	26	60	<0.01
SGR-1 153-156	115	4.25	25	80	<0.01
SGR-1 156-159	62	3.80	30	60	<0.01
SGR-1 159-162	54	3.90	27	90	<0.01
SGR-1 162-165	290	4.53	24	70	<0.01
SGR-1 165-168	22	4.24	28	20	<0.01
SGR-1 168-171	101	3.94	22	40	<0.01
SGR-1 171-174	78	4.09	20	70	<0.01
SGR-1 174-177	12	4.53	28	70	<0.01
SGR-1 177-180	7	3.94	20	50	<0.01
SGR-1 180-183	6	3.44	20	70	<0.01
SGR-1 183-186	6	3.50	23	50	<0.01
SGR-1 186-190	16	4.40	24	70	<0.01
SGR-2 12-15	54	7.47	103	80	<0.01
SGR-2 15-18	51	7.97	100	100	<0.01
SGR-2 18-21	111	3.11	36	130	<0.01
SGR-2 21-24	262	2.78	39	120	<0.01
SGR-2 24-27	354	3.22	50	110	<0.01
SGR-2 27-30	86	3.46	28	70	<0.01
SGR-2 30-33	23	4.01	21	60	<0.01
SGR-2 33-36	20	3.93	21	10	<0.01
SGR-2 36-39	37	8.94	41	70	<0.01
SGR-2 39-42	31	10.9	46	80	<0.01
SGR-2 42-45	27	11.3	41	70	<0.01
SGR-2 45-48	14	9.44	54	60	<0.01
SGR-2 48-51	22	8.76	54	50	<0.01
SGR-2 51-54	54	10.2	64	50	<0.01
SGR-2 54-57	47	8.80	74	50	<0.01
SGR-2 57-60	30	9.86	107	30	<0.01
SGR-2 60-63	36	8.71	109	50	<0.01
SGR-2 63-66	58	8.32	104	40	<0.01
SGR-2 66-69	39	8.73	84	70	<0.01
SGR-2 69-72	37	8.69	102	60	<0.01
SGR-2 72-75	48	8.48	97	70	<0.01
SGR-2 75-78	37	8.91	105	70	<0.01
SGR-2 78-81	120	9.55	894	60	<0.01
SGR-2 81-84	45	6.74	52	110	<0.01



Burnie RESEARCH LABORATORY

A Division of AMMTEC Ltd

ABN: 40 396 637 856

*Hydrometallurgy Consultants &
Flotation Technology Specialists*

39 River Road, Wivenhoe, PO Box 952, Burnie, TAS 7320 Tel: 61 3 6431 6333 Fax: 61 3 6431 6896

Sample	Cu	Fe	Zn	Sn	Au
	ppm	ppm	ppm	ppm	ppm
SGR-2 84-87	37	5.58	38	80	<0.01
SGR-2 87-90	53	6.04	29	90	<0.01
SGR-2 90-93	31	5.32	26	80	<0.01
SGR-2 93-96	3498	6.87	52	60	<0.01
SGR-2 96-100	13	3.12	25	10	<0.01
SGR-3 32-35	190	3.04	44	90	<0.01
SGR-3 35-38	2508	2.82	82	50	<0.01
SGR-3 38-41	934	2.43	90	50	<0.01
SGR-3 41-44	404	2.50	71	40	<0.01
SGR-3 44-47	14500	3.39	337	30	0.05
SGR-3 47-50	306	7.98	92	80	<0.01
SGR-3 50-53	441	8.96	71	80	<0.01
SGR-3 53-57	594	4.74	42	70	0.29
SGR-4 24-27	365	5.87	85	110	<0.01
SGR-4 27-30	101	3.77	47	90	<0.01
SGR-4 30-33	61	3.94	50	90	<0.01
SGR-4 33-36	45	3.66	70	140	<0.01
SGR-4 36-39	28	3.69	52	160	<0.01
SGR-4 39-42	22	3.04	70	70	<0.01
SGR-4 42-45	51	4.13	66	100	<0.01
SGR-4 45-48	32	3.57	69	140	<0.01
SGR-4 48-51	40	3.19	66	120	<0.01
SGR-4 51-54	34	5.07	146	130	<0.01
SGR-4 54-57	21	4.01	87	120	<0.01
SGR-4 57-60	23	3.66	121	160	<0.01
SGR-4 60-63	28	4.11	116	150	<0.01
SGR-4 63-66	43	3.56	69	160	<0.01
SGR-4 66-69	119	2.56	1241	160	<0.01
SGR-4 69-72	20	2.60	90	180	<0.01
SGR-4 72-75	24	3.36	60	190	<0.01
SGR-4 75-78	35	2.70	47	210	<0.01
SGR-4 78-81	13	1.67	46	180	<0.01
SGR-4 81-84	298	1.90	39	100	<0.01
SGR-4 84-87	18	1.46	21	120	<0.01
SGR-4 87-90	8	1.56	23	160	<0.01
SGR-4 90-93	5	2.05	26	150	<0.01
SGR-4 93-96	8	2.05	24	120	<0.01
SGR-4 96-99	79	1.82	36	100	<0.01
SGR-4 99-102	125	2.22	41	140	<0.01
SGR-4 102-105	40	7.29	91	70	<0.01



Burnie RESEARCH LABORATORY

A Division of AMMTEC Ltd

ABN: 40 396 637 856

*Hydrometallurgy Consultants &
Flotation Technology Specialists*

39 River Road, Wivenhoe, PO Box 952, Burnie, TAS 7320 Tel: 61 3 6431 6333 Fax: 61 3 6431 6896

Sample	Cu	Fe	Zn	Sn	Au
	ppm	ppm	ppm	ppm	ppm
SGR-4 105-108	26	8.15	74	110	<0.01
SGR-4 108-111	38	5.37	60	110	<0.01
SGR-4 111-114	28	2.32	43	100	<0.01
SGR-4 114-117	62	2.53	27	100	<0.01
SGR-4 117-120	31	1.97	34	90	<0.01
SGR-4 120-123	39	2.33	48	100	<0.01
SGR-4 123-126	56	2.57	35	90	<0.01
SGR-4 126-129	62	3.18	29	110	<0.01
SGR-4 129-132	79	2.53	34	100	<0.01
SGR-4 132-135	116	1.95	33	100	<0.01
SGR-4 135-138	131	1.98	51	100	<0.01
SGR-4 138-141	254	2.06	47	90	<0.01
SGR-4 141-144	168	2.17	32	90	<0.01
SGR-4 144-147	189	2.87	41	100	<0.01
SGR-4 147-150	150	3.17	44	120	<0.01
SGR-4 150-153	397	2.93	69	140	<0.01
SGR-4 153-156	89	2.41	37	90	<0.01
SGR-4 156-159	28	2.70	33	80	<0.01
SGR-4 159-162	28	3.63	36	90	<0.01
SGR-4 162-165	71	2.93	42	120	<0.01
SGR-4 165-168	64	5.15	37	90	<0.01
SGR-4 168-172	85	3.73	31	110	<0.01
SGR-5 30-32	12	3.92	75	90	<0.01
SGR-5 32-34	46	4.35	79	100	<0.01
SGR-6 37-40	64	4.45	59	70	<0.01
SGR-6 40-43	35	5.60	158	60	<0.01
SGR-6 43-46	44	6.78	141	80	<0.01
SGR-6 46-49	45	4.68	131	70	<0.01
SGR-6 49-52	22	3.80	97	60	<0.01
SGR-6 52-55	33	3.90	82	70	<0.01
SGR-6 55-58	36	3.39	62	170	<0.01
SGR-6 58-61	74	8.96	112	90	<0.01
SGR-6 61-64	20	3.58	64	90	<0.01
SGR-6 64-67	18	3.14	60	70	<0.01
SGR-6 67-70	37	7.44	116	80	<0.01
SGR-6 70-73	32	7.83	179	70	<0.01
SGR-6 73-76	32	4.25	107	40	<0.01
SGR-6 76-79	30	5.08	112	60	<0.01
SGR-6 79-82	19	3.74	103	60	<0.01
SGR-6 82-85	96	2.96	52	80	<0.01



Burnie RESEARCH LABORATORY

A Division of AMMTEC Ltd

ABN: 40 396 637 856

*Hydrometallurgy Consultants &
Flotation Technology Specialists*

39 River Road, Wivenhoe, PO Box 952, Burnie, TAS 7320 Tel: 61 3 6431 6333 Fax: 61 3 6431 6896

Sample	Cu	Fe	Zn	Sn	Au
	ppm	ppm	ppm	ppm	ppm
SGR-6 85-88	937	2.05	59	60	<0.01
SGR-7 7-10	78	6.40	83	130	<0.01
SGR-7 10-13	32	5.64	67	110	<0.01
SGR-7 13-16	53	16.4	56	240	<0.01
SGR-7 16-19	90	5.93	58	170	<0.01
SGR-7 19-22	177	16.7	47	80	<0.01
SGR-7 22-25	277	30.7	77	30	<0.01
SGR-7 25-28	154	12.8	49	60	<0.01
SGR-7 28-31	81	5.56	40	90	<0.01
SGR-7 31-34	120	5.45	33	60	<0.01
SGR-7 34-37	83	4.18	36	90	<0.01
SGR-7 37-40	22	3.96	31	20	<0.01
SGR-7 40-43	39	5.90	31	70	<0.01
SGR-7 43-46	94	7.41	26	60	<0.01
SGR-7 46-49	75	9.87	32	60	<0.01
SGR-7 49-52	55	7.38	32	30	<0.01
SGR-7 52-55	56	6.87	36	40	<0.01
SGR-7 55-58	48	7.28	34	40	<0.01
SGR-7 58-61	58	6.50	36	50	<0.01
SGR-7 61-64	53	5.97	31	40	<0.01
SGR-7 64-67	140	8.41	46	30	<0.01
SGR-7 67-70	135	8.75	44	60	<0.01
SGR-7 70-73	274	8.59	36	40	<0.01
SGR-7 73-76	134	5.43	23	20	<0.01
SGR-7 76-79	1093	2.48	26	<10	<0.01
SGR-7 79-82	96	7.04	27	<10	<0.01
SGR-7 82-85	8	6.58	26	<10	<0.01
SGR-7 85-88	9	5.61	30	10	<0.01
SGR-7 88-91	21	6.55	32	20	<0.01
SGR-7 91-94	123	6.73	36	30	<0.01
SGR-7 94-97	874	7.39	27	30	<0.01
SGR-7 97-100	462	5.67	26	10	<0.01
SGR-7 100-103	359	5.21	29	10	<0.01
SGR-7 103-106	181	6.46	27	10	<0.01
SGR-7 106-109	141	8.16	30	20	<0.01
SGR-7 109-112	30	6.66	21	10	<0.01
SGR-7 112-115	331	7.08	28	60	<0.01
SGR-7 115-118	169	5.41	27	20	<0.01
SGR-7 118-121	58	5.42	27	30	<0.01
SGR-7 121-124	130	6.91	28	20	<0.01
SGR-7 124-127	32	6.21	28	10	<0.01



Burnie RESEARCH LABORATORY

A Division of AMMTEC Ltd

ABN: 40 396 637 856

*Hydrometallurgy Consultants &
Flotation Technology Specialists*

39 River Road, Wivenhoe, PO Box 952, Burnie, TAS 7320 Tel: 61 3 6431 6333 Fax: 61 3 6431 6896

Duplicates

Sample	Cu	Fe	Zn	Sn	Au
	ppm	ppm	ppm	ppm	ppm
SGR-1 12-15	n/a	n/a	n/a	n/a	<0.01
SGR-1 48-51	n/a	n/a	n/a	50	n/a
SGR-1 75-78	n/a	n/a	n/a	n/a	<0.01
SGR-1 108-111	9	7.85	20	n/a	n/a
SGR-1 123-126	n/a	n/a	n/a	<10	n/a
SGR-1 138-141	n/a	n/a	n/a	n/a	<0.01
SGR-1 165-168	n/a	n/a	n/a	20	n/a
SGR-1 177-180	8	4.04	23	n/a	n/a
SGR-2 12-15	n/a	n/a	n/a	n/a	<0.01
SGR-2 33-36	n/a	n/a	n/a	20	n/a
SGR-2 48-51	n/a	n/a	n/a	n/a	<0.01
SGR-2 87-90	n/a	n/a	n/a	80	n/a
SGR-2 69-72	37	8.69	102	n/a	n/a
SGR-3 44-47	n/a	n/a	n/a	n/a	0.05
SGR-3 53-57	n/a	n/a	n/a	90	n/a
SGR-4 39-42	20	2.96	62	n/a	n/a
SGR-4 54-57	n/a	n/a	n/a	130	n/a
SGR-4 81-84	n/a	n/a	n/a	n/a	<0.01
SGR-4 108-111	39	5.16	60	n/a	n/a
SGR-4 117-120	n/a	n/a	n/a	100	n/a
SGR-4 144-147	n/a	n/a	n/a	n/a	<0.01
SGR-6 37-40	65	4.66	65	n/a	n/a
SGR-6 79-82	n/a	n/a	n/a	50	n/a
SGR-6 82-85	n/a	n/a	n/a	n/a	<0.01
SGR-7 25-28	151	12.5	51	n/a	n/a
SGR-7 43-46	n/a	n/a	n/a	n/a	<0.01
SGR-7 70-73	n/a	n/a	n/a	40	n/a
SGR-7 106-109	n/a	n/a	n/a	n/a	<0.01
SGR-7 124-127	30	6.15	27	20	n/a