



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Page: 1  
Total # Pages: 5 (A – D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE AD22061837

Project: Exploration

P.O. No.: P280332

This report is for 160 samples of Drill Core submitted to our lab in Burnie, TAS, Australia on 2-FEB-2022.

The following have access to data associated with this certificate:

PAUL DALE

ROBERT REID

## SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
SPLIT-X	Create X Label
LOG-22	Sample login – Rcd w/o BarCode
CRU-31	Fine crushing – 70% <2mm
SPL-21	Split sample – riffle splitter
PUL-32	Pulverize 1000g to 85% < 75 um
LEV-01	Waste Disposal Levy
LOG-24	Pulp Login – Rcd w/o Barcode
CRU-QC	Crushing QC Test
SPL-22Y	Split Sample – Boyd Rotary Splitter
BAG-01	Bulk Master for Storage
PUL-QC	Pulverizing QC Test

## ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
ME-MS61L	Super Trace Lowest DL 4A by ICP-MS	
ME-OG62	Ore Grade Elements – Four Acid	ICP-AES
Pb-OG62	Ore Grade Pb – Four Acid	
Au-AA25	Ore Grade Au 30g FA AA finish	AAS

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

\*\*\*\*\* See Appendix Page for comments regarding this certificate \*\*\*\*\*

Signature:

Shaun Kenny, Brisbane Laboratory Manager



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 2 - A  
Total # Pages: 5 (A - D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg 0.02	Au-AA25 Au ppm 0.01	PUL-QC Pass7Sum % 0.01	ME-MS61L Ag ppm 0.002	ME-MS61L Al % 0.01	ME-MS61L As ppm 0.02	ME-MS61L Ba ppm 1	ME-MS61L Be ppm 0.02	ME-MS61L Bi ppm 0.002	ME-MS61L Ca % 0.01	ME-MS61L Cd ppm 0.005	ME-MS61L Ce ppm 0.01	ME-MS61L Co ppm 0.005	ME-MS61L Cr ppm 0.3	ME-MS61L Cs ppm 0.01
CEH003_1		2.76	<0.01	97.0	0.013	7.28	0.66	1000	2.59	0.034	0.89	0.010	91.3	1.435	1.5	1.87
CEH003_2		2.90	<0.01	98.0	0.073	6.98	3.66	880	2.26	0.321	3.15	0.050	66.3	6.29	3.0	2.89
CEH003_3		2.21	<0.01	98.0	0.023	6.58	3.82	2830	2.01	0.342	3.44	0.029	84.5	3.26	2.2	2.22
CEH003_4		2.26	<0.01		0.024	7.62	2.30	990	2.39	0.397	1.44	0.008	92.5	2.37	1.4	3.73
CEH003_5		2.18	<0.01		0.033	7.29	2.82	1690	2.41	0.434	1.90	0.013	100.5	2.75	1.5	3.38
CEH003_6		2.09	<0.01		0.023	7.63	2.43	860	2.59	0.313	1.73	0.016	97.9	2.50	2.3	2.98
CEH003_7		2.51	<0.01		0.017	6.86	2.03	660	1.54	0.134	0.93	0.020	79.2	1.970	1.8	1.10
CEH003_8		2.59	<0.01		0.010	7.09	1.57	860	1.77	0.067	1.01	<0.005	81.4	1.405	1.8	1.47
CEH003_9		2.39	<0.01		0.007	7.33	1.38	1180	2.10	0.048	1.13	0.007	97.2	1.195	1.9	2.50
CEH003_10		2.30	<0.01		0.022	7.36	1.33	1370	2.01	0.070	1.43	0.015	91.3	1.410	2.4	2.20
CEH003_11		1.46	<0.01		0.022	8.25	2.15	1420	2.86	0.317	1.69	0.033	89.2	7.78	4.2	3.94
CEH003_12		1.64	<0.01		0.054	6.38	3.34	1570	2.11	0.502	1.51	0.041	93.0	7.32	1.9	2.63
CEH003_13		1.43	<0.01		0.010	8.21	8.80	940	1.80	0.037	6.50	0.041	28.6	24.9	23.5	7.15
CEH003_14		2.54	<0.01		0.016	6.93	1.59	860	1.84	0.107	1.51	0.010	107.0	2.57	2.3	2.14
CEH003_15		2.13	0.01		0.015	7.42	1.60	1250	2.32	0.113	1.57	0.007	94.6	1.975	1.6	2.15
CEH003_16		2.18	0.01		0.021	6.90	1.99	1440	2.40	0.098	1.65	0.016	88.8	1.895	2.1	2.68
CEH003_17		2.10	0.01		0.019	7.16	1.61	1670	2.39	0.080	1.27	0.017	94.9	1.440	2.4	2.79
CEH003_18		2.57	<0.01		0.034	7.43	2.49	1390	2.27	0.180	1.19	0.026	100.5	2.70	2.7	3.02
CEH003_19		2.44	0.01		0.054	7.99	1.97	1170	2.34	0.130	1.32	0.011	104.5	1.995	1.6	3.76
CEH003_20		2.70	<0.01		0.025	7.10	2.64	1150	2.10	0.138	1.25	0.008	93.1	2.06	2.5	2.75
CEH003_21		0.07	4.27		0.815	7.45	454	570	2.54	7.49	1.08	0.064	76.5	18.25	193.0	5.25
CEH003_22		2.37	<0.01		0.032	7.22	2.67	1120	2.09	0.131	1.09	<0.005	93.8	1.820	2.6	2.38
CEH003_23		2.52	<0.01		0.030	7.33	2.97	1020	2.15	0.126	0.84	<0.005	93.1	1.895	2.6	2.46
CEH003_24		2.41	<0.01		0.050	6.94	3.77	670	1.91	0.200	1.63	0.082	86.1	3.08	3.0	2.39
CEH003_25		2.54	<0.01		0.064	7.51	3.71	780	2.19	0.264	1.37	0.081	91.3	2.94	2.7	2.83
CEH003_26		2.79	<0.01		0.034	7.21	3.36	880	2.19	0.154	1.17	0.055	87.1	2.29	2.7	2.95
CEH003_27		2.54	<0.01		0.037	7.18	3.14	750	2.06	0.142	1.43	0.104	93.0	2.71	2.7	2.89
CEH003_28		0.83	<0.01		0.054	6.80	4.25	660	1.87	0.406	1.30	0.073	100.5	4.24	5.9	2.38
CEH003_29		2.34	<0.01		0.021	6.40	1.36	690	1.69	0.058	1.22	0.014	83.2	1.205	2.0	1.72
CEH003_30		2.34	<0.01		0.021	7.02	2.52	770	1.88	0.359	1.10	0.014	88.7	3.12	2.1	2.29
CEH003_31		3.79	<0.01		0.026	6.90	1.92	800	2.00	0.275	1.30	0.007	95.5	2.68	2.4	2.33
CEH003_32		3.43	<0.01		0.027	6.90	1.42	790	1.87	0.180	1.42	0.014	95.7	2.16	3.6	1.93
CEH003_33		3.46	<0.01		0.025	6.99	1.48	770	1.86	0.070	1.07	0.009	101.0	1.420	2.5	2.20
CEH003_34		3.83	<0.01		0.035	6.54	1.27	790	1.81	0.205	1.15	0.020	97.9	1.930	2.4	1.80
CEH003_35		3.42	0.04		0.019	7.13	1.78	810	1.92	0.177	1.29	0.013	80.2	2.12	12.9	1.29
CEH003_36		3.79	<0.01		0.024	7.06	1.66	690	1.88	0.228	1.40	0.006	89.9	2.22	2.2	1.78
CEH003_37		3.88	<0.01		0.025	7.74	1.64	950	2.33	0.238	1.38	0.015	83.5	2.39	2.0	3.75
CEH003_38		3.76	<0.01		0.019	7.30	1.60	790	2.13	0.120	1.25	0.011	88.8	1.890	2.1	2.74
CEH003_39		3.90	<0.01		0.029	7.53	1.60	690	2.06	0.059	1.34	0.009	89.8	1.535	2.4	2.52
CEH003_40		3.96	<0.01		0.053	6.90	1.26	660	1.94	0.040	1.30	0.005	87.8	1.640	1.6	2.62



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 2 - B  
Total # Pages: 5 (A - D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L
		Cu	Fe	Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni
		ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm
		0.02	0.002	0.05	0.05	0.004	0.005	0.01	0.005	0.2	0.01	0.2	0.02	0.001	0.005	0.08
CEH003_1		4.97	1.270	15.50	0.13	4.10	0.014	3.17	43.6	7.1	0.50	182.5	0.38	1.800	14.05	0.60
CEH003_2		8.05	2.69	17.00	0.16	3.86	0.043	3.20	29.7	10.7	0.82	809	2.77	1.430	12.05	2.06
CEH003_3		3.56	2.29	16.10	0.18	3.77	0.042	2.39	39.4	9.8	0.51	873	1.37	2.10	11.35	1.10
CEH003_4		3.11	2.31	18.55	0.18	4.31	0.065	3.11	44.7	11.4	0.50	416	0.79	2.05	13.15	0.55
CEH003_5		2.96	2.26	16.60	0.20	4.23	0.045	2.89	47.9	11.0	0.45	595	1.25	2.11	13.00	0.41
CEH003_6		2.48	2.47	18.10	0.19	4.67	0.056	2.81	47.4	10.2	0.50	522	1.83	2.53	14.00	1.74
CEH003_7		2.08	2.01	13.65	0.15	4.08	0.035	1.33	38.0	5.8	0.39	401	0.72	3.69	12.50	0.39
CEH003_8		1.62	2.10	14.85	0.15	3.92	0.039	1.69	38.1	6.4	0.44	472	0.46	3.31	11.80	0.40
CEH003_9		2.03	2.20	16.60	0.17	4.27	0.054	2.36	48.4	8.1	0.51	511	0.47	2.93	12.35	0.50
CEH003_10		2.63	2.21	15.95	0.17	4.46	0.044	2.51	44.5	8.4	0.55	596	0.91	2.82	12.80	0.58
CEH003_11		4.07	2.89	19.25	0.19	4.43	0.061	3.38	45.1	12.1	0.78	711	0.74	2.42	12.50	3.52
CEH003_12		13.45	2.41	13.40	0.19	3.73	0.042	3.32	45.9	8.2	0.47	519	0.92	1.435	10.20	1.78
CEH003_13		16.35	5.16	15.85	0.21	1.790	0.051	3.23	13.30	18.2	1.88	2380	0.29	1.885	3.62	24.5
CEH003_14		4.83	2.14	14.40	0.16	4.04	0.034	2.03	52.1	8.0	0.50	573	1.20	3.15	11.95	0.55
CEH003_15		1.78	2.18	17.25	0.18	4.17	0.041	3.12	46.0	8.7	0.49	584	1.08	2.54	12.70	0.49
CEH003_16		3.19	1.970	15.40	0.16	4.05	0.033	3.44	42.9	8.1	0.40	542	1.10	2.12	12.65	0.65
CEH003_17		1.34	2.00	16.05	0.16	4.14	0.033	4.25	46.3	9.4	0.45	503	0.95	1.725	13.35	0.36
CEH003_18		1.56	2.21	16.60	0.18	4.50	0.042	3.71	49.1	9.6	0.46	508	1.40	2.29	13.60	0.71
CEH003_19		1.27	2.29	18.55	0.17	4.77	0.044	3.49	50.8	10.6	0.45	565	1.11	2.94	14.40	0.38
CEH003_20		1.20	2.06	15.35	0.16	4.16	0.037	3.19	46.1	8.8	0.36	526	1.35	2.54	12.85	0.53
CEH003_21		66.0	4.58	19.35	0.19	4.55	0.052	1.87	40.2	29.1	1.29	336	4.19	0.779	24.0	89.2
CEH003_22		1.58	2.17	15.20	0.14	4.27	0.036	3.09	46.4	9.2	0.36	509	1.28	2.64	12.40	0.71
CEH003_23		1.50	2.15	15.55	0.15	4.50	0.044	2.94	46.9	10.5	0.37	575	1.36	2.65	12.90	0.90
CEH003_24		2.60	2.62	14.60	0.17	3.99	0.034	2.67	42.0	12.0	0.59	1320	1.81	2.50	10.80	1.16
CEH003_25		6.23	2.22	16.55	0.15	4.45	0.037	3.03	45.6	9.7	0.38	698	1.71	2.63	11.85	1.20
CEH003_26		1.54	1.990	15.60	0.14	4.30	0.040	2.89	44.1	7.6	0.31	596	1.63	2.63	11.90	0.98
CEH003_27		1.54	2.32	15.70	0.16	4.32	0.038	2.77	45.5	9.7	0.39	885	1.49	2.71	12.15	1.30
CEH003_28		2.77	2.00	15.90	0.17	4.54	0.037	2.57	50.5	7.0	0.30	657	2.93	2.54	12.30	1.66
CEH003_29		1.64	1.850	13.20	0.12	3.70	0.039	2.15	41.5	5.7	0.28	697	1.09	2.83	10.85	0.45
CEH003_30		1.50	2.03	15.05	0.14	4.19	0.040	2.42	44.4	7.7	0.31	498	1.27	3.00	12.15	0.65
CEH003_31		1.82	2.06	15.05	0.15	4.13	0.038	2.49	47.6	8.0	0.31	534	1.46	2.84	11.75	0.58
CEH003_32		1.15	2.12	15.40	0.14	4.14	0.032	2.41	47.5	8.8	0.34	570	1.12	2.86	11.45	0.56
CEH003_33		1.04	1.980	15.05	0.15	4.23	0.028	2.23	49.9	8.1	0.31	469	0.83	3.13	12.10	0.45
CEH003_34		1.65	1.770	13.25	0.14	3.92	0.032	2.19	49.1	6.7	0.27	469	0.86	2.88	10.75	0.65
CEH003_35		1.24	1.930	14.95	0.15	3.78	0.035	2.23	38.6	8.6	0.32	489	0.86	3.21	11.25	1.33
CEH003_36		1.34	2.15	15.05	0.15	4.08	0.030	2.15	44.7	10.0	0.37	553	0.88	3.07	12.20	0.55
CEH003_37		1.34	2.49	17.45	0.15	4.16	0.045	2.84	40.5	11.9	0.44	565	1.03	2.95	13.00	0.56
CEH003_38		1.14	2.23	16.55	0.17	4.08	0.037	2.37	42.3	10.1	0.39	499	1.23	3.08	12.60	0.51
CEH003_39		0.92	2.11	16.30	0.18	4.08	0.039	2.20	44.4	9.1	0.35	542	0.99	3.36	12.55	0.48
CEH003_40		1.21	1.920	15.20	0.18	3.88	0.030	2.13	43.1	7.0	0.32	480	0.77	3.03	12.60	0.48



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 2 - C  
Total # Pages: 5 (A - D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L
		P	Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti
		%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.001	0.01	0.02	0.0004	0.01	0.02	0.01	0.006	0.02	0.02	0.01	0.005	0.004	0.001
CEH003_1		0.023	2.61	124.0	0.0008	0.01	0.57	4.46	0.023	1.96	98.7	0.99	<0.005	18.20	0.184
CEH003_2		0.031	11.25	126.0	0.0011	0.09	0.77	7.33	0.051	2.66	170.0	0.88	0.014	13.75	0.236
CEH003_3		0.024	7.59	114.0	0.0012	0.15	0.62	4.50	0.048	2.16	195.5	0.85	<0.005	15.55	0.150
CEH003_4		0.027	10.30	159.5	0.0010	0.09	0.60	4.61	0.046	2.56	111.5	0.96	<0.005	18.85	0.176
CEH003_5		0.026	14.70	149.5	0.0012	0.20	0.57	4.50	0.062	2.40	162.5	0.94	<0.005	18.20	0.172
CEH003_6		0.028	8.74	147.5	0.0014	0.09	0.54	5.12	0.033	2.84	125.5	1.04	<0.005	20.1	0.187
CEH003_7		0.025	5.64	62.8	0.0009	0.07	0.40	3.88	0.040	1.86	159.5	0.90	<0.005	18.00	0.169
CEH003_8		0.025	3.90	78.9	0.0012	0.02	0.39	4.09	0.046	2.04	149.0	0.85	<0.005	17.30	0.160
CEH003_9		0.026	3.90	110.0	0.0014	0.01	0.46	4.38	0.046	2.18	150.5	0.89	<0.005	18.45	0.166
CEH003_10		0.027	6.08	107.0	0.0013	0.02	0.46	4.56	0.027	2.19	166.5	0.91	<0.005	19.45	0.170
CEH003_11		0.029	10.15	157.5	0.0014	0.32	0.56	7.92	0.176	2.33	157.5	0.89	0.009	18.65	0.199
CEH003_12		0.021	27.5	130.0	0.0013	0.90	0.69	4.03	0.529	2.05	124.0	0.73	0.020	16.10	0.134
CEH003_13		0.032	4.12	165.0	0.0008	0.07	0.61	28.4	0.045	0.89	215	0.26	<0.005	5.80	0.286
CEH003_14		0.025	9.71	88.0	0.0012	0.18	0.44	4.35	0.091	2.11	185.0	0.86	<0.005	17.55	0.159
CEH003_15		0.026	8.51	121.0	0.0015	0.05	0.46	4.66	0.054	2.22	179.0	0.91	<0.005	18.10	0.173
CEH003_16		0.025	14.45	124.5	0.0013	0.07	0.46	4.63	0.035	2.15	174.5	0.89	<0.005	17.50	0.170
CEH003_17		0.026	12.75	141.0	0.0015	0.04	0.47	4.60	0.021	2.13	162.0	0.93	<0.005	18.10	0.181
CEH003_18		0.027	21.5	138.0	0.0015	0.18	0.51	4.72	0.068	2.23	171.0	0.96	<0.005	19.25	0.182
CEH003_19		0.028	15.45	139.5	0.0015	0.07	0.47	5.00	0.051	2.48	185.5	1.03	<0.005	21.1	0.190
CEH003_20		0.025	16.20	115.5	0.0014	0.09	0.50	4.33	0.051	2.21	169.5	0.91	<0.005	18.20	0.170
CEH003_21		0.081	14.25	80.7	0.0039	0.04	20.7	16.45	0.417	8.12	241	1.61	0.206	10.80	0.546
CEH003_22		0.026	16.05	110.5	0.0011	0.06	0.56	4.39	0.056	2.16	165.0	0.94	<0.005	18.45	0.166
CEH003_23		0.027	10.75	113.0	0.0012	0.07	0.69	4.57	0.041	2.10	150.5	0.90	<0.005	18.65	0.174
CEH003_24		0.024	8.65	109.0	0.0010	0.09	1.65	4.36	0.057	1.94	128.5	0.77	<0.005	16.45	0.150
CEH003_25		0.027	10.00	126.0	0.0009	0.11	2.01	4.99	0.055	2.15	143.5	0.82	<0.005	18.50	0.166
CEH003_26		0.025	9.88	118.0	0.0010	0.11	1.14	4.65	0.031	2.01	151.0	0.87	<0.005	18.15	0.161
CEH003_27		0.025	10.75	119.0	0.0013	0.07	1.42	4.73	0.067	2.15	149.5	0.87	<0.005	17.85	0.167
CEH003_28		0.024	13.45	117.0	0.0011	0.09	1.31	4.99	0.116	2.29	141.5	0.86	0.006	17.95	0.169
CEH003_29		0.023	8.02	87.0	0.0009	0.01	0.69	3.88	0.054	1.84	160.0	0.77	<0.005	15.85	0.149
CEH003_30		0.025	7.94	98.3	0.0009	0.08	0.60	4.46	0.047	2.11	171.0	0.86	<0.005	17.90	0.168
CEH003_31		0.024	9.91	100.5	0.0010	0.07	0.67	4.35	0.057	2.01	170.5	0.82	<0.005	17.55	0.157
CEH003_32		0.024	12.40	96.8	0.0011	0.05	0.55	4.52	0.054	1.89	172.0	0.83	<0.005	17.50	0.156
CEH003_33		0.025	8.03	93.1	0.0011	0.02	0.61	4.39	0.049	1.96	176.5	0.86	<0.005	18.10	0.169
CEH003_34		0.023	11.25	84.7	0.0013	0.05	0.45	3.98	0.068	1.79	173.5	0.78	<0.005	16.15	0.151
CEH003_35		0.026	8.16	76.2	<0.0004	0.07	0.47	4.90	0.015	1.90	183.5	0.80	<0.005	15.60	0.175
CEH003_36		0.025	15.75	82.2	<0.0004	0.07	0.47	4.55	0.024	2.25	177.0	0.85	<0.005	16.45	0.171
CEH003_37		0.028	8.68	110.0	<0.0004	0.06	0.53	4.89	0.022	2.34	195.0	0.91	<0.005	18.25	0.180
CEH003_38		0.026	6.26	99.0	<0.0004	0.03	0.48	4.75	0.020	2.33	191.0	0.86	<0.005	17.45	0.175
CEH003_39		0.027	7.29	93.9	<0.0004	0.02	0.46	4.68	0.013	2.18	194.0	0.87	<0.005	17.80	0.176
CEH003_40		0.025	6.35	98.0	<0.0004	0.01	0.53	4.34	0.020	2.21	182.0	0.85	<0.005	17.15	0.170



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 2 – D  
Total # Pages: 5 (A – D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	Pb-OG62	CRU-QC
		U	V	W	Y	Zn	Pb	Pass2mm
		ppm	ppm	ppm	ppm	ppm	%	%
		0.01	0.1	0.008	0.01	0.2	0.001	0.01
CEH003_1		4.99	11.2	1.080	26.3	20.1	127.0	92.0
CEH003_2		3.68	43.3	0.749	22.2	56.7	118.5	80.3
CEH003_3		3.60	12.8	0.535	27.0	41.4	112.5	
CEH003_4		5.21	9.1	0.526	30.5	41.8	127.5	
CEH003_5		4.76	8.9	0.437	31.5	42.6	126.0	
CEH003_6		5.21	10.2	0.394	36.9	53.4	136.5	
CEH003_7		4.72	7.2	0.371	28.0	53.6	121.5	
CEH003_8		4.42	7.9	0.392	31.6	51.5	118.5	
CEH003_9		4.67	9.1	0.400	33.6	52.5	126.5	
CEH003_10		4.71	9.6	0.671	39.1	55.9	130.0	
CEH003_11		4.68	32.4	0.583	36.1	72.5	132.0	
CEH003_12		4.26	10.3	0.499	31.0	41.9	112.0	
CEH003_13		1.78	162.5	0.525	19.55	175.5	54.7	
CEH003_14		4.21	9.0	0.439	37.4	51.0	120.0	
CEH003_15		4.73	9.7	0.445	37.8	49.6	124.0	
CEH003_16		4.38	10.9	0.438	35.4	45.7	120.5	
CEH003_17		5.01	8.9	0.470	35.5	49.0	124.0	
CEH003_18		5.28	9.2	0.486	37.0	52.6	135.0	
CEH003_19		5.31	10.5	0.423	41.5	56.0	140.0	
CEH003_20		4.63	8.6	0.466	37.1	47.3	125.0	
CEH003_21		2.10	116.5	82.7	16.55	86.6	186.5	
CEH003_22		4.90	8.8	0.461	33.7	46.7	129.0	
CEH003_23		5.50	10.0	0.472	33.6	46.8	133.0	
CEH003_24		4.17	9.4	0.391	29.6	52.7	121.5	
CEH003_25		5.08	11.2	0.464	28.7	52.1	135.0	
CEH003_26		4.78	10.0	0.400	28.5	45.8	130.0	
CEH003_27		4.65	10.2	0.397	34.4	65.5	134.5	
CEH003_28		5.18	11.2	0.460	30.5	50.2	144.0	
CEH003_29		4.09	7.6	0.369	34.7	36.1	113.0	
CEH003_30		4.59	9.2	0.388	34.5	42.5	128.5	
CEH003_31		4.62	8.8	0.446	37.3	40.9	126.0	
CEH003_32		4.47	9.5	0.391	35.9	50.0	124.5	
CEH003_33		4.46	9.8	0.379	34.7	45.9	126.0	
CEH003_34		4.32	7.6	0.397	33.8	37.1	120.0	
CEH003_35		4.05	9.6	0.387	32.7	44.7	124.5	
CEH003_36		4.08	9.3	0.392	34.8	47.4	131.0	
CEH003_37		4.64	10.2	0.399	33.8	52.4	138.5	
CEH003_38		4.37	10.2	0.386	36.9	50.5	135.0	
CEH003_39		4.48	9.2	0.368	35.2	45.7	133.0	
CEH003_40		4.39	8.9	0.363	35.7	43.1	129.0	



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 3 - A  
Total # Pages: 5 (A - D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	WEI-21	Au-AA25	PUL-QC	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L
		Recvd Wt.	Au	Pass75um	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs
		kg	ppm	%	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm
		0.02	0.01	0.01	0.002	0.01	0.02	1	0.02	0.002	0.01	0.005	0.01	0.005	0.3	0.01
CEH003_41		0.12	0.12		0.614	2.64	20.2	172	1.02	1.215	3.94	0.225	80.1	6.74	11.4	2.09
CEH003_42		4.16	<0.01		0.477	7.43	3.24	940	2.26	1.220	2.31	0.052	93.9	4.21	2.1	2.80
CEH003_43		4.03	<0.01		0.062	6.96	2.31	980	1.95	0.182	2.02	0.014	73.0	2.53	1.5	2.10
CEH003_44		2.69	<0.01		0.030	7.31	1.30	1070	2.16	0.103	1.79	0.020	98.1	2.23	1.9	2.21
CEH003_45		2.09	<0.01	95.0	0.065	6.29	2.09	1090	1.66	0.211	1.34	0.007	84.2	6.18	1.4	1.66
CEH003_46		3.17	<0.01		0.016	6.81	1.54	1220	1.61	0.060	1.70	0.009	81.1	2.11	2.0	1.86
CEH003_47		2.77	<0.01		0.036	6.97	2.31	1330	1.74	0.037	1.20	0.013	88.8	2.25	1.7	2.14
CEH003_48		3.93	<0.01		0.030	7.09	1.70	1040	1.79	0.170	1.14	0.007	84.6	2.10	1.7	1.58
CEH003_49		3.66	<0.01		0.014	7.19	1.51	1200	2.01	0.057	1.23	0.007	85.2	1.275	1.6	1.62
CEH003_50		4.08	<0.01		0.014	4.28	0.51	770	1.14	0.039	0.95	0.007	48.6	0.879	0.7	1.13
CEH003_51		3.81	<0.01		0.092	7.10	1.90	1070	2.53	0.322	1.24	<0.005	85.6	2.27	1.5	2.45
CEH003_52		3.79	<0.01		0.138	7.28	2.08	1020	3.06	0.472	1.10	0.007	88.5	1.995	1.7	3.05
CEH003_53		4.12	<0.01		0.024	6.50	1.20	700	1.61	0.068	1.15	0.016	80.4	1.310	1.9	1.27
CEH003_54		4.04	<0.01		0.036	6.98	3.27	780	1.77	0.347	1.06	0.014	87.6	2.84	1.9	1.63
CEH003_55		4.02	<0.01		0.131	6.97	1.83	960	2.46	0.445	1.09	0.037	84.8	1.585	1.6	2.41
CEH003_56		3.91	<0.01		0.040	7.26	1.72	1190	2.61	0.161	1.25	0.010	91.4	1.820	2.5	3.81
CEH003_57		4.27	<0.01		0.011	7.27	1.24	1080	2.37	0.133	1.19	0.011	90.1	1.905	4.5	2.63
CEH003_58		4.02	<0.01		0.015	7.04	1.15	1040	1.98	0.163	1.13	0.007	88.2	1.795	1.9	2.39
CEH003_59		4.17	<0.01		0.024	6.78	2.16	1010	2.07	0.225	1.04	0.021	77.8	2.25	5.0	2.16
CEH003_60		3.07	<0.01		0.014	7.31	1.98	1340	2.03	0.150	1.01	0.012	93.3	1.770	1.7	3.06
CEH003_61		2.71	<0.01		0.012	6.94	1.85	1360	1.98	0.136	1.05	0.013	83.5	1.880	1.8	2.75
CEH003_62		2.39	<0.01		0.009	7.02	2.11	950	2.28	0.152	1.25	0.018	89.1	1.895	2.2	3.52
CEH003_63		0.11	0.08		0.502	6.88	18.60	315	1.88	1.215	4.26	0.222	83.3	7.50	53.9	3.45
CEH003_64		2.94	<0.01		0.011	7.05	4.30	840	2.77	0.343	1.60	0.012	89.5	2.34	1.4	4.19
CEH003_65		3.11	<0.01		0.022	6.92	4.69	910	2.41	0.298	1.18	0.021	88.1	2.86	2.3	2.54
CEH003_66		1.60	<0.01		0.015	7.00	1.88	386	1.73	0.038	1.27	0.056	83.5	2.72	3.2	0.48
CEH003_67		1.56	<0.01		0.033	7.02	7.71	219	1.38	0.032	5.82	0.063	46.3	18.75	23.8	1.18
CEH003_68		1.80	<0.01		0.069	7.93	17.75	347	0.83	0.023	7.48	0.127	12.95	37.9	50.2	1.06
CEH003_69		1.96	<0.01		0.072	7.90	16.45	443	0.54	0.034	6.43	0.093	12.50	41.0	50.4	1.47
CEH003_70		2.05	<0.01		0.089	8.13	14.15	950	0.46	0.035	5.88	0.049	12.30	42.1	53.2	1.37
CEH003_71		1.90	<0.01		0.072	8.02	14.50	470	0.49	0.030	6.74	0.098	12.25	43.4	55.1	1.50
CEH003_72		2.06	0.01		0.126	8.13	15.85	490	0.58	0.099	6.44	3.56	12.65	41.2	54.5	0.76
CEH003_73		1.86	<0.01		0.046	8.00	16.00	650	0.42	0.024	6.51	0.079	11.40	43.0	63.0	1.87
CEH003_74		1.97	<0.01		0.073	7.81	15.45	560	0.42	0.032	6.97	0.075	12.15	39.7	53.8	0.73
CEH003_75		1.81	<0.01		0.107	7.81	15.60	155	0.71	0.078	6.42	0.433	11.85	40.7	52.3	0.73
CEH003_76		1.88	<0.01		0.103	7.89	16.45	198	0.74	0.080	6.85	0.121	12.05	40.3	53.0	0.93
CEH003_77		1.98	<0.01		0.185	8.60	22.5	231	0.92	0.094	6.36	0.176	26.8	41.6	25.6	0.53
CEH003_78		1.84	<0.01		0.082	8.62	13.00	520	0.83	0.062	6.51	0.053	33.4	35.9	16.9	0.77
CEH003_79		1.85	<0.01		0.029	8.50	14.85	610	0.85	0.033	7.03	0.029	34.6	35.9	16.9	0.97
CEH003_80		0.93	<0.01		0.050	8.47	22.0	441	1.12	0.037	6.93	0.029	32.3	34.6	16.0	1.68



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 3 - B  
Total # Pages: 5 (A - D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L
		Cu	Fe	Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni
		ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm
		0.02	0.002	0.05	0.05	0.004	0.005	0.01	0.005	0.2	0.01	0.2	0.02	0.001	0.005	0.08
CEH003_41		44.0	2.37	6.00	0.18	1.790	0.040	1.32	39.7	4.3	0.71	1135	1.28	0.068	0.211	12.95
CEH003_42		5.12	2.26	16.65	0.21	4.09	0.043	3.03	45.3	9.6	0.52	704	0.95	2.38	13.45	2.53
CEH003_43		17.40	1.990	15.90	0.20	3.97	0.049	3.11	35.1	8.2	0.39	626	0.78	2.10	13.55	0.44
CEH003_44		13.30	2.24	17.45	0.23	4.03	0.064	3.45	48.4	8.5	0.40	551	0.72	2.01	14.30	0.46
CEH003_45		1.32	2.17	14.60	0.23	3.48	0.047	2.87	41.3	7.2	0.36	551	0.51	1.900	11.45	0.42
CEH003_46		14.35	1.910	15.35	0.22	4.07	0.038	3.43	38.3	5.4	0.26	546	0.86	2.41	13.95	0.38
CEH003_47		6.23	2.49	17.20	0.25	4.22	0.043	3.66	42.1	7.3	0.34	495	0.78	2.08	12.95	0.50
CEH003_48		12.15	1.850	15.35	0.25	4.13	0.022	3.27	41.7	5.7	0.23	348	0.96	2.83	13.90	0.35
CEH003_49		7.09	1.970	15.45	0.24	4.19	0.032	3.37	41.9	6.2	0.23	341	0.47	2.69	13.60	0.35
CEH003_50		10.05	1.200	8.97	0.21	2.57	0.023	2.01	22.7	4.3	0.15	278	0.34	1.545	8.72	0.23
CEH003_51		1.48	2.15	15.65	0.26	4.10	0.054	3.36	41.7	10.7	0.42	441	1.08	1.940	13.95	0.52
CEH003_52		0.97	1.960	16.40	0.24	4.15	0.047	3.94	44.2	10.3	0.46	349	1.02	1.440	14.55	0.39
CEH003_53		1.20	1.930	13.35	0.24	3.62	0.025	2.16	39.2	6.1	0.32	456	1.04	2.86	11.55	0.41
CEH003_54		2.59	2.03	15.05	0.28	3.86	0.031	2.45	43.7	6.3	0.34	463	1.95	2.90	12.60	0.40
CEH003_55		1.60	1.770	14.90	0.21	3.96	0.049	3.42	42.1	7.5	0.32	353	2.10	1.875	13.10	0.39
CEH003_56		1.82	2.14	16.10	0.24	4.22	0.042	3.96	45.9	9.4	0.42	488	1.35	1.740	14.35	0.72
CEH003_57		0.96	2.06	15.75	0.25	4.02	0.039	3.12	45.4	7.9	0.39	546	1.08	2.75	13.60	0.90
CEH003_58		1.06	2.06	15.40	0.26	3.92	0.035	2.70	43.8	8.5	0.42	533	1.14	2.91	12.50	0.51
CEH003_59		2.00	1.960	14.55	0.26	3.89	0.039	2.83	38.3	7.8	0.41	469	2.76	2.63	12.25	0.65
CEH003_60		1.16	2.17	16.85	0.29	4.06	0.035	3.28	45.3	9.3	0.53	547	2.05	2.76	12.85	0.51
CEH003_61		1.26	2.01	14.80	0.29	3.92	0.035	3.33	41.0	8.9	0.53	522	1.04	2.44	12.20	0.51
CEH003_62		1.95	2.11	15.20	0.28	3.93	0.036	2.99	44.6	10.2	0.56	526	1.25	2.35	12.75	0.67
CEH003_63		42.7	2.93	13.85	0.30	4.52	0.087	2.90	42.2	9.0	1.04	1225	1.42	1.270	7.54	16.10
CEH003_64		1.75	2.05	16.00	0.34	4.00	0.036	3.30	43.9	10.4	0.57	524	1.82	1.845	12.90	0.40
CEH003_65		2.12	2.02	15.80	0.29	4.00	0.045	2.64	43.5	7.0	0.43	491	1.66	2.65	13.05	0.89
CEH003_66		3.19	2.24	14.40	0.28	4.11	0.025	0.74	41.7	4.5	0.39	570	1.43	4.51	12.55	0.80
CEH003_67		35.3	4.12	14.00	0.28	2.45	0.038	0.56	20.6	8.1	1.24	1260	0.69	3.49	6.32	14.45
CEH003_68		91.4	6.49	15.70	0.27	1.575	0.053	0.58	5.20	12.4	3.26	1810	0.38	3.04	1.150	31.5
CEH003_69		72.0	6.86	15.75	0.17	1.730	0.050	0.81	4.98	15.3	3.96	1560	0.27	2.60	1.010	32.9
CEH003_70		75.4	6.83	16.10	0.19	1.610	0.047	1.25	4.94	14.5	4.35	1460	0.22	2.41	0.997	35.0
CEH003_71		76.3	6.88	16.45	0.18	1.395	0.054	0.66	4.83	12.1	3.77	1375	0.24	2.48	0.975	34.5
CEH003_72		64.8	7.04	16.30	0.18	1.670	0.064	0.63	4.97	13.0	3.98	1730	0.30	2.56	1.055	35.4
CEH003_73		62.9	6.65	15.50	0.16	1.420	0.048	1.05	4.53	16.8	4.11	1400	0.24	2.32	0.872	38.4
CEH003_74		77.2	6.52	15.85	0.19	1.600	0.050	0.95	4.82	9.1	3.74	1385	0.29	2.01	0.991	33.8
CEH003_75		72.1	7.00	15.75	0.17	1.465	0.059	0.29	4.67	12.5	3.75	1855	0.40	2.75	0.923	34.8
CEH003_76		48.7	6.89	16.20	0.20	1.515	0.051	0.27	4.73	11.4	3.73	1885	0.47	2.74	1.035	35.8
CEH003_77		149.0	6.56	14.20	0.15	1.310	0.051	0.41	12.20	11.3	3.11	1720	0.48	3.41	1.575	35.9
CEH003_78		68.0	6.33	14.45	0.17	1.275	0.047	0.98	15.00	11.8	2.81	1525	0.35	2.60	1.675	35.7
CEH003_79		43.3	6.40	14.70	0.16	1.295	0.042	1.36	15.50	12.1	2.42	1415	0.55	1.970	1.790	35.1
CEH003_80		70.9	6.13	14.30	0.16	1.345	0.040	1.24	15.00	11.7	1.88	1535	0.29	2.92	1.700	33.2



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 3 - C  
Total # Pages: 5 (A - D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L
		P	Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti
		%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.001	0.01	0.02	0.0004	0.01	0.02	0.01	0.006	0.02	0.02	0.01	0.005	0.004	0.001
CEH003_41		0.043	43.7	67.6	0.0011	1.10	0.40	6.16	1.260	1.12	59.8	<0.01	0.362	11.80	0.054
CEH003_42		0.027	71.3	127.5	<0.0004	0.02	0.71	5.52	0.043	2.22	190.0	0.92	<0.005	16.70	0.191
CEH003_43		0.026	18.40	124.5	<0.0004	0.03	0.73	4.31	0.020	2.04	122.5	0.91	<0.005	16.05	0.186
CEH003_44		0.025	9.15	142.0	<0.0004	0.02	0.65	4.67	0.014	2.42	128.0	0.96	<0.005	17.40	0.194
CEH003_45		0.021	9.24	108.5	<0.0004	0.11	0.61	3.93	0.026	1.73	125.5	0.79	<0.005	14.75	0.155
CEH003_46		0.025	5.18	111.5	<0.0004	0.03	0.83	4.45	0.018	1.62	160.5	0.95	<0.005	16.45	0.183
CEH003_47		0.024	3.90	126.0	<0.0004	0.05	0.94	4.57	0.020	1.56	130.5	0.88	<0.005	17.20	0.173
CEH003_48		0.025	4.50	107.5	<0.0004	0.02	0.69	4.29	0.022	1.40	158.0	0.95	<0.005	17.25	0.188
CEH003_49		0.025	3.53	110.5	<0.0004	0.03	0.60	4.32	0.006	1.42	169.5	0.92	<0.005	17.55	0.185
CEH003_50		0.013	2.48	69.7	<0.0004	0.01	0.37	2.53	<0.006	0.93	102.0	0.61	<0.005	10.30	0.118
CEH003_51		0.026	15.60	139.0	<0.0004	0.03	0.67	4.47	0.030	2.54	146.5	0.92	<0.005	17.10	0.192
CEH003_52		0.027	19.70	172.0	<0.0004	0.03	0.67	4.56	0.011	2.62	156.5	0.95	<0.005	18.70	0.198
CEH003_53		0.022	7.50	81.5	<0.0004	0.01	0.60	3.91	0.024	1.88	147.0	0.78	<0.005	15.10	0.159
CEH003_54		0.025	6.67	99.2	<0.0004	0.14	0.67	4.37	0.036	2.09	141.5	0.84	<0.005	16.75	0.176
CEH003_55		0.025	22.5	141.0	<0.0004	0.03	0.72	4.33	0.025	2.85	167.5	0.89	0.006	17.15	0.176
CEH003_56		0.026	11.40	163.0	<0.0004	0.03	0.66	4.52	0.032	2.44	177.0	0.99	<0.005	18.85	0.191
CEH003_57		0.027	5.48	115.5	<0.0004	0.03	0.44	4.76	0.029	2.21	218	0.93	<0.005	17.70	0.189
CEH003_58		0.026	6.01	101.5	<0.0004	0.03	0.38	4.34	0.035	1.99	218	0.87	<0.005	16.85	0.171
CEH003_59		0.025	9.62	105.5	<0.0004	0.14	0.45	4.29	0.109	2.19	191.0	0.85	<0.005	17.40	0.165
CEH003_60		0.027	5.44	124.0	<0.0004	0.04	0.35	4.55	0.060	2.32	217	0.89	<0.005	17.45	0.176
CEH003_61		0.026	6.10	122.5	<0.0004	0.05	0.49	4.25	0.065	2.08	213	0.84	<0.005	16.35	0.167
CEH003_62		0.026	5.20	141.5	<0.0004	0.05	0.64	4.36	0.044	2.14	185.5	0.89	<0.005	17.15	0.171
CEH003_63		0.045	42.8	151.5	0.0010	1.11	2.27	13.45	1.340	2.69	75.6	0.51	1.215	15.25	0.229
CEH003_64		0.026	4.96	165.0	<0.0004	0.14	0.48	4.54	0.141	2.15	164.5	0.88	0.009	16.35	0.178
CEH003_65		0.026	7.64	116.5	<0.0004	0.09	0.53	4.38	0.081	2.12	200	0.91	<0.005	17.05	0.174
CEH003_66		0.026	11.25	21.1	0.0004	0.02	0.59	4.38	0.017	1.99	193.5	0.89	<0.005	16.65	0.175
CEH003_67		0.032	7.34	17.60	0.0004	0.14	1.08	19.40	0.099	1.28	309	0.45	<0.005	8.31	0.379
CEH003_68		0.042	17.50	16.00	0.0009	0.02	0.90	38.0	0.073	0.81	432	0.08	<0.005	1.430	0.666
CEH003_69		0.040	18.15	25.1	0.0012	0.08	1.20	36.6	0.149	0.69	552	0.07	<0.005	1.335	0.652
CEH003_70		0.036	29.2	34.1	0.0011	0.12	1.47	39.6	0.254	0.67	692	0.07	<0.005	1.315	0.653
CEH003_71		0.037	22.4	20.9	0.0012	0.15	2.13	39.7	0.209	0.64	822	0.07	<0.005	1.190	0.678
CEH003_72		0.041	177.0	19.20	0.0011	0.05	1.10	39.6	0.180	0.71	475	0.07	<0.005	1.335	0.663
CEH003_73		0.035	14.30	34.8	0.0010	0.06	1.94	40.8	0.110	0.65	697	0.06	<0.005	1.115	0.626
CEH003_74		0.038	19.45	26.0	0.0011	0.03	1.53	39.0	0.125	0.60	571	0.07	<0.005	1.240	0.631
CEH003_75		0.037	75.3	9.33	0.0011	0.02	1.07	38.2	0.078	0.68	477	0.07	<0.005	1.330	0.634
CEH003_76		0.040	179.0	9.34	0.0010	0.01	1.05	41.3	0.116	0.60	552	0.07	<0.005	1.210	0.645
CEH003_77		0.055	76.9	9.51	0.0012	0.04	0.77	26.5	0.101	0.97	457	0.10	<0.005	4.11	0.428
CEH003_78		0.059	27.3	28.9	0.0006	0.01	0.89	26.2	0.049	0.51	478	0.10	<0.005	5.20	0.354
CEH003_79		0.061	12.65	46.2	0.0005	<0.01	1.05	26.8	0.046	0.57	513	0.11	<0.005	5.39	0.368
CEH003_80		0.059	5.27	51.5	0.0006	0.02	0.50	25.1	0.038	0.64	295	0.10	<0.005	5.26	0.354





Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 3 - D  
Total # Pages: 5 (A - D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	Pb-OG62	CRU-QC
		U	V	W	Y	Zn	Pb	Pass2mm
		ppm	ppm	ppm	ppm	ppm	%	%
		0.01	0.1	0.008	0.01	0.2	0.001	0.01
CEH003_41		2.77	30.3	0.120	17.60	67.4	67.8	
CEH003_42		4.16	20.5	0.434	33.1	61.2	135.5	
CEH003_43		3.72	8.8	0.476	30.4	45.9	124.5	
CEH003_44		4.63	9.5	0.513	36.7	50.4	131.0	
CEH003_45		3.97	7.7	0.409	34.1	47.6	111.5	
CEH003_46		3.82	8.5	0.493	29.2	34.1	129.0	
CEH003_47		3.97	9.5	0.489	27.2	35.0	131.5	
CEH003_48		3.86	8.3	0.508	28.6	27.5	129.0	
CEH003_49		3.97	8.2	0.494	29.6	25.5	129.5	
CEH003_50		2.14	4.9	0.301	19.70	18.1	78.5	
CEH003_51		4.87	9.0	0.497	33.4	46.1	131.5	92.4
CEH003_52		4.75	9.2	0.624	33.8	41.5	135.0	
CEH003_53		3.82	7.6	0.405	29.5	40.6	117.0	
CEH003_54		4.47	8.4	0.455	30.3	35.6	126.0	
CEH003_55		4.61	8.4	0.581	32.2	36.2	128.0	
CEH003_56		4.78	9.6	0.554	36.6	44.9	134.5	
CEH003_57		4.63	10.0	0.445	36.7	41.4	132.0	
CEH003_58		4.47	8.9	0.349	35.3	42.6	126.0	
CEH003_59		4.40	8.5	0.388	32.9	41.6	125.5	
CEH003_60		4.52	10.0	0.338	37.8	48.8	134.5	
CEH003_61		4.14	8.5	0.337	34.3	49.4	126.5	
CEH003_62		4.31	8.9	0.370	33.0	48.9	131.5	
CEH003_63		4.09	63.5	1.730	27.7	75.6	165.5	
CEH003_64		4.17	9.0	0.398	35.3	42.4	131.0	
CEH003_65		4.52	9.1	0.389	34.7	44.0	132.0	
CEH003_66		4.31	9.7	0.378	33.4	48.8	128.5	
CEH003_67		2.22	112.5	0.384	28.8	78.0	80.3	
CEH003_68		0.45	236	0.342	24.3	154.0	52.6	
CEH003_69		0.40	238	0.223	23.3	142.5	56.3	
CEH003_70		0.37	244	0.164	22.7	141.0	50.9	
CEH003_71		0.35	254	0.155	23.2	130.0	42.7	
CEH003_72		0.38	241	0.280	24.1	379	61.5	
CEH003_73		0.33	238	0.160	22.2	149.5	46.5	
CEH003_74		0.36	227	0.172	22.6	131.0	54.8	
CEH003_75		0.36	233	0.399	21.9	233	52.8	
CEH003_76		0.36	230	0.460	22.8	192.5	51.1	
CEH003_77		1.21	224	0.483	17.85	165.5	47.0	
CEH003_78		1.45	215	0.523	16.30	136.0	49.2	
CEH003_79		1.49	220	0.584	17.20	111.0	51.2	
CEH003_80		1.46	213	0.597	16.35	115.0	52.1	



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 4 - A  
Total # Pages: 5 (A - D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg 0.02	Au-AA25 Au ppm 0.01	PUL-QC Pass75um % 0.01	ME-MS61L Ag ppm 0.002	ME-MS61L Al % 0.01	ME-MS61L As ppm 0.02	ME-MS61L Ba ppm 1	ME-MS61L Be ppm 0.02	ME-MS61L Bi ppm 0.002	ME-MS61L Ca % 0.01	ME-MS61L Cd ppm 0.005	ME-MS61L Ce ppm 0.01	ME-MS61L Co ppm 0.005	ME-MS61L Cr ppm 0.3	ME-MS61L Cs ppm 0.01
CEH003_81		1.76	<0.01		0.080	6.84	3.67	680	1.91	0.082	1.52	0.021	72.3	5.18	2.1	1.64
CEH003_82		1.59	<0.01		0.014	7.08	2.88	339	1.58	0.075	2.39	0.005	66.0	6.01	7.8	0.99
CEH003_83		1.92	<0.01		0.070	8.08	19.90	69	1.00	0.092	8.11	0.046	14.35	37.9	52.2	0.41
CEH003_84		1.93	<0.01		0.151	7.74	14.60	69	1.06	0.117	8.20	0.075	15.35	36.7	50.1	0.43
CEH003_85		1.32	<0.01		0.019	6.37	2.08	490	1.66	0.038	1.42	<0.005	58.5	3.63	3.2	1.46
CEH003_86		1.92	<0.01	95.0	0.012	6.14	1.39	550	1.90	0.028	2.06	0.006	67.8	2.41	3.4	2.29
CEH003_87		0.12	0.31		12.65	5.26	46.2	233	1.52	20.8	2.06	9.04	74.2	11.55	16.8	2.48
CEH003_88		2.12	<0.01		0.008	7.18	3.79	840	2.59	0.076	1.70	0.011	89.8	2.21	3.0	3.37
CEH003_89		2.00	<0.01		0.034	7.50	7.44	570	1.83	0.162	3.18	0.009	55.6	15.90	1.9	2.43
CEH003_90		1.99	0.01		0.032	7.38	10.70	371	1.42	0.105	3.70	0.014	33.4	18.25	2.1	1.66
CEH003_91		1.80	<0.01		0.047	8.12	15.50	345	1.39	0.110	5.67	0.031	49.3	25.0	2.1	1.86
CEH003_92		1.98	<0.01		0.019	7.29	4.92	700	2.15	0.072	2.29	0.012	70.4	4.64	2.2	3.45
CEH003_93		2.02	<0.01		0.068	7.78	6.45	750	2.37	0.405	1.89	0.025	79.9	9.24	3.5	3.52
CEH003_94		1.87	<0.01		0.023	7.26	7.10	550	1.89	0.148	1.28	0.012	91.6	3.83	3.8	2.54
CEH003_95		1.56	<0.01		0.020	6.64	6.52	287	1.50	0.155	2.09	0.010	75.6	3.39	4.7	1.24
CEH003_96		1.84	<0.01		0.025	7.40	6.77	347	1.52	0.066	1.26	0.038	81.8	2.88	4.5	1.62
CEH003_97		2.16	<0.01		0.047	8.34	26.4	560	2.29	0.102	1.63	0.085	61.7	4.57	5.2	2.99
CEH003_98		1.90	<0.01		0.091	8.83	36.8	730	2.97	0.200	1.18	0.445	91.2	4.31	6.1	3.90
CEH003_99		1.82	<0.01		0.108	7.29	26.3	460	1.85	0.200	2.00	0.408	97.5	3.56	8.6	2.01
CEH003_100		1.65	<0.01		0.069	7.41	18.30	500	2.01	0.165	1.66	0.149	99.6	2.76	4.5	2.55
CEH003_101		1.80	0.02		0.042	7.63	15.30	660	2.45	0.272	1.24	0.113	110.0	2.66	2.3	2.95
CEH003_102		1.91	<0.01		0.054	7.89	23.1	401	1.62	0.086	3.10	0.038	95.5	16.90	0.5	1.41
CEH003_103		2.32	<0.01		0.052	9.01	18.45	930	3.25	0.350	1.02	0.085	122.0	5.92	2.3	4.51
CEH003_104		1.97	<0.01		0.091	6.07	25.1	490	1.92	0.348	1.72	0.362	81.9	4.66	6.0	2.11
CEH003_105		1.74	<0.01		0.059	8.01	12.35	750	2.92	0.218	1.35	0.538	91.8	2.65	1.9	3.64
CEH003_106		1.97	<0.01		0.066	8.08	17.15	780	3.04	0.219	1.14	0.257	104.0	2.41	2.2	3.52
CEH003_107		1.86	<0.01		0.089	6.52	14.60	426	2.22	0.199	2.11	0.700	80.3	2.04	3.1	1.86
CEH003_108		1.78	<0.01		0.072	6.27	11.35	309	1.60	0.205	2.27	0.229	71.1	2.12	2.2	1.30
CEH003_109		1.80	<0.01		0.099	6.74	9.27	490	2.10	0.192	2.24	0.524	92.8	1.565	2.4	2.15
CEH003_110		0.11	0.37		13.95	5.20	48.9	243	1.63	23.0	2.17	9.63	78.7	11.75	14.2	2.59
CEH003_111		1.92	<0.01		0.282	7.72	17.10	730	2.97	0.180	1.09	2.39	104.5	2.10	1.5	3.30
CEH003_112		1.94	<0.01		0.265	6.40	14.70	447	1.91	0.206	1.98	2.48	90.4	1.775	2.6	1.98
CEH003_113		2.25	0.01		0.087	6.43	11.90	620	2.04	0.169	1.24	1.110	80.7	1.855	2.9	2.34
CEH003_114		1.82	<0.01		0.144	7.26	23.8	770	2.63	0.194	1.77	1.650	96.1	2.81	4.2	3.24
CEH003_115		2.03	0.01		0.478	7.99	60.2	1000	3.37	0.280	1.70	7.69	101.0	6.08	12.4	4.03
CEH003_116		1.88	0.01		0.381	7.51	44.2	1000	3.12	0.305	1.50	4.30	101.0	4.23	4.9	3.55
CEH003_117		2.13	<0.01		0.228	7.03	18.35	940	2.76	0.210	1.60	3.15	93.0	2.37	1.8	3.47
CEH003_118		1.99	0.01		0.375	7.12	33.8	1160	3.11	0.355	1.46	5.34	89.5	5.18	7.3	3.31
CEH003_119		1.32	0.01		0.558	9.59	60.8	1820	4.39	1.140	0.77	5.28	122.0	9.45	8.6	4.04
CEH003_120		0.38	<0.01		0.054	4.88	2.28	298	0.85	0.078	2.25	2.37	34.2	1.370	2.5	1.09



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 4 - B  
Total # Pages: 5 (A - D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L
		Cu	Fe	Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni
		ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm
		0.02	0.002	0.05	0.05	0.004	0.005	0.01	0.005	0.2	0.01	0.2	0.02	0.001	0.005	0.08
CEH003_81		63.8	2.22	15.40	0.12	3.67	0.037	1.91	34.0	4.9	0.50	445	1.01	2.60	12.80	1.48
CEH003_82		8.40	2.57	14.80	0.12	3.49	0.029	1.10	30.6	5.0	0.67	697	0.72	3.59	11.30	4.16
CEH003_83		50.0	7.05	17.05	0.15	1.695	0.045	0.18	6.21	12.0	2.56	2150	9.66	3.61	1.040	35.1
CEH003_84		108.5	5.66	16.50	0.13	1.695	0.052	0.17	6.89	9.6	2.01	1975	4.11	3.85	1.175	32.9
CEH003_85		14.30	1.770	13.35	0.10	4.05	0.020	1.69	27.6	5.1	0.43	480	0.95	2.62	12.70	1.42
CEH003_86		9.56	1.880	13.75	0.10	3.94	0.021	2.43	31.9	6.3	0.50	593	1.05	1.455	11.70	1.60
CEH003_87		3600	3.97	10.80	0.16	3.52	0.384	2.80	36.8	6.5	0.55	527	10.10	0.262	4.50	7.45
CEH003_88		3.34	1.910	15.80	0.13	4.80	0.031	3.61	44.7	8.5	0.59	460	1.04	0.765	14.10	1.32
CEH003_89		11.05	3.84	14.85	0.14	3.04	0.031	2.54	25.1	10.2	1.01	1020	0.90	1.835	7.57	8.76
CEH003_90		7.95	4.12	13.40	0.11	2.25	0.023	1.85	15.05	10.1	1.12	1150	0.28	2.50	5.03	10.95
CEH003_91		38.6	5.29	14.95	0.15	2.18	0.037	1.63	22.4	11.8	1.33	1705	0.72	2.93	4.52	13.10
CEH003_92		11.20	2.26	16.25	0.12	4.56	0.025	3.32	32.4	9.3	0.66	567	1.24	1.300	12.80	2.20
CEH003_93		5.32	3.13	16.30	0.15	4.05	0.043	3.37	37.8	11.5	0.93	656	1.74	1.245	11.20	5.21
CEH003_94		5.46	2.16	15.85	0.14	4.64	0.034	2.61	46.7	8.6	0.65	427	0.27	2.09	12.25	1.88
CEH003_95		3.03	1.630	11.85	0.11	4.15	0.024	1.46	36.5	5.6	0.40	487	0.51	3.24	9.81	1.74
CEH003_96		2.23	2.12	15.70	0.12	4.68	0.032	1.80	38.6	8.2	0.62	469	0.20	3.13	10.65	2.22
CEH003_97		6.71	2.68	18.85	0.14	6.28	0.039	2.81	28.0	13.1	0.81	535	1.30	2.59	13.80	5.91
CEH003_98		5.42	2.84	20.2	0.16	8.37	0.067	3.70	42.2	15.9	0.97	442	4.37	1.890	17.50	9.06
CEH003_99		14.50	2.18	17.20	0.14	7.13	0.059	2.14	43.7	10.3	0.59	501	2.46	2.86	14.20	6.03
CEH003_100		8.06	2.13	16.35	0.14	7.08	0.048	2.33	50.3	11.1	0.64	477	1.97	2.53	14.55	3.72
CEH003_101		4.35	2.42	16.80	0.15	7.47	0.064	2.99	53.5	13.9	0.77	480	6.90	1.790	15.75	2.29
CEH003_102		50.2	5.05	17.10	0.18	4.00	0.071	1.57	48.7	9.7	0.84	1180	1.00	3.13	5.00	0.78
CEH003_103		7.79	4.01	21.6	0.18	7.83	0.091	3.96	60.4	19.8	1.21	601	6.32	1.190	16.50	1.69
CEH003_104		6.93	2.50	13.10	0.11	5.69	0.047	2.17	37.3	10.3	0.63	533	2.21	1.665	12.60	5.82
CEH003_105		5.23	2.36	19.35	0.15	7.83	0.057	3.44	43.0	15.3	0.82	491	1.60	1.680	16.60	2.42
CEH003_106		3.40	2.57	21.1	0.15	8.23	0.070	3.66	50.2	16.6	0.90	464	2.03	1.485	17.25	2.51
CEH003_107		4.19	1.930	12.95	0.12	6.46	0.041	1.93	36.4	9.8	0.57	599	1.75	2.52	13.80	2.32
CEH003_108		3.69	1.770	10.70	0.11	6.05	0.029	1.42	33.2	7.5	0.43	594	1.70	2.97	12.90	1.84
CEH003_109		4.14	2.32	14.60	0.15	6.47	0.040	2.17	44.4	11.4	0.72	708	1.37	2.12	14.40	1.28
CEH003_110		3670	4.06	11.40	0.18	3.84	0.411	2.79	39.2	7.3	0.59	539	10.85	0.251	4.87	7.74
CEH003_111		6.86	2.37	19.50	0.16	7.97	0.054	3.39	50.8	15.3	0.83	427	1.67	1.435	15.90	1.53
CEH003_112		4.27	2.00	13.35	0.13	6.19	0.039	1.96	44.3	10.2	0.65	587	2.04	2.16	12.70	2.07
CEH003_113		5.28	2.21	15.05	0.13	6.24	0.042	2.44	39.9	11.2	0.74	440	3.41	1.590	13.05	2.16
CEH003_114		6.69	2.32	17.35	0.15	6.85	0.061	3.25	45.8	13.9	0.84	547	4.83	1.310	14.55	4.53
CEH003_115		6.82	3.23	18.95	0.17	7.42	0.068	4.04	48.8	18.2	1.11	640	5.84	0.764	14.25	14.15
CEH003_116		3.53	3.10	17.45	0.17	7.02	0.057	3.80	49.3	16.6	1.08	563	5.94	0.771	13.95	6.74
CEH003_117		2.77	2.72	15.85	0.16	6.53	0.075	3.23	46.3	15.7	1.07	613	4.56	0.951	14.60	2.92
CEH003_118		6.38	2.91	16.55	0.15	6.25	0.079	3.45	44.1	14.8	1.01	715	4.84	0.837	14.20	9.04
CEH003_119		9.69	3.94	23.1	0.21	9.42	0.086	4.69	58.2	14.7	0.97	501	8.07	0.940	19.70	12.70
CEH003_120		3.21	7.37	13.90	0.17	1.870	0.043	0.93	15.95	25.8	1.61	1435	0.96	0.383	5.20	5.26



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 4 - C  
Total # Pages: 5 (A - D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L
		P	Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti
		%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.001	0.01	0.02	0.0004	0.01	0.02	0.01	0.006	0.02	0.02	0.01	0.005	0.004	0.001
CEH003_81		0.025	3.30	95.7	0.0011	0.07	0.51	4.87	0.063	2.00	161.5	0.88	<0.005	15.85	0.182
CEH003_82		0.028	2.66	50.4	0.0008	0.04	0.35	8.07	0.043	1.89	183.0	0.78	<0.005	13.10	0.228
CEH003_83		0.041	2.28	6.69	0.0012	0.03	0.26	40.5	0.072	0.65	281	0.07	<0.005	1.400	0.656
CEH003_84		0.038	3.02	6.62	0.0012	0.09	0.32	40.3	0.130	0.66	287	0.08	<0.005	1.480	0.628
CEH003_85		0.020	2.34	87.8	0.0008	0.03	0.42	3.90	0.016	1.65	111.0	0.89	<0.005	15.55	0.148
CEH003_86		0.019	3.83	126.0	0.0008	0.02	0.44	4.01	0.016	1.63	86.3	0.82	<0.005	14.50	0.142
CEH003_87		0.062	>10000	126.5	0.0026	3.66	6.46	8.13	8.54	4.76	37.2	0.32	2.79	14.35	0.157
CEH003_88		0.022	3.31	190.0	0.0007	0.03	0.40	4.25	0.024	2.00	71.1	1.00	<0.005	18.75	0.163
CEH003_89		0.034	2.51	122.0	0.0017	0.12	0.41	14.45	0.105	1.62	115.5	0.55	<0.005	9.88	0.251
CEH003_90		0.037	1.96	86.2	0.0009	0.13	0.41	17.35	0.222	2.09	135.5	0.34	<0.005	7.00	0.261
CEH003_91		0.042	2.49	85.7	0.0013	0.14	0.56	21.6	0.108	0.94	206	0.31	<0.005	7.24	0.308
CEH003_92		0.025	2.62	155.0	0.0008	0.08	0.47	5.75	0.056	2.02	83.4	0.93	<0.005	15.50	0.179
CEH003_93		0.029	6.38	170.5	0.0020	0.36	0.54	9.26	0.329	2.11	76.7	0.81	0.022	14.85	0.217
CEH003_94		0.024	2.56	139.5	0.0008	0.16	0.51	4.76	0.064	1.92	97.6	0.88	0.007	18.00	0.165
CEH003_95		0.022	2.90	70.5	0.0008	0.21	0.45	3.82	0.100	1.47	128.5	0.71	0.007	14.45	0.128
CEH003_96		0.025	3.41	93.1	0.0006	0.13	0.40	5.03	0.062	1.74	126.5	0.78	<0.005	17.00	0.156
CEH003_97		0.027	8.12	142.5	0.0014	0.63	0.97	6.13	0.261	2.20	124.5	1.01	0.007	19.50	0.197
CEH003_98		0.025	33.1	199.0	0.0023	0.96	1.41	7.19	0.280	3.03	108.5	1.24	0.023	22.9	0.242
CEH003_99		0.023	49.5	105.0	0.0019	0.82	1.06	6.61	0.235	2.79	104.0	1.00	0.013	18.15	0.195
CEH003_100		0.020	20.1	124.0	0.0012	0.53	0.88	5.83	0.173	2.78	120.0	1.01	0.009	18.85	0.183
CEH003_101		0.021	10.85	158.0	0.0012	0.51	0.83	5.53	0.159	2.80	107.0	1.09	0.008	20.2	0.193
CEH003_102		0.133	2.72	67.2	0.0007	0.29	0.64	11.35	0.127	1.54	202	0.32	<0.005	12.30	0.499
CEH003_103		0.051	5.98	183.5	0.0012	0.63	1.00	7.72	0.101	2.93	85.0	1.11	0.006	21.9	0.291
CEH003_104		0.017	13.60	107.5	0.0010	1.03	0.95	4.70	0.236	2.10	93.6	0.85	0.011	15.20	0.159
CEH003_105		0.024	12.20	169.5	0.0012	0.53	0.88	5.86	0.126	3.02	96.8	1.16	0.007	20.8	0.207
CEH003_106		0.024	14.15	179.5	0.0012	0.65	1.04	6.05	0.088	3.26	90.8	1.20	0.006	21.7	0.214
CEH003_107		0.019	23.9	90.6	0.0010	0.48	0.83	4.57	0.143	2.16	133.0	0.96	0.005	15.20	0.167
CEH003_108		0.016	19.70	69.4	0.0012	0.64	0.75	4.07	0.117	1.80	148.5	0.89	<0.005	15.20	0.147
CEH003_109		0.018	28.5	109.5	0.0010	0.41	0.89	4.63	0.057	2.26	124.0	0.98	<0.005	17.05	0.164
CEH003_110		0.065	>10000	132.0	0.0031	3.77	7.25	8.54	8.86	5.41	38.7	0.33	3.06	15.15	0.163
CEH003_111		0.024	124.5	169.0	0.0012	0.68	1.45	5.89	0.121	2.97	91.9	1.14	<0.005	21.3	0.197
CEH003_112		0.019	160.0	95.1	0.0013	0.44	1.22	4.50	0.121	2.08	115.0	0.87	0.005	15.55	0.154
CEH003_113		0.018	30.9	119.0	0.0010	0.47	1.06	4.76	0.121	2.55	86.9	0.88	0.007	17.05	0.156
CEH003_114		0.023	60.4	158.5	0.0014	0.70	1.28	5.82	0.195	2.70	93.0	0.97	0.009	18.55	0.189
CEH003_115		0.030	418	191.5	0.0027	1.39	2.13	7.81	0.618	2.90	83.0	1.00	0.031	19.85	0.236
CEH003_116		0.023	295	179.5	0.0028	1.13	1.41	5.89	0.353	2.59	77.4	1.01	0.014	19.45	0.195
CEH003_117		0.021	230	159.0	0.0014	0.63	1.03	5.26	0.242	2.78	90.0	1.01	0.011	18.45	0.181
CEH003_118		0.023	417	167.5	0.0025	0.75	1.49	6.16	0.342	2.86	77.7	0.98	0.022	17.30	0.198
CEH003_119		0.028	187.5	225	0.0032	1.56	2.33	8.06	0.492	4.28	67.2	1.41	0.033	25.5	0.282
CEH003_120		0.015	19.55	49.9	0.0004	0.11	0.59	2.16	0.025	0.93	66.3	0.40	<0.005	4.44	0.074



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 4 - D  
Total # Pages: 5 (A - D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	Pb-OG62	CRU-QC
		U	V	W	Y	Zn	Pb	Pass2mm
		ppm	ppm	ppm	ppm	ppm	%	%
		0.01	0.1	0.008	0.01	0.2	0.001	0.01
CEH003_81		4.11	16.6	0.518	31.1	38.0	120.0	
CEH003_82		3.33	35.5	0.523	30.6	50.2	112.5	
CEH003_83		0.41	236	1.610	24.7	182.5	60.8	
CEH003_84		0.53	194.5	1.615	24.5	153.5	63.6	
CEH003_85		3.86	21.4	0.497	29.0	34.6	143.0	
CEH003_86		3.70	14.6	0.450	29.5	36.2	133.5	
CEH003_87		4.27	46.2	1.460	14.80	2580	128.0	1.205
CEH003_88		4.65	13.8	0.536	34.5	35.7	163.0	
CEH003_89		2.63	116.5	0.642	24.8	82.9	103.5	
CEH003_90		1.96	141.5	0.745	19.70	94.2	77.7	
CEH003_91		1.94	174.5	0.473	22.9	124.0	77.5	
CEH003_92		3.84	29.8	0.577	29.3	44.8	153.0	
CEH003_93		3.92	64.2	0.560	32.5	65.1	137.5	
CEH003_94		4.64	18.2	0.410	32.7	44.5	155.0	
CEH003_95		3.64	12.6	0.385	37.8	31.1	142.0	
CEH003_96		4.60	19.8	0.407	28.8	55.6	157.0	
CEH003_97		5.51	29.0	0.503	34.3	57.8	230	
CEH003_98		8.02	22.9	0.641	43.1	98.9	309	
CEH003_99		5.44	15.2	0.596	39.0	81.6	265	
CEH003_100		5.87	9.5	0.532	39.0	52.9	266	
CEH003_101		6.08	7.2	0.634	41.9	63.8	278	92.8
CEH003_102		3.42	70.6	1.020	32.0	108.0	149.5	96.7
CEH003_103		6.41	20.1	0.898	46.1	94.7	300	
CEH003_104		4.72	7.7	0.586	32.9	88.6	217	
CEH003_105		6.17	6.8	0.594	41.9	102.0	293	
CEH003_106		6.51	7.2	0.604	41.8	65.5	305	
CEH003_107		4.24	5.0	0.542	37.2	100.5	242	
CEH003_108		4.70	3.2	0.516	33.3	44.3	226	
CEH003_109		4.97	3.7	0.503	37.6	99.4	244	
CEH003_110		4.50	45.1	1.505	15.50	2720	136.0	1.220
CEH003_111		6.39	5.3	0.555	42.9	605	292	
CEH003_112		4.72	4.7	0.488	34.3	484	230	
CEH003_113		5.06	5.2	0.503	31.0	143.5	233	
CEH003_114		5.75	9.6	0.568	33.3	197.0	256	
CEH003_115		7.35	31.3	0.846	33.5	772	279	
CEH003_116		5.79	16.0	0.616	33.3	506	259	
CEH003_117		5.38	6.7	0.517	33.5	404	244	
CEH003_118		5.65	19.0	0.560	30.3	718	236	
CEH003_119		8.57	26.4	0.801	36.0	787	341	
CEH003_120		1.47	7.2	0.450	10.30	516	65.6	



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 5 - A  
Total # Pages: 5 (A - D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg 0.02	Au-AA25 Au ppm 0.01	PUL-QC Pass75um % 0.01	ME-MS61L Ag ppm 0.002	ME-MS61L Al % 0.01	ME-MS61L As ppm 0.02	ME-MS61L Ba ppm 1	ME-MS61L Be ppm 0.02	ME-MS61L Bi ppm 0.002	ME-MS61L Ca % 0.01	ME-MS61L Cd ppm 0.005	ME-MS61L Ce ppm 0.01	ME-MS61L Co ppm 0.005	ME-MS61L Cr ppm 0.3	ME-MS61L Cs ppm 0.01
CEH003_121		1.69	<0.01		0.221	6.98	5.54	1050	1.94	0.485	1.36	0.062	96.7	1.985	1.5	1.82
CEH003_122		1.94	<0.01		0.031	6.80	4.86	1380	1.99	0.138	1.84	0.060	92.0	2.65	1.3	1.83
CEH003_123		1.82	<0.01		0.107	7.11	2.94	1460	1.97	0.143	1.72	0.656	90.5	2.82	1.9	1.71
CEH003_124		1.89	<0.01		0.168	6.90	2.25	1690	1.91	0.072	1.63	0.986	73.2	1.680	1.5	1.86
CEH003_125		1.54	0.01		0.383	7.33	3.32	1500	2.35	0.280	1.40	10.50	93.4	2.63	1.4	2.06
CEH003_126		0.07	4.19		0.879	7.47	483	580	2.71	7.71	1.12	0.082	79.8	19.50	197.0	5.63
CEH003_127		1.59	<0.01		0.072	7.08	2.67	1250	2.22	0.117	1.54	0.444	79.5	1.740	1.7	1.85
CEH003_128		1.95	<0.01		0.064	7.77	4.81	1450	2.63	0.063	1.70	0.196	98.4	2.07	1.4	2.68
CEH003_129		1.25	<0.01	97.0	0.132	7.60	2.92	1060	2.64	0.103	1.52	0.677	92.1	1.535	1.5	3.10
CEH003_130		1.96	0.01		0.356	6.48	13.65	960	2.79	0.438	1.86	1.645	89.7	4.20	3.8	3.15
CEH003_131		1.92	0.01		0.245	6.62	20.6	820	2.67	0.244	1.96	1.080	80.1	6.16	3.4	3.11
CEH003_132		1.99	0.01		0.187	7.47	15.75	880	3.05	0.177	1.38	0.847	105.0	2.88	2.5	3.92
CEH003_133		1.78	0.01		0.355	6.87	31.0	760	2.60	0.357	1.70	0.929	83.8	10.55	2.9	3.29
CEH003_134		1.88	0.01		0.359	7.49	40.9	560	2.08	0.308	3.68	1.380	51.6	18.80	3.9	2.46
CEH003_135		1.58	0.01		0.140	7.46	17.45	660	2.38	0.237	1.68	0.268	117.0	3.18	2.8	2.83
CEH003_136		2.51	0.01		0.164	6.79	20.1	740	2.30	0.314	3.18	0.238	81.5	8.55	20.4	2.76
CEH003_137		1.23	<0.01		0.134	9.02	38.4	680	2.01	0.077	7.57	0.171	43.6	29.4	84.9	2.90
CEH003_138		1.43	0.03		0.338	9.63	15.35	1140	3.51	0.327	2.47	0.255	114.0	7.70	9.7	4.53
CEH003_139		2.44	<0.01		0.125	9.60	33.6	337	1.08	0.037	7.10	0.247	25.1	35.8	5.7	1.94
CEH003_140		1.75	0.01		0.448	8.33	17.45	800	2.50	0.270	1.61	0.302	149.0	11.05	7.3	2.84
CEH003_141		0.09	0.12		0.598	7.89	21.2	341	1.99	1.370	4.68	0.252	78.4	8.54	53.4	3.77
CEH003_142		1.97	<0.01		0.607	9.25	17.05	790	2.66	0.206	2.03	1.190	95.5	8.50	34.3	3.24
CEH003_143		2.43	<0.01		1.060	8.28	15.20	820	2.80	0.350	1.45	4.26	95.9	6.94	8.1	4.06
CEH003_144		1.65	0.01		1.465	8.01	17.70	780	2.70	0.662	1.72	5.25	108.0	14.40	7.9	4.23
CEH003_145		2.21	<0.01		0.158	7.02	2.27	362	1.56	0.056	1.86	0.072	75.9	3.66	4.2	2.19
CEH003_146		1.68	<0.01		0.082	7.89	3.36	740	1.95	0.032	2.21	0.426	63.0	16.65	8.2	2.13
CEH003_147		2.03	<0.01		0.011	7.92	1.20	620	1.56	0.011	3.38	0.033	46.4	15.90	11.6	2.23
CEH003_148		2.30	<0.01		0.009	7.83	2.11	640	1.67	0.028	2.63	0.036	55.7	8.23	5.2	1.75
CEH003_149		2.52	<0.01		0.043	7.74	3.87	580	1.93	0.149	3.27	0.105	62.3	16.60	43.1	2.38
CEH003_150		2.59	<0.01		0.028	8.50	4.65	670	2.30	0.295	1.82	0.052	63.6	17.60	22.3	4.12
CEH003_151		2.07	<0.01		0.025	7.04	3.52	750	2.46	0.251	0.87	0.026	91.7	9.00	5.9	4.13
CEH003_152		1.73	0.03		0.050	6.79	2.52	750	1.79	0.162	2.09	0.032	64.5	4.57	4.1	0.98
CEH003_153		2.24	0.01		0.053	7.88	2.54	670	2.04	0.072	3.88	0.069	55.1	18.05	23.2	2.79
CEH003_154		1.26	<0.01		0.017	6.79	1.73	1100	1.70	0.032	1.94	0.042	80.2	4.28	1.9	1.82
CEH003_155		1.91	<0.01		0.034	7.07	2.23	1190	1.57	0.070	1.12	0.047	80.8	6.14	2.2	1.87
CEH003_156		1.86	<0.01		0.018	7.44	2.16	920	1.68	0.016	1.31	0.104	104.5	3.41	2.3	1.92
CEH003_157		1.87	<0.01		0.008	7.20	1.35	890	1.61	0.005	1.64	0.039	89.4	2.72	2.1	2.02
CEH003_158		2.83	0.06		0.013	7.59	1.61	1090	1.75	0.013	0.90	0.030	88.1	3.75	2.3	1.78
CEH003_159		0.68	<0.01		0.012	3.19	0.88	363	0.72	0.005	2.96	0.091	265	2.31	3.0	0.75
CEH003_160		2.07	0.01		0.039	7.03	2.45	970	1.57	0.072	1.44	0.139	78.3	5.71	2.3	1.43



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 5 - B  
Total # Pages: 5 (A - D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L
		Cu	Fe	Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni
		ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm
		0.02	0.002	0.05	0.05	0.004	0.005	0.01	0.005	0.2	0.01	0.2	0.02	0.001	0.005	0.08
CEH003_121		1.36	2.04	15.95	0.15	4.70	0.044	2.20	46.5	7.2	0.40	491	1.30	2.43	13.70	0.68
CEH003_122		1.48	2.25	15.60	0.13	4.50	0.047	2.21	41.9	6.6	0.33	660	0.83	2.41	12.95	0.48
CEH003_123		39.4	2.29	16.00	0.13	4.63	0.078	2.15	43.6	5.7	0.28	693	1.10	2.92	14.00	0.61
CEH003_124		113.5	2.67	16.25	0.12	4.40	0.087	2.21	33.7	6.6	0.36	732	0.99	2.48	13.15	0.51
CEH003_125		187.5	2.06	17.40	0.13	4.92	0.168	2.38	45.6	5.6	0.28	641	0.99	2.75	14.55	0.48
CEH003_126		69.1	4.78	20.8	0.17	4.79	0.047	1.88	43.2	29.7	1.38	350	4.43	0.762	24.9	94.7
CEH003_127		5.40	2.10	16.50	0.12	4.58	0.049	2.21	37.5	5.7	0.28	688	1.09	2.79	14.05	0.44
CEH003_128		9.52	2.51	19.40	0.15	5.04	0.086	2.90	47.6	8.7	0.47	756	0.96	2.22	15.80	0.49
CEH003_129		11.60	2.41	17.90	0.15	5.15	0.053	2.76	44.9	10.9	0.74	640	0.98	2.13	15.90	0.73
CEH003_130		7.80	2.19	15.45	0.15	5.73	0.040	3.14	44.3	10.3	0.70	702	3.45	0.897	14.35	4.25
CEH003_131		7.57	2.42	15.90	0.15	5.44	0.056	3.18	38.7	12.5	0.86	730	3.32	0.851	13.25	4.78
CEH003_132		2.17	2.12	18.70	0.16	6.75	0.048	3.74	51.9	12.5	0.86	481	5.84	0.837	16.35	2.24
CEH003_133		9.18	2.75	16.75	0.14	6.57	0.049	3.25	40.8	12.3	0.84	587	7.97	0.873	14.50	5.64
CEH003_134		17.15	4.01	16.70	0.14	4.44	0.046	2.54	22.7	12.9	1.32	1260	6.09	1.865	9.18	9.32
CEH003_135		3.75	2.23	17.40	0.16	6.75	0.056	3.05	55.7	9.2	0.70	488	6.06	1.875	15.60	3.44
CEH003_136		15.95	2.69	15.25	0.15	5.69	0.056	2.94	39.9	10.2	1.13	890	3.08	1.000	12.85	10.60
CEH003_137		54.9	5.99	16.85	0.14	3.28	0.050	3.17	20.1	18.0	3.45	2060	0.70	0.826	6.16	41.4
CEH003_138		5.69	3.23	21.8	0.16	8.20	0.064	4.50	54.5	13.2	1.52	737	3.43	0.998	18.35	12.25
CEH003_139		21.6	7.42	16.65	0.16	1.935	0.049	1.34	11.75	16.2	3.21	2180	0.58	3.28	1.950	19.80
CEH003_140		6.21	3.29	19.40	0.19	7.09	0.059	3.31	71.2	10.8	1.29	565	2.83	1.690	13.70	8.05
CEH003_141		48.5	3.39	15.70	0.14	5.05	0.095	3.40	38.3	8.5	1.19	1305	1.51	1.415	8.27	17.80
CEH003_142		11.50	3.29	19.20	0.15	6.83	0.047	3.50	45.8	10.8	1.20	682	9.28	2.21	14.90	13.35
CEH003_143		22.2	2.74	19.05	0.15	7.28	0.061	3.90	47.3	10.9	1.02	605	2.65	1.175	16.70	7.22
CEH003_144		12.00	2.72	20.0	0.16	7.24	0.067	3.91	54.1	9.2	0.93	704	2.91	0.950	16.20	9.48
CEH003_145		3.95	1.820	12.70	0.12	3.79	0.024	1.68	37.7	4.9	0.53	794	1.38	3.38	12.50	4.02
CEH003_146		1.44	5.79	19.55	0.17	3.31	0.048	1.96	29.9	11.6	1.78	1360	4.57	2.54	9.15	14.30
CEH003_147		0.95	6.31	17.65	0.17	2.66	0.033	1.59	21.4	11.4	2.03	1870	3.82	2.94	5.60	19.50
CEH003_148		0.84	2.85	14.05	0.11	3.58	0.039	1.70	25.1	6.0	0.86	1105	4.63	3.92	10.15	7.91
CEH003_149		1.13	5.11	17.20	0.14	3.60	0.052	1.94	29.6	12.4	1.72	1710	1.80	2.61	8.44	26.0
CEH003_150		1.16	5.85	19.40	0.16	4.45	0.061	2.71	28.5	15.7	2.01	1355	0.90	2.12	11.45	19.55
CEH003_151		1.30	3.15	17.80	0.14	5.55	0.049	3.04	47.4	10.2	1.00	602	1.45	1.485	13.85	5.82
CEH003_152		2.91	1.140	11.15	0.10	5.44	0.027	1.86	30.1	2.2	0.20	658	1.44	3.97	12.45	1.85
CEH003_153		100.5	5.54	17.15	0.16	3.15	0.044	2.09	26.4	15.4	1.65	1760	2.12	2.82	6.44	18.10
CEH003_154		3.95	1.860	14.00	0.14	3.60	0.020	2.89	37.8	3.3	0.29	669	0.82	2.76	12.50	0.91
CEH003_155		4.43	2.06	14.45	0.12	3.73	0.020	3.13	40.8	3.4	0.27	475	0.79	3.05	12.90	0.87
CEH003_156		4.12	2.01	16.05	0.14	3.95	0.019	3.15	51.3	3.0	0.30	548	0.55	3.11	13.15	1.06
CEH003_157		3.98	1.960	15.65	0.12	3.95	0.019	3.32	46.2	2.5	0.30	555	0.57	2.80	13.40	1.05
CEH003_158		6.72	1.840	16.35	0.13	4.00	0.016	3.56	44.1	1.9	0.26	362	0.54	2.99	13.55	0.90
CEH003_159		14.65	1.280	6.08	0.23	1.675	0.015	1.34	130.5	1.2	0.21	722	0.58	1.305	5.20	1.49
CEH003_160		4.16	1.860	14.60	0.13	3.72	0.017	2.84	38.6	2.4	0.21	497	0.63	3.23	13.10	0.98



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 5 - C  
Total # Pages: 5 (A - D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L
		P	Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti
		%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.001	0.01	0.02	0.0004	0.01	0.02	0.01	0.006	0.02	0.02	0.01	0.005	0.004	0.001
CEH003_121		0.030	24.1	107.0	0.0007	0.18	1.04	4.87	0.046	2.35	137.5	0.89	<0.005	17.50	0.186
CEH003_122		0.028	5.74	99.8	0.0007	0.15	0.76	4.69	0.034	2.35	152.0	0.88	<0.005	16.35	0.182
CEH003_123		0.029	15.90	97.0	0.0006	0.14	0.79	4.84	0.019	4.65	177.5	0.94	<0.005	17.40	0.194
CEH003_124		0.028	7.47	99.0	0.0007	0.08	0.73	4.64	0.034	3.84	162.5	0.89	<0.005	15.45	0.179
CEH003_125		0.030	38.5	110.5	0.0008	0.16	1.25	5.07	0.035	7.96	161.5	1.00	<0.005	18.00	0.198
CEH003_126		0.086	15.10	83.4	0.0030	0.05	22.6	18.45	0.527	8.57	247	1.64	0.222	11.05	0.518
CEH003_127		0.030	11.95	96.5	0.0006	0.04	0.91	4.75	0.027	3.38	157.5	0.94	<0.005	15.05	0.194
CEH003_128		0.032	17.50	139.5	0.0007	0.13	1.34	5.28	0.053	4.69	141.0	1.03	<0.005	18.90	0.210
CEH003_129		0.032	63.1	131.5	0.0008	0.06	1.36	5.36	0.032	2.54	151.0	1.07	<0.005	18.20	0.210
CEH003_130		0.017	89.0	154.5	0.0013	0.56	1.46	5.03	0.172	2.36	86.3	1.00	0.011	17.85	0.155
CEH003_131		0.020	84.8	146.0	0.0012	0.57	1.61	8.07	0.219	2.28	83.0	0.89	0.011	15.15	0.188
CEH003_132		0.018	59.6	181.5	0.0011	0.61	1.56	5.74	0.136	2.79	71.2	1.10	0.007	20.6	0.170
CEH003_133		0.017	107.0	164.0	0.0018	1.09	1.98	5.94	0.317	2.42	77.4	1.03	0.014	19.05	0.160
CEH003_134		0.028	151.5	111.0	0.0015	1.01	1.58	17.45	0.335	1.85	148.5	0.63	0.014	11.35	0.275
CEH003_135		0.019	36.5	145.5	0.0013	0.98	1.59	5.65	0.191	2.88	102.0	1.10	0.010	19.15	0.162
CEH003_136		0.017	38.4	146.0	0.0015	0.61	1.56	9.56	0.203	2.04	115.5	0.89	0.011	15.65	0.181
CEH003_137		0.025	22.6	136.0	0.0013	0.20	1.03	29.8	0.156	1.36	206	0.43	0.008	7.85	0.395
CEH003_138		0.021	59.2	195.0	0.0021	0.46	2.07	7.03	0.249	3.26	99.8	1.34	0.020	23.7	0.211
CEH003_139		0.041	17.90	64.7	0.0013	0.11	0.97	35.1	0.072	0.69	296	0.14	<0.005	3.73	0.425
CEH003_140		0.022	45.6	147.5	0.0014	0.66	1.72	8.40	0.303	3.04	98.3	0.99	0.017	20.2	0.191
CEH003_141		0.047	45.7	143.0	0.0013	1.22	2.54	13.15	1.520	2.94	83.5	0.59	1.365	14.15	0.240
CEH003_142		0.030	164.0	158.0	0.0016	0.73	1.83	9.80	0.226	2.65	122.0	1.07	0.012	18.85	0.254
CEH003_143		0.021	932	175.5	0.0016	0.58	1.95	6.32	0.217	3.00	60.9	1.17	0.019	20.0	0.197
CEH003_144		0.021	1630	177.5	0.0017	0.70	2.13	8.12	0.352	3.10	70.9	1.09	0.017	19.50	0.208
CEH003_145		0.017	236	81.6	0.0006	0.04	1.01	4.23	0.024	1.07	100.0	0.93	<0.005	17.75	0.139
CEH003_146		0.030	106.5	90.1	0.0016	0.09	1.01	14.85	0.059	1.80	113.0	0.67	<0.005	14.10	0.304
CEH003_147		0.034	5.22	65.6	0.0012	0.02	0.44	21.0	0.017	1.94	159.0	0.41	<0.005	9.68	0.392
CEH003_148		0.023	4.99	58.8	0.0010	0.05	0.46	9.53	0.030	2.28	149.0	0.77	<0.005	13.30	0.233
CEH003_149		0.031	15.00	87.7	0.0011	0.08	0.76	15.15	0.073	1.58	148.5	0.61	<0.005	12.60	0.317
CEH003_150		0.022	6.40	109.5	0.0007	0.12	0.71	14.30	0.097	2.02	100.5	0.80	0.007	12.35	0.262
CEH003_151		0.014	4.95	152.0	0.0006	0.10	0.76	6.28	0.059	2.43	58.1	0.99	0.005	18.80	0.149
CEH003_152		0.017	19.40	55.4	0.0007	0.07	0.95	3.84	0.069	1.58	167.5	0.88	<0.005	14.15	0.163
CEH003_153		0.036	8.09	89.5	0.0018	0.05	0.71	20.4	0.099	1.39	189.5	0.46	<0.005	9.42	0.407
CEH003_154		0.015	6.33	94.3	0.0006	0.05	0.48	2.73	0.037	1.66	138.5	0.95	<0.005	18.85	0.127
CEH003_155		0.016	9.99	98.9	0.0006	0.07	0.59	2.96	0.064	1.78	119.0	0.98	<0.005	19.85	0.132
CEH003_156		0.017	7.84	111.0	0.0004	0.03	0.82	2.96	0.032	1.58	108.0	0.98	<0.005	21.1	0.134
CEH003_157		0.016	3.89	118.0	0.0005	0.02	0.79	2.97	0.014	2.37	110.0	1.00	<0.005	20.2	0.133
CEH003_158		0.017	5.54	125.0	0.0005	0.04	0.81	3.01	0.022	1.70	102.0	1.02	<0.005	21.3	0.139
CEH003_159		0.013	2.98	48.5	<0.0004	0.02	0.46	2.11	0.079	0.69	97.6	0.35	<0.005	10.05	0.067
CEH003_160		0.016	12.80	91.6	0.0004	0.04	0.58	2.80	0.059	1.38	127.0	0.98	<0.005	19.35	0.132





Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: 5 – D  
Total # Pages: 5 (A – D)  
Plus Appendix Pages  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS AD22061837

Sample Description	Method Analyte Units LOD	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	Pb-OG62	CRU-QC
		U	V	W	Y	Zn	Pb	Pass2mm
		ppm	ppm	ppm	ppm	ppm	%	%
		0.01	0.1	0.008	0.01	0.2	0.001	0.01
CEH003_121		4.37	9.6	0.747	26.5	47.6	162.5	
CEH003_122		4.05	9.4	0.847	22.8	46.0	151.5	
CEH003_123		4.24	9.8	0.796	22.5	132.0	161.0	
CEH003_124		3.78	9.7	0.879	23.5	188.0	150.0	
CEH003_125		4.70	10.6	0.858	27.5	1610	166.5	
CEH003_126		2.15	121.0	85.3	18.25	90.6	205	
CEH003_127		3.95	9.7	1.500	25.3	93.4	161.0	
CEH003_128		4.76	11.8	2.51	28.1	81.6	177.5	
CEH003_129		4.60	11.1	0.800	27.0	176.5	176.5	
CEH003_130		4.88	7.5	0.742	27.1	330	210	
CEH003_131		4.39	31.4	0.800	25.1	205	195.0	
CEH003_132		5.74	5.9	0.677	31.4	139.0	251	
CEH003_133		5.68	17.6	0.673	28.4	267	239	
CEH003_134		3.64	105.5	1.095	20.4	381	164.5	
CEH003_135		5.34	6.2	0.782	29.8	58.0	247	
CEH003_136		4.79	33.0	1.325	29.9	83.9	208	
CEH003_137		2.51	172.5	0.592	19.70	217	114.0	
CEH003_138		6.99	27.2	0.423	37.0	134.0	303	
CEH003_139		1.13	244	1.120	14.50	266	66.2	
CEH003_140		6.02	27.4	0.441	30.6	145.0	265	
CEH003_141		4.01	68.1	1.530	22.9	84.0	186.5	
CEH003_142		5.49	40.2	0.969	30.6	369	258	
CEH003_143		6.19	15.1	0.650	33.0	1010	270	
CEH003_144		5.82	28.0	0.717	28.7	1180	260	
CEH003_145		3.67	19.6	0.454	17.35	53.1	114.0	
CEH003_146		3.60	119.0	0.612	20.3	306	102.5	
CEH003_147		2.66	168.5	0.572	14.00	224	86.0	
CEH003_148		3.09	71.8	0.522	12.95	93.1	107.5	
CEH003_149		3.42	114.5	0.540	18.25	203	120.5	
CEH003_150		3.46	82.2	0.451	17.25	221	159.0	
CEH003_151		4.89	26.6	0.525	24.3	98.4	203	73.9
CEH003_152		3.55	14.6	0.542	17.30	20.6	209	
CEH003_153		2.78	161.5	0.710	16.55	206	115.5	
CEH003_154		4.60	9.5	0.496	15.65	37.6	105.0	
CEH003_155		4.80	7.7	0.434	15.80	41.0	110.0	
CEH003_156		5.74	8.5	0.485	16.85	41.8	115.5	
CEH003_157		4.64	8.1	0.526	17.45	28.8	115.0	
CEH003_158		5.06	9.3	0.556	15.45	27.1	119.0	
CEH003_159		1.61	10.7	0.282	14.55	19.2	50.8	
CEH003_160		4.55	7.9	0.496	17.00	35.3	110.0	



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Brisbane is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 818.

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration

Page: Appendix 1  
Total # Appendix Pages: 1  
Finalized Date: 27-APR-2022  
Account: HENMINEXP

**CERTIFICATE OF ANALYSIS AD22061837**

**CERTIFICATE COMMENTS**

**ACCREDITATION COMMENTS**

Applies to Method:

NATA Accreditation covers the performance of this service but does not cover the performance of ALS Brisbane Sample Preparation. Corporate Accreditation No:825, Corporate Site No:818. Technical Signatory is Samantha Profke,ICPAES Supervising Chemist  
ME-OG62 Pb-OG62

**LABORATORY ADDRESSES**

Applies to Method:

Processed at ALS Townsville located at 14-15 Desma Court, Bohle, Townsville, QLD, Australia.  
Au-AA25

Applies to Method:

Processed at ALS Adelaide located at Unit 1, 1 Burma Road, Pooraka, Adelaide, SA, Australia.

BAG-01	CRU-31	CRU-QC	LEV-01
LOG-22	LOG-24	PUL-32	PUL-QC
SPL-21	SPL-22Y	SPLIT-X	WEI-21

Applies to Method:

Processed at ALS Brisbane located at 32 Shand Street, Stafford, Brisbane, QLD, Australia. Processed at ALS Brisbane Sample Preparation at 23 Pineapple Street, Zillmere, QLD, 4034, Australia  
ME-MS61L ME-OG62 Pb-OG62