



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Page: 1  
Total # Pages: 2 (A - D)  
Plus Appendix Pages  
Finalized Date: 28-APR-2022  
Account: HENMINEXP

## CERTIFICATE BU22052061

Project: Exploration 1-3-22

P.O. No.: P280332

This report is for 36 samples of Drill Core submitted to our lab in Burnie, TAS, Australia on 1-MAR-2022.

The following have access to data associated with this certificate:

PAUL DALE

ROBERT REID

## SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
SPL-21	Split sample - riffle splitter
LOG-22	Sample login - Rcd w/o BarCode
SPLIT-X	Create X Label
BAG-21	Raw Sample in a new bag
LEV-01	Waste Disposal Levy
CRU-21	Crush entire sample
PUL-QC	Pulverizing QC Test
PUL-23	Pulv Sample - Split/Retain
BAG-01	Bulk Master for Storage

## ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
ME-MS61L	Super Trace Lowest DL 4A by ICP-MS	
Au-AA25	Ore Grade Au 30q FA AA finish	AAS

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

\*\*\*\*\* See Appendix Page for comments regarding this certificate \*\*\*\*\*

Signature:

Cameron Brosnan, Laboratory Manager, Perth



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Page: 2 - A  
Total # Pages: 2 (A - D)  
Plus Appendix Pages  
Finalized Date: 28-APR-2022  
Account: HENMINEXP

Project: Exploration 1-3-22

## CERTIFICATE OF ANALYSIS BU22052061

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg 0.02	Au-AA25 Au ppm 0.01	PUL-QC Pass75um % 0.01	ME-MS61L Ag ppm 0.002	ME-MS61L Al % 0.01	ME-MS61L As ppm 0.02	ME-MS61L Ba ppm 1	ME-MS61L Be ppm 0.02	ME-MS61L Bi ppm 0.002	ME-MS61L Ca % 0.01	ME-MS61L Cd ppm 0.005	ME-MS61L Ce ppm 0.01	ME-MS61L Co ppm 0.005	ME-MS61L Cr ppm 0.3	ME-MS61L Cs ppm 0.01
CEH001-000		0.40	<0.01	99.2	0.020	7.05	1.35	168	1.74	0.014	5.40	0.058	52.5	50.8	207	0.45
CEH001-001		2.45	<0.01		0.049	7.61	1.84	1240	1.96	0.098	0.03	0.016	98.4	6.27	2.9	4.18
CEH001-002		1.33	<0.01		0.145	8.06	1.76	1090	2.02	0.075	0.03	0.040	115.5	4.43	2.3	4.30
CEH001-003		0.77	<0.01		0.020	7.43	2.24	880	2.26	0.029	0.09	0.045	98.1	5.18	3.8	5.32
CEH001-004		6.66	<0.01		0.043	7.20	2.29	1550	2.06	0.105	0.08	0.135	94.7	3.89	3.5	4.73
CEH001-005		1.17	<0.01		0.040	4.94	3.07	1950	1.64	0.187	0.06	0.216	30.4	7.74	24.3	4.37
CEH001-006		1.83	<0.01		0.037	10.80	22.5	3800	3.14	0.450	0.10	0.130	58.7	13.35	47.3	8.10
CEH001-007		3.56	<0.01		0.027	7.42	5.27	2260	2.28	0.193	0.08	0.063	99.1	5.28	1.6	5.44
CEH001-008		4.66	<0.01		0.032	7.32	4.41	1990	2.34	0.183	0.07	0.126	93.6	5.28	1.4	5.25
CEH001-009		2.53	<0.01		0.021	8.29	8.53	1270	1.87	0.180	0.25	0.170	44.3	18.15	0.9	3.60
CEH001-010		2.11	<0.01		0.021	8.04	3.74	1170	1.84	0.155	0.23	0.188	50.8	14.10	0.9	3.19
CEH001-011		4.82	<0.01		0.033	6.79	2.32	1250	2.28	0.134	1.35	0.133	91.8	3.31	1.2	4.56
CEH001-012		4.81	<0.01		0.005	6.86	1.29	1060	2.12	0.028	1.11	0.144	94.0	1.980	1.3	4.61
CEH001-013		4.20	0.01		0.037	6.72	1.37	1020	2.19	0.111	1.51	0.156	91.9	1.780	1.6	4.71
CEH001-014		4.01	<0.01		0.008	7.01	1.03	1030	2.26	0.045	1.64	0.118	93.5	1.645	1.3	4.99
CEH001-015		3.90	<0.01		0.008	6.93	1.17	1020	2.30	0.038	0.58	0.084	97.6	1.810	1.5	5.13
CEH001-016		4.44	<0.01		0.029	6.80	1.05	950	2.04	0.054	1.77	0.154	92.1	2.15	1.5	4.57
CEH001-017		3.78	<0.01		0.010	6.87	1.15	960	2.03	0.031	1.79	0.194	92.3	2.28	1.4	4.46
CEH001-018		4.91	<0.01		0.015	7.14	1.06	1110	2.24	0.023	1.90	0.111	93.3	1.175	1.7	5.00
CEH001-019		4.51	<0.01		0.014	6.85	1.29	990	2.05	0.032	2.48	0.158	90.0	1.890	1.5	4.54
CEH001-020		4.38	<0.01		0.034	5.42	1.98	620	1.40	0.072	2.40	0.188	75.6	2.02	1.4	3.05
CEH001-021		4.85	<0.01		0.049	6.67	2.80	940	2.29	0.123	3.24	0.247	79.3	1.815	1.4	4.67
CEH001-022		1.49	<0.01		0.078	8.12	3.44	770	1.78	0.110	6.38	1.100	27.5	21.8	7.4	4.20
CEH001-023		5.06	<0.01		0.051	6.67	2.10	760	1.96	0.141	2.19	0.305	87.4	3.28	1.2	4.64
CEH001-024		4.53	<0.01		0.034	6.82	2.01	800	2.00	0.166	2.12	0.176	88.4	2.54	1.7	4.70
CEH001-025		3.18	<0.01		0.041	7.46	4.61	690	1.97	0.193	2.28	0.452	80.4	7.18	1.2	4.18
CEH001-026		4.24	<0.01		0.037	6.72	2.29	630	1.90	0.128	1.68	0.115	88.8	3.71	1.3	4.19
CEH001-027		1.09	0.01		0.057	8.06	6.92	530	1.60	0.166	4.20	0.408	36.3	30.2	22.4	3.64
CEH001-028		2.91	<0.01		0.055	6.96	4.03	600	1.80	0.208	1.25	0.389	84.0	11.10	6.1	4.33
CEH001-029		1.62	<0.01		0.012	7.03	2.74	349	1.16	0.076	3.90	0.197	51.0	7.91	0.7	2.53
CEH001-030		2.31	<0.01		0.027	6.81	2.17	630	1.87	0.154	1.99	0.099	86.5	6.00	1.2	4.53
CEH001-031		1.89	<0.01		0.067	7.31	2.57	620	1.60	0.282	3.96	0.205	68.1	18.00	8.0	4.48
CEH001-032		1.31	<0.01		0.027	7.66	2.37	610	1.37	0.050	5.93	0.311	42.8	23.7	13.0	4.11
CEH001-033		3.86	0.01		0.014	7.79	1.81	780	1.34	0.047	6.10	0.280	42.0	28.3	13.1	4.27
CEH001-034		3.24	<0.01		0.017	7.38	1.05	810	1.44	0.014	6.16	0.271	41.8	27.9	12.7	4.67
CEH001-035		0.09	0.52		7.92	5.96	23.0	179	1.19	8.00	1.41	1.495	70.5	5.29	23.4	2.13



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration 1-3-22

Page: 2 - B  
Total # Pages: 2 (A - D)  
Plus Appendix Pages  
Finalized Date: 28-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS BU22052061

Sample Description	Method Analyte Units LOD	ME-MS61L Cu ppm 0.02	ME-MS61L Fe % 0.002	ME-MS61L Ga ppm 0.05	ME-MS61L Ge ppm 0.05	ME-MS61L Hf ppm 0.004	ME-MS61L In ppm 0.005	ME-MS61L K % 0.01	ME-MS61L La ppm 0.005	ME-MS61L Li ppm 0.2	ME-MS61L Mg % 0.01	ME-MS61L Mn ppm 0.2	ME-MS61L Mo ppm 0.02	ME-MS61L Na % 0.001	ME-MS61L Nb ppm 0.005	ME-MS61L Ni ppm 0.08
CEH001-000		37.5	8.16	19.95	0.16	4.15	0.070	1.37	23.2	8.9	5.58	1170	2.36	2.12	29.6	174.0
CEH001-001		13.45	2.00	16.45	0.10	4.49	0.043	2.29	48.7	3.3	0.21	57.7	0.42	1.300	12.50	1.91
CEH001-002		7.48	2.44	18.40	0.11	4.80	0.037	2.31	54.9	4.0	0.25	78.3	0.41	1.415	12.95	2.67
CEH001-003		13.05	2.69	16.10	0.10	4.49	0.046	2.57	47.3	5.1	0.31	182.0	0.50	0.619	13.35	4.46
CEH001-004		6.62	1.990	16.25	0.10	4.38	0.033	2.43	46.5	3.2	0.21	846	0.50	1.145	12.20	4.83
CEH001-005		11.50	1.710	9.34	<0.05	1.575	0.023	2.08	13.80	1.4	0.13	952	0.98	0.353	4.26	8.93
CEH001-006		14.00	3.83	19.25	0.08	3.49	0.054	3.93	27.5	3.8	0.37	719	0.70	1.820	6.88	25.7
CEH001-007		5.96	2.24	16.00	0.10	4.65	0.031	2.67	48.6	2.8	0.28	310	0.87	1.070	11.55	6.09
CEH001-008		10.85	2.46	16.00	0.10	4.55	0.040	2.61	45.5	3.7	0.29	580	0.57	1.050	11.35	3.34
CEH001-009		12.95	8.17	19.60	0.10	3.47	0.065	1.65	19.80	14.5	0.92	565	0.35	1.640	3.13	2.05
CEH001-010		2.56	7.60	18.60	0.09	3.56	0.061	1.55	23.3	11.9	0.68	524	0.49	1.995	3.86	2.54
CEH001-011		2.48	2.08	15.15	0.10	4.13	0.038	2.27	43.9	3.6	0.29	533	0.86	1.410	11.70	1.24
CEH001-012		2.25	2.00	15.55	0.09	4.19	0.042	2.18	45.6	3.4	0.27	580	0.51	1.620	11.40	0.53
CEH001-013		2.11	1.930	15.20	0.10	4.33	0.033	2.26	44.2	3.2	0.31	724	0.62	1.500	12.15	0.61
CEH001-014		1.75	1.890	15.40	0.10	4.51	0.038	2.34	46.1	3.6	0.29	510	0.31	1.540	13.10	0.37
CEH001-015		1.81	1.960	15.65	0.10	4.40	0.039	2.35	47.4	3.3	0.26	309	0.20	1.470	11.80	0.54
CEH001-016		2.51	2.06	14.90	0.10	4.12	0.036	2.11	43.0	3.5	0.29	661	0.42	1.760	12.10	0.51
CEH001-017		1.93	2.10	15.55	0.10	4.36	0.042	2.12	45.0	3.9	0.30	680	0.27	1.780	12.60	0.42
CEH001-018		1.44	1.970	16.35	0.10	4.56	0.042	2.39	45.6	3.5	0.30	567	0.30	1.635	13.55	0.51
CEH001-019		1.61	2.15	15.30	0.10	4.32	0.042	2.14	43.8	4.1	0.34	687	0.35	1.640	13.05	0.44
CEH001-020		2.28	1.830	10.90	0.08	3.41	0.032	1.46	37.3	3.6	0.30	634	0.52	1.620	10.25	0.54
CEH001-021		2.02	2.23	15.95	0.09	4.34	0.050	2.41	36.7	4.2	0.38	919	0.69	1.415	12.40	0.55
CEH001-022		89.1	5.37	13.20	0.06	1.385	0.042	2.08	11.75	13.5	1.39	2590	0.31	1.990	1.360	29.0
CEH001-023		5.65	1.970	14.80	0.10	4.52	0.035	2.26	41.1	5.7	0.37	704	1.06	1.255	12.45	1.03
CEH001-024		4.95	2.24	15.90	0.10	4.29	0.041	2.47	41.7	3.6	0.37	749	1.40	1.250	12.65	0.44
CEH001-025		7.27	3.86	16.95	0.10	4.27	0.050	2.11	37.9	8.0	0.74	1245	0.99	1.755	11.00	1.14
CEH001-026		3.55	2.19	15.15	0.11	4.22	0.039	2.22	43.7	3.8	0.43	693	0.89	1.430	12.35	1.05
CEH001-027		125.5	6.02	14.85	0.08	1.945	0.049	1.89	15.70	14.1	1.27	2070	1.14	1.970	1.720	23.4
CEH001-028		24.5	2.84	14.60	0.08	3.70	0.037	2.25	40.8	5.0	0.56	968	1.67	1.425	9.54	6.26
CEH001-029		11.00	5.20	16.75	0.07	3.27	0.046	1.20	23.7	12.7	1.04	1155	0.88	2.13	5.69	0.54
CEH001-030		14.40	2.47	16.45	0.09	4.23	0.043	2.33	42.0	4.4	0.45	530	1.09	1.320	13.50	1.08
CEH001-031		73.8	4.15	15.00	0.08	3.05	0.045	2.16	32.4	7.4	0.89	1245	0.73	1.595	7.35	11.25
CEH001-032		75.6	5.89	14.20	0.07	2.04	0.046	2.04	20.2	12.2	1.48	1870	0.56	1.425	2.12	19.80
CEH001-033		40.4	5.98	14.20	0.07	1.950	0.047	2.22	19.15	10.7	1.60	1655	0.49	1.430	2.25	22.2
CEH001-034		41.5	6.18	13.60	0.07	1.900	0.046	2.30	19.10	9.9	1.87	1695	0.44	1.190	2.08	22.8
CEH001-035		1030	2.18	8.51	0.08	4.38	0.129	2.93	35.3	4.0	0.95	216	4.81	0.186	6.85	10.95



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration 1-3-22

Page: 2 - C  
Total # Pages: 2 (A - D)  
Plus Appendix Pages  
Finalized Date: 28-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS BU22052061

Sample Description	Method Analyte Units LOD	ME-MS61L P %	ME-MS61L Pb ppm	ME-MS61L Rb ppm	ME-MS61L Re ppm	ME-MS61L S %	ME-MS61L Sb ppm	ME-MS61L Sc ppm	ME-MS61L Se ppm	ME-MS61L Sn ppm	ME-MS61L Sr ppm	ME-MS61L Ta ppm	ME-MS61L Te ppm	ME-MS61L Th ppm	ME-MS61L Ti %	ME-MS61L Tl ppm
		0.001	0.01	0.02	0.0004	0.01	0.02	0.01	0.006	0.02	0.02	0.01	0.005	0.004	0.001	0.002
CEH001-000		0.212	4.06	20.0	<0.0004	0.04	0.13	19.00	0.061	1.65	577	1.89	0.007	3.08	1.240	0.083
CEH001-001		0.015	8.34	116.5	<0.0004	0.01	0.60	4.43	0.046	3.45	49.0	0.93	0.005	19.30	0.155	0.596
CEH001-002		0.016	9.44	123.5	0.0021	0.01	0.57	4.78	0.041	3.11	53.5	0.95	<0.005	20.6	0.156	0.590
CEH001-003		0.019	6.25	143.0	0.0017	0.01	0.65	5.15	0.036	2.20	44.6	0.95	<0.005	18.40	0.179	0.656
CEH001-004		0.017	9.15	158.0	0.0013	0.01	0.50	4.29	0.014	2.38	60.6	0.93	<0.005	18.70	0.155	0.717
CEH001-005		0.011	19.75	130.0	0.0012	0.01	0.59	7.76	0.009	1.10	32.2	0.28	<0.005	5.46	0.138	0.634
CEH001-006		0.028	10.85	259	0.0008	0.03	0.67	20.3	0.042	1.67	78.0	0.49	<0.005	10.80	0.241	1.255
CEH001-007		0.021	7.38	178.5	0.0006	0.01	0.53	4.75	0.035	2.34	51.4	0.87	<0.005	19.75	0.148	0.832
CEH001-008		0.024	10.45	172.5	0.0007	0.01	0.58	6.23	0.033	2.24	51.2	0.83	<0.005	18.30	0.199	0.778
CEH001-009		0.079	10.70	106.0	0.0004	<0.01	0.98	28.8	0.016	1.12	58.8	0.24	<0.005	5.80	0.420	0.502
CEH001-010		0.064	8.07	96.6	0.0004	0.01	0.96	26.2	0.040	1.14	68.1	0.28	<0.005	6.68	0.434	0.455
CEH001-011		0.023	9.16	142.0	<0.0004	0.05	0.53	4.16	0.025	2.17	82.0	0.83	<0.005	17.30	0.150	0.670
CEH001-012		0.022	6.63	149.0	<0.0004	0.01	0.46	4.08	0.030	2.19	82.6	0.83	<0.005	18.00	0.147	0.625
CEH001-013		0.024	16.65	144.5	<0.0004	0.02	0.51	4.01	0.031	2.20	87.1	0.87	<0.005	17.80	0.156	0.661
CEH001-014		0.023	8.55	148.5	<0.0004	0.02	0.51	3.97	0.028	2.31	91.8	0.93	<0.005	18.40	0.166	0.681
CEH001-015		0.023	8.55	160.0	<0.0004	0.01	0.50	4.10	0.040	2.29	65.7	0.84	<0.005	18.60	0.152	0.687
CEH001-016		0.023	10.95	128.0	<0.0004	0.04	0.57	3.74	0.009	2.27	93.6	0.87	<0.005	17.90	0.150	0.608
CEH001-017		0.023	10.00	131.0	<0.0004	0.04	0.57	4.11	0.025	2.22	99.5	0.91	<0.005	17.50	0.163	0.605
CEH001-018		0.024	8.83	156.0	<0.0004	0.02	0.56	4.18	0.022	2.38	107.0	0.96	<0.005	18.85	0.174	0.673
CEH001-019		0.024	11.10	133.5	<0.0004	0.06	0.55	3.98	0.026	2.25	122.5	0.92	<0.005	18.10	0.168	0.614
CEH001-020		0.018	20.5	90.4	<0.0004	0.09	0.53	3.09	0.020	1.60	111.5	0.73	<0.005	13.25	0.130	0.421
CEH001-021		0.023	50.8	129.0	<0.0004	0.06	0.52	4.10	0.010	2.45	140.5	0.88	<0.005	15.45	0.163	0.652
CEH001-022		0.042	135.0	109.5	<0.0004	0.10	0.63	22.9	0.038	0.86	188.0	0.09	<0.005	3.87	0.286	0.594
CEH001-023		0.022	33.4	131.5	<0.0004	0.18	0.51	4.15	0.047	2.20	94.9	0.87	0.006	16.55	0.159	0.612
CEH001-024		0.022	19.60	143.0	<0.0004	0.16	0.47	4.00	0.056	2.19	98.1	0.92	0.011	17.35	0.163	0.636
CEH001-025		0.043	23.8	113.0	<0.0004	0.18	0.73	11.10	0.078	2.13	112.5	0.77	0.016	14.55	0.323	0.559
CEH001-026		0.024	16.75	123.5	<0.0004	0.13	0.45	4.33	0.038	2.08	88.6	0.91	<0.005	17.60	0.161	0.575
CEH001-027		0.061	19.25	89.6	<0.0004	0.21	0.69	27.4	0.078	0.84	145.0	0.10	0.006	5.45	0.337	0.501
CEH001-028		0.031	17.65	125.5	0.0007	0.20	0.57	9.35	0.074	1.96	76.3	0.67	0.026	14.95	0.195	0.561
CEH001-029		0.074	11.40	68.8	0.0004	0.12	1.04	23.0	0.056	1.46	149.0	0.38	0.010	6.64	0.602	0.289
CEH001-030		0.024	7.45	124.5	0.0020	0.17	0.54	4.83	0.137	2.52	105.0	0.93	0.027	18.30	0.182	0.555
CEH001-031		0.044	12.50	122.5	0.0005	0.39	0.84	16.70	0.106	2.06	141.5	0.50	0.047	11.65	0.280	0.516
CEH001-032		0.061	8.93	114.5	<0.0004	0.08	0.72	26.5	0.038	0.77	169.5	0.14	0.005	6.79	0.339	0.490
CEH001-033		0.062	6.77	120.5	<0.0004	0.05	0.70	26.7	0.018	0.66	171.0	0.14	<0.005	6.62	0.328	0.499
CEH001-034		0.059	7.04	134.0	<0.0004	0.02	0.77	26.0	0.031	0.62	164.0	0.13	<0.005	6.42	0.348	0.538
CEH001-035		0.044	4600	129.0	0.0015	1.08	3.60	9.33	2.53	4.88	78.3	0.46	5.17	13.40	0.224	0.648



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Project: Exploration 1-3-22

Page: 2 - D  
Total # Pages: 2 (A - D)  
Plus Appendix Pages  
Finalized Date: 28-APR-2022  
Account: HENMINEXP

## CERTIFICATE OF ANALYSIS BU22052061

Sample Description	Method Analyte Units LOD	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L	ME-MS61L
		U	V	W	Y	Zn	Zr
		ppm	ppm	ppm	ppm	ppm	ppm
		0.01	0.1	0.008	0.01	0.2	0.1
CEH001-000		1.16	186.0	0.127	18.10	105.5	195.0
CEH001-001		4.51	8.6	0.532	20.7	43.5	129.0
CEH001-002		5.03	9.4	0.745	28.7	63.6	140.0
CEH001-003		4.10	19.2	0.554	22.9	57.3	126.5
CEH001-004		4.87	8.8	0.404	20.4	61.1	126.0
CEH001-005		2.24	43.1	0.234	7.59	35.2	44.6
CEH001-006		3.05	109.5	0.325	16.25	79.0	100.5
CEH001-007		4.40	12.2	0.309	24.6	61.6	129.0
CEH001-008		4.00	32.0	0.525	22.0	72.4	128.0
CEH001-009		2.31	261	0.903	21.5	298	118.5
CEH001-010		2.98	234	0.776	24.2	349	118.0
CEH001-011		4.68	9.3	0.307	22.5	85.8	117.5
CEH001-012		3.94	7.8	0.268	23.4	62.9	120.5
CEH001-013		4.03	7.6	0.298	23.0	57.2	122.0
CEH001-014		4.04	7.8	0.341	23.0	62.6	127.5
CEH001-015		3.70	8.1	0.303	22.7	62.4	124.5
CEH001-016		3.83	7.1	0.380	21.1	66.1	120.0
CEH001-017		3.67	7.7	0.446	23.3	87.1	124.5
CEH001-018		4.42	8.4	0.418	21.3	79.4	131.0
CEH001-019		4.25	7.6	0.452	20.0	108.0	122.5
CEH001-020		3.52	5.5	0.436	15.65	112.5	100.0
CEH001-021		3.73	8.0	0.417	24.8	134.5	124.5
CEH001-022		1.16	182.0	0.562	11.20	524	44.6
CEH001-023		4.04	9.4	0.449	18.90	122.5	118.5
CEH001-024		4.36	7.8	0.459	18.15	86.5	121.0
CEH001-025		3.89	74.7	0.651	19.80	228	127.0
CEH001-026		4.57	9.9	0.444	18.25	77.3	119.5
CEH001-027		1.64	231	0.694	11.70	277	64.9
CEH001-028		4.63	61.6	0.543	15.80	107.0	107.5
CEH001-029		2.22	190.0	1.450	17.45	223	108.0
CEH001-030		4.33	19.8	0.470	17.10	69.1	123.5
CEH001-031		3.22	133.5	0.784	14.90	117.5	93.3
CEH001-032		2.20	218	0.628	11.90	182.5	71.8
CEH001-033		2.00	219	0.536	12.60	155.5	68.8
CEH001-034		1.87	214	0.708	13.50	144.0	66.4
CEH001-035		4.06	61.8	4.06	14.25	387	152.0



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

To: HENTY GOLD PTY LTD  
EXPLORATION DEPARTMENT  
PO BOX 231  
QUEENSTOWN TAS 7467

Page: Appendix 1  
Total # Appendix Pages: 1  
Finalized Date: 28-APR-2022  
Account: HENMINEXP

Project: Exploration 1-3-22

**CERTIFICATE OF ANALYSIS BU22052061**

	CERTIFICATE COMMENTS
	<p style="text-align: center;"><b>LABORATORY ADDRESSES</b></p> <p>Processed at ALS Perth located at 31 Denninup Way, Malaga, Australia. Processed at ALS Perth Sample Preparation at 79 Distinction Road, Wangara, WA, Australia</p> <p>Applies to Method: BAG-21 ME-MS61L SPLIT-X</p> <p>Processed at ALS Townsville located at 14-15 Desma Court, Bohle, Townsville, QLD, Australia.</p> <p>Applies to Method: Au-AA25</p> <p>Processed at ALS Burnie located at 39 River Road, Burnie, TAS, Australia.</p> <p>Applies to Method: BAG-01 CRU-21 LEV-01 LOG-22 PUL-23 PUL-QC SPL-21 WEI-21</p>