



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Page: 1

Total # Pages: 9 (A – E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

## CERTIFICATE AD25025626

Project: EDGI\_18

This report is for 300 samples of Drill Core submitted to our lab in Burnie, TAS, Australia on 7-JAN-2025.

The following have access to data associated with this certificate:

ESTHER LITTLE

MITCHELL PETERSEN

DECLAN RADFORD

## SAMPLE PREPARATION

ALS CODE	DESCRIPTION
PUL-QC	Pulverizing QC Test
SPL-21	Split sample – riffle splitter
OA-HSUL10	Handling of High Sulphide Samples
WEI-21	Received Sample Weight
LEV-01	Waste Disposal Levy
LOG-22	Sample login – Rcd w/o BarCode
LOG-24	Pulp Login – Rcd w/o Barcode
CRU-21	Crush entire sample
PUL-23	Pulv Sample – Split/Retain
BAG-01	Bulk Master for Storage
BAG-21	Raw Sample in a new bag

## ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-ICP21	Au 30q FA ICP-AES Finish	ICP-AES
ME-XRF15b	Various elements in ores by fusion XRF	XRF
ME-MS61r	4A multi-element ICP-MS + REE	

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

\*\*\*\*\* See Appendix Page for comments regarding this certificate \*\*\*\*\*

Signature:

Cameron Brosnan, Laboratory Manager, Perth



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD  
PO BOX 20  
ZEEHAN TAS 7469

Page: 2 - A  
Total # Pages: 9 (A - E)  
Plus Appendix Pages  
Finalized Date: 5-MAR-2025  
Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg 0.02	PUL-QC Pass75um % 0.01	Au-ICP21 Au ppm 0.001	ME-XRF15b Sn % 0.005	ME-MS61r Ag ppm 0.01	ME-MS61r Al % 0.01	ME-MS61r As ppm 0.2	ME-MS61r Ba ppm 10	ME-MS61r Be ppm 0.05	ME-MS61r Bi ppm 0.01	ME-MS61r Ca % 0.01	ME-MS61r Cd ppm 0.02	ME-MS61r Ce ppm 0.01	ME-MS61r Co ppm 0.1	ME-MS61r Cr ppm 1
RDD284791		1.51	93.0	<0.001	<0.005	0.48	7.97	8.4	60	2.90	0.08	3.79	1.01	41.2	68.1	208
RDD284792		2.58	98.0	<0.001	<0.005	0.37	6.91	31.5	50	3.24	0.16	5.37	0.71	42.4	39.4	186
RDD284793		2.41	87.0	0.008	0.007	1.82	4.97	141.0	30	2.20	1.08	0.26	16.20	24.8	21.3	150
RDD284794		1.97		0.001	<0.005	1.88	6.71	83.2	50	3.06	1.28	0.30	23.8	33.2	48.7	200
RDD284795		3.00		0.001	<0.005	0.09	6.00	4.4	290	1.30	0.08	10.35	0.35	44.8	41.6	125
RDD284796		1.44		0.001	<0.005	0.09	6.26	4.1	330	1.48	0.06	7.99	0.18	51.5	34.0	111
RDD284797		2.44		<0.001	<0.005	0.07	5.92	2.9	470	1.17	0.07	10.55	0.17	50.7	38.5	126
RDD284798		1.52		0.003	<0.005	0.04	6.62	2.0	520	1.39	0.07	8.05	0.05	48.7	40.4	176
RDD284799		3.17		<0.001	<0.005	0.05	5.43	2.1	170	1.15	0.07	10.45	1.92	23.4	37.7	88
RDD284800		3.17		<0.001	<0.005	0.06	6.90	0.7	160	0.88	0.02	6.65	0.28	25.7	51.7	104
RDD284801		2.92		<0.001	<0.005	0.05	6.65	0.5	60	1.10	0.01	8.09	0.89	24.1	40.8	94
RDD284802		4.85		<0.001	<0.005	0.01	7.12	1.1	180	0.72	0.01	6.17	0.59	26.4	45.9	100
RDD284803		4.07		<0.001	<0.005	0.05	6.71	1.0	200	0.63	0.02	8.01	0.08	23.4	44.0	107
RDD284804		4.19		<0.001	<0.005	0.04	7.66	0.6	110	0.69	0.02	8.06	0.13	24.9	48.4	116
RDD284805		3.65		0.001	<0.005	0.18	5.81	6.1	100	1.02	0.08	9.33	0.50	44.5	40.9	129
RDD284806		3.38		0.001	0.005	0.04	4.58	3.4	250	0.89	0.09	18.10	0.09	38.8	26.3	84
RDD284807		3.81		0.001	<0.005	0.07	4.62	5.0	230	0.89	0.13	16.05	0.12	43.6	27.8	97
RDD284808		3.51		<0.001	<0.005	0.07	4.16	1.0	170	0.91	0.12	18.60	0.21	40.3	24.5	83
RDD284809		3.70		0.001	<0.005	0.07	5.73	1.8	130	1.18	0.12	10.35	0.07	59.0	30.3	84
RDD284810		3.84		<0.001	<0.005	0.05	2.72	1.6	50	0.67	0.05	23.2	0.06	30.7	15.6	35
RDD284811		3.91		0.001	0.005	0.09	4.60	4.3	110	1.10	0.10	15.50	0.21	44.8	26.0	76
RDD284812		4.06		0.001	0.005	0.07	3.95	7.5	90	0.86	0.09	17.75	0.12	38.5	23.3	83
RDD284813		3.25		0.002	<0.005	0.08	4.29	3.1	100	0.98	0.10	16.20	0.08	40.5	25.7	82
RDD284814		3.66		<0.001	<0.005	0.06	4.14	4.3	90	0.89	0.10	18.30	0.08	37.3	24.0	80
RDD284815		<0.02			1.180											
RDD284816		0.07		1.690		0.15	7.63	330	700	2.41	0.36	0.93	0.04	79.7	16.6	125
RDD284817		3.37		0.003	<0.005	0.09	4.81	11.1	120	1.12	0.12	15.35	0.07	48.2	29.1	105
RDD284818		3.63		<0.001	<0.005	0.07	3.94	5.5	80	0.89	0.10	16.75	0.22	39.3	23.1	76
RDD284819		3.85		0.004	<0.005	0.09	4.57	6.8	100	0.87	0.13	16.00	0.39	43.9	26.3	100
RDD284820		1.89		<0.001	<0.005	0.01	0.10	1.2	10	<0.05	0.03	0.43	<0.02	1.97	0.6	7
RDD284821		4.83		0.002	<0.005	0.08	4.90	13.3	50	0.78	0.15	15.40	0.31	41.2	31.2	97
RDD284822		3.73		0.001	<0.005	0.12	5.35	0.5	150	1.32	0.11	12.75	0.11	67.7	23.8	67
RDD284823		3.07		<0.001	<0.005	0.06	3.11	7.2	50	0.81	0.08	21.7	0.07	28.8	21.1	61
RDD284824		3.56		0.001	<0.005	0.15	4.84	4.6	120	1.18	0.15	13.90	0.09	47.7	30.0	107
RDD284825		3.45		0.001	<0.005	0.11	4.17	2.2	90	0.98	0.15	18.00	0.05	42.1	25.8	76
RDD284826		3.32		0.001	<0.005	0.14	5.66	6.2	120	1.23	0.16	12.30	0.16	57.9	33.0	112
RDD284827		3.89		0.001	<0.005	0.10	4.64	4.0	100	1.04	0.14	15.65	0.19	47.6	27.2	92
RDD284828		3.01		0.002	<0.005	0.11	5.58	5.6	130	1.31	0.17	9.91	0.09	56.3	32.5	132
RDD284829		3.46		0.002	<0.005	0.15	6.24	0.5	140	1.44	0.17	8.23	0.15	58.2	38.2	146
RDD284830		3.25		<0.001	<0.005	0.10	5.44	2.0	80	0.94	0.04	10.70	0.10	36.2	35.4	117



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Page: 2 - B

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Cs	Cu	Fe	Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb
		ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm
		0.05	0.2	0.01	0.05	0.05	0.1	0.005	0.01	0.5	0.2	0.01	5	0.05	0.01	0.1
RDD284791		12.25	187.5	10.20	23.4	0.20	4.7	0.884	0.95	16.6	77.8	2.33	3450	0.69	1.31	23.9
RDD284792		8.11	100.5	13.55	21.8	0.19	4.1	0.496	0.80	18.0	142.5	2.40	7320	0.48	0.06	21.7
RDD284793		3.84	29.6	22.5	15.85	0.38	2.7	20.6	0.04	10.4	68.6	2.11	13800	0.67	0.02	13.5
RDD284794		6.25	124.0	11.35	21.1	0.18	3.0	7.64	0.97	14.1	139.0	1.70	5310	1.26	0.01	17.4
RDD284795		5.42	95.3	7.70	18.75	0.17	4.3	0.399	0.63	20.5	26.6	2.42	1120	0.34	2.25	20.1
RDD284796		7.16	83.4	7.52	19.75	0.18	5.4	0.088	0.63	23.5	28.1	2.41	928	0.20	2.38	25.9
RDD284797		3.92	88.9	7.45	19.55	0.16	4.9	0.086	0.55	24.2	23.8	2.42	939	0.27	2.16	24.2
RDD284798		5.96	73.6	9.14	20.1	0.20	4.8	0.088	0.99	21.9	28.1	3.55	1370	1.42	2.31	26.0
RDD284799		3.49	74.2	7.04	13.60	0.13	2.4	0.081	0.39	9.9	17.4	2.70	1535	0.49	2.62	10.4
RDD284800		4.07	105.5	9.56	19.50	0.16	2.5	0.093	0.26	10.8	32.2	4.04	1725	0.48	2.78	10.5
RDD284801		1.58	104.5	9.12	17.70	0.16	2.2	0.124	0.13	10.4	27.6	3.60	3020	0.45	2.80	9.9
RDD284802		7.33	69.4	9.22	18.40	0.17	2.7	0.097	0.33	11.0	30.7	4.05	1830	0.48	2.94	11.2
RDD284803		6.70	86.2	9.04	18.00	0.16	2.5	0.082	0.44	10.1	29.6	4.11	1505	0.70	2.41	9.3
RDD284804		10.20	112.5	9.47	20.2	0.17	3.0	0.089	0.36	11.0	28.1	4.01	1520	0.64	2.41	10.3
RDD284805		1.41	104.5	8.20	18.50	0.17	4.4	0.101	0.28	19.8	33.5	2.94	1235	0.52	1.76	21.5
RDD284806		0.97	64.4	6.16	14.45	0.13	3.4	0.066	0.43	17.4	28.3	2.10	1385	0.50	1.50	16.5
RDD284807		0.80	72.8	6.08	14.25	0.13	3.3	0.093	0.41	19.2	27.6	1.95	1350	0.87	1.75	16.7
RDD284808		0.78	70.7	5.47	12.45	0.11	3.1	0.103	0.36	18.0	24.0	1.59	1340	0.97	1.75	15.4
RDD284809		2.31	89.1	7.10	16.85	0.16	5.1	0.055	0.53	24.7	33.9	2.17	1195	1.57	2.49	28.6
RDD284810		0.84	43.3	3.77	8.37	0.09	2.0	0.033	0.22	14.6	19.4	1.05	1525	1.25	1.08	10.1
RDD284811		1.35	72.1	6.09	14.10	0.13	3.6	0.074	0.33	20.4	29.4	1.93	1370	1.23	1.92	18.4
RDD284812		1.97	52.9	5.06	13.15	0.11	2.8	0.048	0.30	17.4	27.4	1.76	1350	0.61	1.52	14.4
RDD284813		1.62	71.2	5.82	13.80	0.12	3.0	0.040	0.31	18.0	27.7	1.83	1260	0.82	1.72	15.6
RDD284814		1.26	61.5	5.49	13.50	0.11	3.1	0.034	0.28	17.1	28.2	1.82	1340	0.78	1.61	15.4
RDD284815																
RDD284816		9.40	27.2	4.18	19.05	0.16	3.7	0.066	2.80	40.9	56.0	1.81	413	0.90	0.75	15.4
RDD284817		1.48	69.4	5.88	15.00	0.12	3.6	0.044	0.39	21.6	29.6	1.93	1320	0.82	1.95	17.9
RDD284818		1.27	58.4	5.05	12.60	0.10	2.9	0.065	0.27	17.6	25.7	1.66	1220	0.87	1.55	14.9
RDD284819		1.44	64.6	5.77	14.50	0.11	3.3	0.128	0.29	19.0	30.1	2.04	1545	0.96	1.76	16.1
RDD284820		0.07	3.3	0.63	0.48	<0.05	0.4	<0.005	0.01	1.0	1.9	0.04	88	0.45	0.03	1.5
RDD284821		1.50	68.1	6.53	15.10	0.10	3.5	0.119	0.17	19.0	36.1	2.54	1485	0.93	1.80	17.3
RDD284822		2.20	61.4	5.43	17.45	0.22	5.3	0.096	0.43	30.4	31.9	2.00	1405	0.81	2.34	29.8
RDD284823		1.05	43.6	3.85	10.65	0.08	2.1	0.047	0.15	12.1	23.0	1.35	1615	0.81	1.21	9.7
RDD284824		1.51	69.4	5.84	14.75	0.11	3.2	0.089	0.33	20.0	31.0	1.99	1410	0.67	1.91	16.1
RDD284825		1.41	65.7	5.29	13.65	0.10	2.9	0.081	0.26	17.2	28.1	1.72	1660	0.90	1.59	14.3
RDD284826		1.82	84.6	7.03	17.15	0.14	4.1	0.090	0.34	26.1	35.1	2.27	1540	0.88	2.29	22.0
RDD284827		1.17	67.1	5.74	13.80	0.11	3.4	0.101	0.26	19.9	28.6	1.81	1765	0.72	1.91	15.8
RDD284828		1.94	75.9	6.62	16.70	0.17	3.7	0.060	0.33	25.1	33.7	2.29	1250	1.41	2.26	19.2
RDD284829		2.68	105.5	7.85	17.80	0.16	3.9	0.086	0.33	26.7	35.8	2.47	1190	1.91	2.67	20.3
RDD284830		4.53	71.3	7.05	16.60	0.11	3.1	0.082	0.40	14.5	38.0	3.32	1445	0.21	1.06	15.7



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD  
PO BOX 20  
ZEEHAN TAS 7469

Project: EDGI\_18

Page: 2 - C  
Total # Pages: 9 (A - E)  
Plus Appendix Pages  
Finalized Date: 5-MAR-2025  
Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ni	P	Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th
		ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.2	10	0.5	0.1	0.002	0.01	0.05	0.1	1	0.2	0.2	0.05	0.05	0.01
RDD284791		146.0	1290	45.9	114.5	0.003	0.05	60.3	36.2	1	2.3	92.4	1.43	<0.05	2.69
RDD284792		96.6	1110	127.5	100.5	<0.002	0.01	69.2	32.5	1	9.5	57.0	1.26	<0.05	2.43
RDD284793		46.3	770	104.0	3.8	<0.002	7.81	42.8	23.8	4	50.8	45.1	0.83	<0.05	1.64
RDD284794		93.3	1020	2140	148.5	0.002	0.16	31.1	25.9	4	25.0	20.8	1.07	<0.05	2.04
RDD284795		82.3	990	7.1	16.6	<0.002	0.44	1.25	27.3	1	2.8	239	1.24	<0.05	3.31
RDD284796		73.7	1040	5.6	18.8	<0.002	0.22	1.22	27.8	1	2.7	226	1.58	<0.05	4.90
RDD284797		73.1	940	4.9	13.4	<0.002	0.32	1.22	25.6	1	2.8	266	1.44	<0.05	5.00
RDD284798		97.7	1170	18.0	18.0	<0.002	0.06	0.48	28.3	1	2.4	263	1.59	<0.05	4.16
RDD284799		53.8	720	113.0	7.7	0.002	0.19	0.38	30.8	1	1.1	266	0.63	0.05	1.32
RDD284800		65.1	880	42.8	10.3	0.002	0.17	0.30	46.3	1	1.0	218	0.62	<0.05	1.20
RDD284801		54.6	830	39.7	4.1	0.002	0.12	0.41	42.2	1	1.2	221	0.56	<0.05	1.06
RDD284802		58.8	930	6.7	15.3	0.002	0.15	0.45	45.3	1	1.0	294	0.66	<0.05	1.39
RDD284803		60.5	750	4.4	19.4	0.002	0.06	0.28	42.6	1	1.1	301	0.56	<0.05	1.30
RDD284804		67.3	840	3.4	23.1	0.002	0.14	0.23	46.3	1	1.0	213	0.61	<0.05	1.40
RDD284805		80.8	1030	80.4	6.0	0.002	0.73	2.17	26.8	1	2.2	169.0	1.26	<0.05	2.66
RDD284806		53.0	800	5.8	8.3	0.002	1.14	0.44	18.2	1	1.7	330	1.02	<0.05	3.30
RDD284807		64.3	770	10.5	8.7	0.002	1.48	0.47	17.2	1	1.7	298	1.03	0.08	3.78
RDD284808		54.0	750	7.8	9.5	0.002	1.71	0.45	16.2	1	1.6	319	0.96	0.06	3.36
RDD284809		57.9	820	13.8	22.6	0.002	2.62	0.72	19.8	1	2.2	250	1.74	0.07	5.41
RDD284810		23.9	570	13.8	12.4	<0.002	1.52	0.79	9.4	1	1.0	380	0.63	<0.05	2.37
RDD284811		52.2	770	16.6	12.1	<0.002	2.21	1.14	16.1	1	1.8	382	1.13	0.05	3.93
RDD284812		52.8	660	11.4	15.5	0.002	1.54	0.87	15.2	1	1.5	308	0.87	0.05	3.38
RDD284813		52.7	780	10.5	11.8	0.002	1.80	0.91	17.0	1	1.6	312	0.96	0.05	3.21
RDD284814		50.7	710	9.3	10.5	0.002	1.49	0.94	16.0	1	1.6	336	0.94	0.05	3.34
RDD284815															
RDD284816		64.1	740	17.8	162.5	<0.002	0.14	338	13.9	<1	3.7	147.0	1.10	<0.05	13.50
RDD284817		67.1	810	10.4	13.6	0.002	1.66	1.08	18.8	1	1.9	294	1.12	<0.05	4.17
RDD284818		48.6	650	10.2	10.2	0.002	1.43	1.10	14.4	1	1.6	274	0.91	0.05	3.58
RDD284819		63.8	790	8.5	9.8	0.002	1.56	1.34	16.8	1	1.7	339	1.02	0.05	4.26
RDD284820		1.5	20	1.2	0.6	<0.002	0.02	0.21	0.4	<1	0.2	7.5	0.08	<0.05	0.31
RDD284821		64.6	860	8.4	5.9	0.002	1.62	1.47	18.2	1	1.6	289	1.08	0.06	3.93
RDD284822		46.5	650	22.7	16.8	0.002	1.52	1.71	16.6	1	3.3	321	1.87	<0.05	7.56
RDD284823		74.6	590	7.0	6.4	<0.002	0.99	1.07	11.3	<1	1.3	425	0.66	<0.05	2.91
RDD284824		70.8	790	12.5	12.5	0.002	1.43	1.55	18.6	1	2.3	314	1.07	0.09	4.27
RDD284825		54.2	690	24.0	10.9	0.002	1.27	1.51	16.0	1	2.0	382	0.91	0.05	4.04
RDD284826		78.3	880	17.2	13.8	0.002	1.83	2.20	21.3	<1	2.7	308	1.46	0.05	5.45
RDD284827		62.7	770	15.5	10.8	0.002	1.53	2.22	17.2	1	2.0	353	1.04	0.06	4.43
RDD284828		83.1	900	18.5	12.4	0.005	1.62	2.74	21.4	1	2.5	275	1.26	0.06	4.93
RDD284829		92.6	960	19.6	12.0	0.005	2.15	3.90	23.2	1	2.7	236	1.36	0.08	5.08
RDD284830		68.4	890	3.0	51.7	<0.002	0.16	1.79	23.6	<1	2.3	277	0.99	<0.05	2.08



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 2 - D

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ti	U	V	W	Y	Zn	Zr	Dy	Er	Eu	Gd	Ho	Lu	Nd	Pr
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.02	0.1	1	0.1	0.1	2	0.5	0.05	0.03	0.03	0.05	0.01	0.01	0.1	0.03
RDD284791		1.53	1.2	357	3.2	22.3	622	165.0	4.71	2.51	1.42	5.40	0.84	0.29	26.7	5.88
RDD284792		1.20	1.2	316	2.5	21.5	674	138.0	4.39	2.17	1.60	5.41	0.84	0.34	26.7	5.77
RDD284793		0.92	1.2	230	9.0	26.5	1760	90.8	5.52	2.60	2.46	5.08	1.02	0.29	15.8	3.41
RDD284794		1.78	1.4	302	8.2	26.3	4170	134.5	6.38	3.40	1.71	5.19	1.26	0.34	21.1	4.66
RDD284795		0.39	1.5	260	0.7	29.9	114	159.5	5.81	2.99	1.80	6.00	1.10	0.38	25.5	5.83
RDD284796		0.33	2.2	258	0.6	35.8	134	186.0	6.87	3.55	1.84	6.88	1.29	0.47	29.4	6.83
RDD284797		0.30	2.1	250	0.6	36.2	98	184.5	6.38	3.32	1.59	6.35	1.24	0.45	27.7	6.42
RDD284798		0.18	1.6	279	0.8	34.2	99	189.0	6.57	3.32	2.23	6.65	1.22	0.44	28.3	6.41
RDD284799		0.11	0.4	244	0.3	25.2	565	92.9	4.69	2.55	1.89	4.56	0.94	0.32	14.9	3.21
RDD284800		0.17	0.4	331	0.3	31.9	158	94.2	5.98	3.47	1.39	5.50	1.18	0.46	16.5	3.46
RDD284801		0.11	0.3	309	0.3	31.6	343	83.4	5.59	3.16	1.27	5.08	1.12	0.42	15.8	3.30
RDD284802		0.21	0.4	337	0.3	33.9	244	92.0	6.09	3.40	1.45	5.51	1.21	0.46	16.8	3.50
RDD284803		0.18	0.5	297	0.2	28.8	89	99.0	5.19	2.92	1.29	4.71	1.04	0.40	14.3	3.13
RDD284804		0.21	0.4	328	0.2	31.0	101	101.5	5.70	3.17	1.67	5.24	1.14	0.44	16.0	3.38
RDD284805		0.16	1.1	243	0.6	26.7	183	157.0	5.27	2.46	1.71	5.68	0.96	0.29	26.0	5.94
RDD284806		0.12	1.3	175	0.7	22.1	88	134.0	4.27	2.11	1.22	4.49	0.80	0.27	20.7	4.75
RDD284807		0.14	1.4	162	0.7	21.8	84	128.0	4.26	2.12	1.27	4.51	0.79	0.27	22.2	5.17
RDD284808		0.14	1.4	151	0.8	21.2	95	122.0	3.96	1.94	1.20	4.15	0.74	0.25	20.9	4.89
RDD284809		0.23	1.8	186	0.9	31.0	70	186.5	6.18	3.15	1.49	6.23	1.14	0.41	30.3	7.23
RDD284810		0.14	1.4	83	0.5	16.8	46	76.6	3.08	1.56	0.80	3.16	0.59	0.21	14.9	3.58
RDD284811		0.26	1.5	154	0.8	24.2	104	135.0	4.51	2.27	1.27	4.70	0.85	0.30	22.9	5.40
RDD284812		0.17	1.3	139	0.7	20.0	78	113.5	3.74	1.84	1.14	3.97	0.69	0.24	19.4	4.59
RDD284813		0.16	1.4	157	0.8	20.9	72	125.5	3.97	1.96	1.24	4.22	0.73	0.24	20.8	4.83
RDD284814		0.14	1.3	153	0.7	20.9	68	135.0	3.84	1.90	1.14	4.00	0.70	0.25	19.9	4.60
RDD284815																
RDD284816		0.79	2.8	111	2.4	16.6	96	140.5	3.67	1.70	1.15	4.36	0.59	0.26	36.3	9.36
RDD284817		0.15	1.5	176	0.9	23.2	78	142.5	4.38	2.20	1.37	4.68	0.81	0.28	23.9	5.67
RDD284818		0.14	1.4	139	0.7	20.8	107	114.5	3.73	1.85	1.07	3.94	0.69	0.25	20.0	4.75
RDD284819		0.15	1.7	157	0.7	22.5	159	128.5	4.20	2.14	1.01	4.45	0.80	0.29	21.9	5.19
RDD284820		<0.02	0.2	6	0.2	1.3	4	16.8	0.22	0.14	0.04	0.19	0.05	0.02	0.9	0.23
RDD284821		0.12	1.6	179	0.7	21.7	155	135.5	4.01	2.08	0.88	4.26	0.76	0.27	21.0	5.02
RDD284822		0.19	1.8	147	0.8	37.6	76	168.0	6.48	3.59	1.43	6.52	1.34	0.47	33.5	7.83
RDD284823		0.09	1.2	104	0.5	15.2	53	83.2	2.76	1.52	0.79	2.88	0.57	0.18	14.7	3.31
RDD284824		0.17	1.2	169	0.9	22.5	81	120.0	4.28	2.24	1.27	4.43	0.86	0.26	24.3	5.44
RDD284825		0.18	1.2	140	0.7	20.8	68	109.5	3.82	2.05	1.13	4.02	0.80	0.26	21.0	4.81
RDD284826		0.21	1.4	191	1.0	30.2	102	147.5	5.46	2.89	1.52	5.54	1.13	0.34	30.2	6.80
RDD284827		0.20	1.3	153	0.9	23.3	104	121.0	4.36	2.30	1.25	4.38	0.88	0.30	23.9	5.45
RDD284828		0.22	1.4	196	1.1	27.4	92	135.0	4.94	2.65	1.49	5.14	1.00	0.30	28.3	6.40
RDD284829		0.27	1.4	222	1.1	28.1	116	141.5	5.37	2.81	1.58	5.58	1.08	0.33	30.0	6.77
RDD284830		0.63	1.0	213	0.2	18.2	123	113.5	3.48	1.89	1.44	3.84	0.73	0.23	21.6	4.63



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 2 – E

Total # Pages: 9 (A – E)

Plus Appendix Pages

Finalized Date: 5–MAR–2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Sm	Tb	Tm	Yb
		ppm	ppm	ppm	ppm
		0.03	0.01	0.01	0.03
RDD284791		6.41	0.78	0.35	2.21
RDD284792		6.31	0.76	0.32	2.21
RDD284793		4.34	0.86	0.35	2.20
RDD284794		5.12	0.90	0.48	2.82
RDD284795		6.22	0.94	0.42	2.72
RDD284796		7.01	1.07	0.51	3.42
RDD284797		6.55	0.99	0.49	3.33
RDD284798		6.90	1.04	0.49	3.60
RDD284799		4.01	0.72	0.36	2.31
RDD284800		4.68	0.90	0.48	3.30
RDD284801		4.50	0.83	0.46	3.08
RDD284802		4.73	0.90	0.49	3.23
RDD284803		4.00	0.77	0.42	2.88
RDD284804		4.47	0.85	0.47	3.13
RDD284805		6.14	0.87	0.34	2.26
RDD284806		4.78	0.69	0.30	2.00
RDD284807		5.07	0.69	0.30	2.00
RDD284808		4.76	0.64	0.28	1.80
RDD284809		6.98	0.98	0.46	3.04
RDD284810		3.38	0.48	0.22	1.54
RDD284811		5.29	0.73	0.33	2.21
RDD284812		4.44	0.59	0.27	1.76
RDD284813		4.88	0.65	0.28	1.81
RDD284814		4.60	0.62	0.28	1.82
RDD284815					
RDD284816		6.95	0.59	0.25	2.13
RDD284817		5.45	0.72	0.31	2.11
RDD284818		4.55	0.61	0.27	1.84
RDD284819		4.99	0.68	0.30	2.03
RDD284820		0.19	0.03	0.02	0.17
RDD284821		4.88	0.65	0.30	1.95
RDD284822		7.20	1.04	0.48	3.20
RDD284823		3.15	0.44	0.19	1.28
RDD284824		5.15	0.67	0.28	1.90
RDD284825		4.62	0.62	0.25	1.76
RDD284826		6.55	0.83	0.36	2.37
RDD284827		5.20	0.69	0.30	1.94
RDD284828		6.09	0.79	0.33	2.12
RDD284829		6.46	0.86	0.35	2.22
RDD284830		4.68	0.58	0.23	1.61



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Page: 3 - A

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg	PUL-QC Pass75um %	Au-ICP21 Au ppm	ME-XRF15b Sn %	ME-MS61r Ag ppm	ME-MS61r Al %	ME-MS61r As ppm	ME-MS61r Ba ppm	ME-MS61r Be ppm	ME-MS61r Bi ppm	ME-MS61r Ca %	ME-MS61r Cd ppm	ME-MS61r Ce ppm	ME-MS61r Co ppm	ME-MS61r Cr ppm
		0.02	0.01	0.001	0.005	0.01	0.01	0.2	10	0.05	0.01	0.01	0.02	0.01	0.1	1
RDD284831		2.81		0.001	0.005	0.39	6.32	18.0	70	2.21	0.05	3.08	3.92	42.6	44.1	152
RDD284832		2.57		0.001	<0.005	0.22	6.79	12.3	100	1.52	0.03	2.02	0.54	41.6	41.2	216
RDD284833		2.84		0.001	<0.005	0.18	7.07	16.0	100	1.17	0.03	1.97	0.58	38.9	47.0	251
RDD284834		2.03		0.002	<0.005	0.16	6.51	18.4	70	1.51	0.05	5.84	0.44	37.8	44.1	194
RDD284835		3.64		0.001	<0.005	0.17	5.58	7.4	30	1.74	0.05	9.34	0.18	37.8	33.8	124
RDD284836		3.62		0.001	<0.005	0.50	6.59	43.7	30	0.80	0.26	3.47	1.07	36.9	47.9	307
RDD284837		2.69		0.002	0.007	0.25	4.94	14.2	20	1.19	0.16	6.58	0.34	37.0	23.7	186
RDD284838		3.43		0.001	0.006	0.62	3.25	18.2	170	0.59	0.21	20.6	2.84	25.1	33.2	112
RDD284839		2.38	89.0	0.002	<0.005	0.37	4.59	6.9	50	0.66	0.10	12.80	0.95	29.8	34.3	150
RDD284840		<0.02			1.125											
RDD284841		0.07		1.695		0.15	7.84	361	700	2.48	0.32	0.93	0.04	84.6	18.4	129
RDD284842		4.38		0.004	<0.005	0.36	6.37	12.4	30	0.74	0.04	5.99	0.28	38.4	38.1	203
RDD284843		3.43		0.001	<0.005	0.15	5.05	<0.2	10	0.57	0.02	7.41	0.12	38.2	16.4	150
RDD284844		2.82		0.001	0.005	0.08	4.53	6.3	70	0.68	0.02	12.50	0.03	33.5	30.3	121
RDD284845		3.55		0.001	<0.005	0.08	5.51	2.5	60	0.81	0.03	9.86	0.04	34.8	36.9	158
RDD284846		2.95		<0.001	<0.005	0.04	4.22	12.6	100	0.80	0.08	14.55	0.48	32.8	25.4	80
RDD284847		4.65		0.001	<0.005	0.53	3.89	24.5	30	3.17	0.27	8.99	8.96	32.6	21.0	88
RDD284848		1.76		<0.001	<0.005	0.01	0.05	0.7	<10	<0.05	0.01	0.08	<0.02	1.51	0.4	9
RDD284849		3.07		0.001	<0.005	1.08	5.05	37.4	110	1.42	0.58	12.00	4.23	41.5	33.0	109
RDD284850		3.13		<0.001	<0.005	0.07	6.82	11.2	120	4.95	0.05	1.92	0.04	46.8	47.0	170
RDD284851		1.42		0.001	<0.005	0.04	6.82	<0.2	170	2.97	0.02	5.25	0.05	43.9	40.9	126
RDD284852		4.69		0.001	<0.005	0.04	6.65	0.7	310	1.01	0.02	6.00	0.08	25.7	41.2	96
RDD284853		4.99		<0.001	<0.005	0.06	6.99	0.9	350	0.73	0.03	5.20	0.14	27.7	43.7	110
RDD284854		4.13		0.001	<0.005	0.09	7.03	<0.2	500	0.75	0.03	5.77	0.12	27.2	50.9	103
RDD284855		3.89		<0.001	<0.005	0.06	6.81	3.1	380	2.13	0.03	6.02	0.12	27.2	45.4	98
RDD284856		2.79		0.001	<0.005	0.03	7.11	<0.2	290	0.79	0.02	5.89	0.11	27.1	44.7	109
RDD284857		5.30		0.001	0.005	0.05	6.83	2.3	210	1.31	0.03	6.53	0.18	25.1	45.3	113
RDD284858		3.92		0.001	0.005	0.07	7.05	1.5	420	0.94	0.03	5.67	0.32	28.1	49.5	112
RDD284859		3.83		<0.001	<0.005	0.07	6.76	1.0	340	0.81	0.01	6.07	0.10	25.3	47.1	110
RDD284860		3.93		<0.001	<0.005	0.13	6.65	0.6	450	0.72	0.07	6.24	0.23	24.8	51.0	104
RDD284861		3.66		0.001	0.006	0.06	6.65	1.6	360	0.61	0.01	5.49	0.11	24.6	46.7	105
RDD284862		4.19		0.001	<0.005	0.07	6.80	1.2	360	0.67	0.01	5.79	0.10	26.2	47.2	109
RDD284863		4.09		0.001	<0.005	0.07	6.76	1.8	270	0.91	0.01	6.17	0.10	25.8	49.1	109
RDD284864		3.89		0.001	<0.005	0.07	6.29	3.3	360	1.35	0.02	7.22	0.12	27.3	40.8	99
RDD284865		<0.02			2.65											
RDD284866		0.07		0.336		0.14	6.81	19.2	80	0.31	0.01	7.27	0.23	10.05	43.6	97
RDD284867		4.15		0.001	0.007	0.07	6.38	3.8	410	1.24	0.02	7.04	0.12	51.6	41.0	126
RDD284868		5.16		0.001	<0.005	0.41	5.91	15.3	60	4.69	0.07	5.09	4.69	52.1	28.5	84
RDD284869		2.84		0.001	0.008	0.30	1.93	20.0	20	7.89	0.02	6.40	4.61	13.80	7.3	38
RDD284870		4.62		0.001	0.007	0.35	6.07	35.3	90	5.06	0.07	5.09	1.81	46.6	36.4	104



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Page: 3 - B

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Cs	Cu	Fe	Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb
		ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm
		0.05	0.2	0.01	0.05	0.05	0.1	0.005	0.01	0.5	0.2	0.01	5	0.05	0.01	0.1
RDD284831		9.40	92.5	10.10	19.05	0.18	3.3	0.200	0.72	20.3	61.7	3.58	11650	0.57	0.29	16.7
RDD284832		5.17	83.3	9.93	20.6	0.21	3.3	0.159	0.42	16.5	49.8	4.12	5650	0.23	1.13	17.8
RDD284833		3.09	78.3	9.54	21.9	0.21	2.9	0.181	0.23	15.6	55.2	4.64	2530	0.23	1.53	19.0
RDD284834		4.25	76.2	9.15	19.70	0.21	2.8	0.157	0.36	15.3	67.4	4.43	2030	0.26	0.90	18.4
RDD284835		6.97	87.7	8.30	18.00	0.14	2.8	0.150	0.48	15.9	69.4	4.14	2220	0.34	0.05	17.5
RDD284836		8.50	130.5	9.98	19.40	0.17	2.3	1.055	0.15	14.8	65.3	5.74	3370	0.34	1.03	17.3
RDD284837		4.61	140.5	14.40	15.20	0.20	1.8	2.83	0.04	14.7	47.4	3.43	8430	0.27	0.02	13.6
RDD284838		6.11	97.1	5.08	9.43	0.08	2.0	1.195	0.49	10.4	27.8	1.64	3600	0.24	0.85	8.8
RDD284839		6.21	121.0	7.35	13.85	0.09	2.0	0.408	0.28	11.6	36.1	3.22	3000	0.26	1.13	12.6
RDD284840																
RDD284841		9.45	29.7	4.28	20.2	0.22	4.0	0.061	2.86	42.9	57.8	1.84	412	1.04	0.78	15.7
RDD284842		3.59	157.5	9.96	18.95	0.18	2.0	0.313	0.08	15.3	47.7	4.24	2210	0.32	1.40	18.1
RDD284843		3.11	76.7	9.66	15.95	0.14	2.0	0.277	0.04	14.8	37.8	4.26	2810	0.40	0.75	14.2
RDD284844		1.59	76.2	7.08	14.90	0.11	2.7	0.093	0.12	13.9	33.6	3.63	1005	0.56	0.65	12.9
RDD284845		1.73	88.2	7.66	16.55	0.16	3.0	0.075	0.10	14.4	35.1	3.83	882	0.38	1.37	14.7
RDD284846		3.02	35.5	7.31	13.50	0.08	2.8	0.556	0.22	13.8	33.1	2.59	4150	0.38	0.51	13.5
RDD284847		7.84	32.2	14.05	12.80	0.13	2.1	4.57	0.20	13.6	41.3	3.64	24600	1.23	0.02	11.9
RDD284848		0.07	3.2	0.68	0.27	<0.05	0.4	<0.005	0.01	0.8	1.4	0.02	103	0.55	0.01	1.1
RDD284849		6.08	69.5	9.23	17.00	0.14	3.4	1.350	0.25	17.3	42.5	3.66	9170	0.66	0.38	16.8
RDD284850		28.4	99.7	11.95	21.4	0.19	4.4	0.096	1.17	20.2	73.8	3.65	13050	0.92	0.11	22.6
RDD284851		21.0	14.1	10.95	21.3	0.17	4.0	0.119	0.54	19.2	56.0	4.00	2020	0.40	1.28	20.2
RDD284852		16.50	63.0	8.67	16.95	0.15	2.4	0.089	0.61	10.4	24.7	3.78	1520	0.57	2.61	10.0
RDD284853		12.35	82.6	9.20	18.20	0.17	2.4	0.091	0.60	11.2	26.2	3.88	1525	0.47	2.70	10.6
RDD284854		13.60	107.5	9.23	18.40	0.17	2.4	0.093	0.77	10.9	21.0	3.84	1515	0.42	2.59	10.0
RDD284855		35.5	104.0	9.00	17.50	0.14	2.3	0.104	0.70	10.7	81.6	4.26	1890	0.56	1.85	9.7
RDD284856		16.30	64.5	9.03	18.05	0.25	2.2	0.093	0.62	11.2	24.9	3.94	1550	0.43	2.55	10.4
RDD284857		23.5	75.7	9.16	17.65	0.16	2.4	0.087	0.61	9.8	42.3	3.80	2370	0.39	2.22	9.8
RDD284858		13.95	96.8	9.46	18.50	0.16	2.3	0.095	0.72	11.6	41.2	3.88	1860	0.40	2.38	10.3
RDD284859		13.60	94.3	8.96	18.35	0.21	2.6	0.083	0.69	11.0	31.2	3.86	1705	0.33	2.39	10.3
RDD284860		7.88	181.0	9.22	18.45	0.21	2.3	0.092	0.56	10.1	25.8	3.70	1735	0.31	2.62	10.0
RDD284861		8.98	101.0	9.07	18.65	0.19	2.2	0.090	0.55	11.1	29.3	3.83	1650	0.31	2.49	10.4
RDD284862		13.10	100.0	8.96	18.90	0.18	2.7	0.109	0.71	11.6	30.0	3.83	1595	0.28	2.40	10.6
RDD284863		14.75	99.5	8.87	18.65	0.20	2.6	0.129	0.68	11.4	32.9	3.69	1565	0.33	2.44	10.6
RDD284864		8.42	89.9	8.26	16.85	0.19	2.5	0.118	0.64	12.2	25.4	3.51	1540	0.80	2.39	11.0
RDD284865																
RDD284866		0.35	166.5	7.59	15.65	0.14	1.5	0.066	0.24	3.8	11.0	3.78	1290	0.67	1.57	3.3
RDD284867		9.58	67.8	11.50	21.1	0.22	4.5	0.132	0.62	23.5	45.7	4.30	1635	2.15	1.03	26.7
RDD284868		25.0	63.1	9.86	18.90	0.20	4.1	0.338	1.28	24.3	48.4	2.47	14400	0.30	0.34	20.3
RDD284869		6.43	5.2	19.35	8.62	0.19	1.3	0.462	0.78	5.9	6.6	2.71	81800	0.22	0.02	6.7
RDD284870		32.8	80.8	8.94	20.1	0.20	4.0	0.131	1.85	22.3	28.1	2.10	12600	0.42	0.35	23.8





Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD  
PO BOX 20  
ZEEHAN TAS 7469

Project: EDGI\_18

Page: 3 - C  
Total # Pages: 9 (A - E)  
Plus Appendix Pages  
Finalized Date: 5-MAR-2025  
Account: BLUMINJV

**CERTIFICATE OF ANALYSIS AD25025626**

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ni	P	Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th
		ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.2	10	0.5	0.1	0.002	0.01	0.05	0.1	1	0.2	0.2	0.05	0.05	0.01
RDD284831		104.5	1070	253	121.0	0.002	0.08	21.7	28.8	1	4.5	124.5	1.08	<0.05	2.63
RDD284832		126.5	1150	6.4	38.1	<0.002	0.03	6.20	33.1	1	4.5	105.0	1.14	<0.05	2.43
RDD284833		120.5	1140	4.3	13.1	<0.002	0.02	3.91	37.7	1	3.7	103.5	1.18	<0.05	2.05
RDD284834		115.5	1060	5.3	34.4	<0.002	0.12	35.4	31.2	1	3.6	154.5	1.15	<0.05	2.11
RDD284835		77.6	930	9.3	69.0	<0.002	0.04	60.2	25.7	<1	1.6	209	1.10	<0.05	2.31
RDD284836		172.0	1040	179.5	12.8	<0.002	0.11	4.36	32.6	<1	4.1	106.5	1.09	<0.05	1.44
RDD284837		95.4	790	13.0	3.9	0.002	1.69	19.40	26.1	<1	9.0	122.0	0.90	<0.05	1.34
RDD284838		87.6	710	481	40.6	0.002	0.77	5.15	14.3	1	2.5	417	0.56	<0.05	1.56
RDD284839		92.9	770	116.0	21.6	<0.002	0.48	2.02	21.6	<1	2.4	304	0.81	<0.05	1.32
RDD284840															
RDD284841		68.9	770	19.4	174.0	<0.002	0.15	343	15.0	1	3.8	152.0	1.14	<0.05	16.05
RDD284842		129.5	1020	24.8	5.1	0.002	0.15	1.21	31.7	1	2.1	183.5	1.11	<0.05	1.58
RDD284843		88.1	770	6.4	2.9	0.002	0.13	2.51	25.6	<1	1.3	202	0.90	<0.05	1.41
RDD284844		73.1	770	5.5	4.1	0.002	0.21	0.60	21.8	<1	1.2	314	0.84	<0.05	1.78
RDD284845		89.1	910	5.9	4.5	0.002	0.48	0.86	26.3	<1	1.5	264	0.93	<0.05	1.69
RDD284846		45.7	750	6.3	19.6	<0.002	0.20	2.19	19.1	<1	7.2	198.0	0.83	<0.05	2.06
RDD284847		48.1	670	416	31.0	<0.002	0.37	18.90	17.7	1	23.8	81.1	0.76	<0.05	1.92
RDD284848		1.3	10	1.3	0.5	<0.002	<0.01	0.23	0.2	<1	0.2	3.1	0.07	<0.05	0.28
RDD284849		67.5	830	656	31.6	<0.002	0.16	11.90	22.8	<1	19.9	146.0	1.08	<0.05	3.01
RDD284850		104.0	1250	8.8	168.0	0.003	0.13	23.8	33.5	<1	3.0	42.3	1.45	<0.05	3.13
RDD284851		84.7	1070	12.0	62.3	<0.002	0.05	2.53	27.1	<1	2.9	151.5	1.32	<0.05	3.10
RDD284852		55.5	870	5.5	34.3	<0.002	0.12	0.81	45.1	<1	1.1	337	0.63	<0.05	1.39
RDD284853		60.7	900	7.4	42.0	0.002	0.11	0.78	47.7	1	1.3	241	0.66	<0.05	1.43
RDD284854		63.2	860	5.1	59.4	0.002	0.24	0.97	47.5	1	1.2	300	0.62	<0.05	1.38
RDD284855		61.9	850	7.8	78.4	0.003	0.16	4.23	46.7	1	1.3	248	0.61	<0.05	1.25
RDD284856		63.6	920	4.4	54.6	0.002	0.15	1.63	48.9	1	1.1	336	0.65	<0.05	1.30
RDD284857		63.9	890	12.8	69.1	0.002	0.16	3.04	47.1	1	1.6	288	0.61	<0.05	1.21
RDD284858		69.4	920	10.2	52.6	0.002	0.11	1.69	48.9	<1	1.3	414	0.64	<0.05	1.19
RDD284859		62.3	890	4.9	47.0	0.003	0.15	0.82	47.3	1	1.1	291	0.62	<0.05	1.21
RDD284860		63.4	880	72.7	29.7	0.003	0.25	0.77	45.4	1	1.0	319	0.64	<0.05	1.14
RDD284861		60.8	860	6.2	39.8	0.002	0.16	1.01	48.3	1	1.1	335	0.63	<0.05	1.15
RDD284862		61.3	910	5.4	50.9	0.003	0.29	1.42	48.7	1	1.2	309	0.67	<0.05	1.22
RDD284863		62.4	900	3.9	53.8	0.002	0.30	1.29	48.4	1	1.2	235	0.66	<0.05	1.20
RDD284864		57.3	890	6.0	31.8	0.002	0.19	0.90	43.1	1	1.3	237	0.68	<0.05	1.35
RDD284865															
RDD284866		85.1	390	8.1	5.9	0.003	0.18	0.51	43.7	1	0.7	226	0.21	<0.05	0.45
RDD284867		89.4	1220	3.6	25.1	0.002	0.06	0.76	34.6	1	2.3	261	1.58	<0.05	3.18
RDD284868		55.7	960	515	207	<0.002	0.15	18.80	24.9	1	7.4	59.4	1.28	<0.05	4.62
RDD284869		11.9	480	165.5	103.5	<0.002	0.11	3.71	7.9	<1	18.9	32.7	0.42	<0.05	0.87
RDD284870		66.7	1090	371	284	<0.002	0.30	45.4	29.6	1	6.7	55.3	1.42	<0.05	3.29



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD  
PO BOX 20  
ZEEHAN TAS 7469

Page: 3 - D  
Total # Pages: 9 (A - E)  
Plus Appendix Pages  
Finalized Date: 5-MAR-2025  
Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ti	U	V	W	Y	Zn	Zr	Dy	Er	Eu	Gd	Ho	Lu	Nd
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.02	0.1	1	0.1	0.1	2	0.5	0.05	0.03	0.03	0.05	0.01	0.01	0.1
RDD284831		1.26	1.4	239	1.0	27.2	1550	124.5	5.00	2.53	1.59	5.31	0.99	0.28	25.0
RDD284832		0.50	1.3	235	0.7	26.8	694	130.5	5.11	2.49	1.97	5.47	0.99	0.28	26.4
RDD284833		0.22	0.9	296	0.3	22.6	583	116.0	4.49	2.21	1.69	5.12	0.88	0.25	24.8
RDD284834		0.48	0.8	278	2.6	20.9	312	111.5	4.15	2.02	1.22	4.77	0.82	0.23	23.4
RDD284835		0.83	0.7	259	1.2	21.3	217	110.0	3.95	2.14	0.89	4.40	0.81	0.26	22.3
RDD284836		0.25	0.4	305	0.2	16.0	369	86.3	3.41	1.65	1.18	4.08	0.67	0.19	21.9
RDD284837		0.22	0.4	225	3.5	20.0	254	73.2	4.13	1.90	1.60	4.72	0.80	0.19	22.6
RDD284838		0.54	1.2	127	0.2	14.8	484	75.1	2.68	1.49	0.93	2.88	0.57	0.18	14.5
RDD284839		0.30	0.5	207	0.3	16.2	312	72.9	3.23	1.58	1.23	3.71	0.63	0.17	18.3
RDD284840															
RDD284841		0.87	2.6	111	2.5	18.1	99	141.5	3.43	1.87	1.19	4.41	0.70	0.31	38.6
RDD284842		0.18	0.4	293	0.3	17.9	220	78.6	3.88	1.79	1.18	4.50	0.72	0.21	23.8
RDD284843		0.07	0.5	227	0.2	16.7	177	81.0	3.35	1.61	1.21	4.20	0.64	0.19	23.9
RDD284844		0.14	0.7	217	0.3	19.8	109	102.5	3.68	1.95	1.22	3.94	0.75	0.23	19.5
RDD284845		0.12	0.8	255	0.3	21.8	120	111.0	4.16	2.14	1.33	4.31	0.87	0.25	21.4
RDD284846		0.28	1.2	195	0.7	19.3	209	108.0	3.64	1.97	1.24	3.81	0.77	0.24	18.9
RDD284847		0.34	0.8	173	4.3	20.0	2670	77.5	3.73	1.87	1.93	4.05	0.75	0.21	18.6
RDD284848		0.03	0.1	3	0.2	0.9	3	14.3	0.14	0.11	<0.03	0.10	0.03	0.02	0.6
RDD284849		0.36	1.2	218	1.1	24.5	1180	128.0	4.48	2.33	1.96	4.55	0.92	0.30	23.0
RDD284850		2.03	1.0	322	1.4	33.1	202	159.0	6.03	3.24	1.62	5.99	1.25	0.38	27.6
RDD284851		0.74	1.0	248	0.3	28.7	110	142.0	5.23	2.79	1.87	5.52	1.07	0.33	25.4
RDD284852		0.48	0.3	305	0.3	32.6	77	73.1	5.54	3.19	1.29	4.97	1.22	0.43	16.5
RDD284853		0.68	0.4	318	0.3	33.4	115	78.1	5.47	3.25	1.39	5.02	1.20	0.41	17.4
RDD284854		0.92	0.3	316	0.3	33.2	98	77.2	5.61	3.32	1.49	4.99	1.23	0.42	17.1
RDD284855		1.09	0.3	305	1.2	32.0	98	85.7	5.52	3.18	1.46	4.95	1.18	0.40	16.9
RDD284856		0.74	0.3	330	0.3	33.5	95	74.1	5.70	3.44	1.54	5.21	1.25	0.42	17.7
RDD284857		0.79	0.3	318	0.3	32.3	137	76.4	5.37	3.18	1.39	4.85	1.18	0.42	16.0
RDD284858		0.82	0.3	329	0.3	33.8	179	71.3	5.77	3.29	1.74	5.19	1.22	0.40	18.0
RDD284859		0.70	0.3	323	0.3	31.0	103	71.0	5.62	3.23	1.55	5.25	1.19	0.43	15.0
RDD284860		0.50	0.3	313	0.2	29.8	136	62.0	5.39	3.13	1.36	5.13	1.14	0.42	14.6
RDD284861		0.67	0.3	315	0.2	30.7	101	56.0	5.49	3.18	1.44	5.11	1.17	0.43	15.2
RDD284862		0.84	0.3	326	0.2	32.1	95	60.0	5.69	3.33	1.50	5.16	1.21	0.44	15.8
RDD284863		0.83	0.3	324	0.3	32.5	95	61.0	5.73	3.31	1.60	5.23	1.21	0.46	15.7
RDD284864		0.45	0.3	292	0.3	29.5	90	82.2	5.23	3.02	1.33	5.10	1.10	0.40	15.9
RDD284865															
RDD284866		0.09	0.1	272	7.6	20.3	98	52.5	3.45	2.18	0.82	2.96	0.76	0.31	7.3
RDD284867		0.36	1.1	283	0.4	31.8	160	167.5	6.14	3.08	2.29	6.73	1.23	0.34	28.3
RDD284868		2.31	1.1	178	1.4	26.9	1665	112.0	5.38	2.75	1.68	5.91	1.11	0.36	27.3
RDD284869		1.00	0.3	76	2.4	9.5	1595	49.2	1.74	0.85	1.26	2.04	0.34	0.11	7.4
RDD284870		3.28	0.8	247	1.3	24.6	865	115.0	4.82	2.54	1.63	5.79	0.96	0.32	25.6



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 3 - E

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Sm	Tb	Tm	Yb
		ppm	ppm	ppm	ppm
		0.03	0.01	0.01	0.03
RDD284831		5.56	0.78	0.33	1.94
RDD284832		6.02	0.83	0.31	1.95
RDD284833		5.70	0.75	0.28	1.78
RDD284834		5.20	0.73	0.25	1.67
RDD284835		5.01	0.66	0.26	1.76
RDD284836		4.79	0.58	0.21	1.36
RDD284837		5.29	0.71	0.22	1.37
RDD284838		3.38	0.45	0.18	1.15
RDD284839		4.25	0.56	0.19	1.21
RDD284840					
RDD284841		6.96	0.61	0.26	1.82
RDD284842		5.27	0.66	0.21	1.39
RDD284843		5.40	0.59	0.19	1.31
RDD284844		4.41	0.57	0.25	1.53
RDD284845		4.91	0.66	0.27	1.71
RDD284846		4.17	0.58	0.25	1.64
RDD284847		4.29	0.60	0.23	1.51
RDD284848		0.12	0.02	0.02	0.12
RDD284849		5.34	0.71	0.32	2.07
RDD284850		6.44	0.94	0.42	2.61
RDD284851		5.79	0.84	0.37	2.26
RDD284852		4.35	0.82	0.42	2.79
RDD284853		4.48	0.85	0.44	2.71
RDD284854		4.43	0.82	0.43	2.83
RDD284855		4.46	0.79	0.42	2.65
RDD284856		4.64	0.84	0.43	2.84
RDD284857		4.19	0.79	0.42	2.79
RDD284858		4.72	0.87	0.42	2.89
RDD284859		4.19	0.86	0.46	3.01
RDD284860		4.09	0.84	0.46	2.83
RDD284861		4.27	0.83	0.45	2.77
RDD284862		4.56	0.88	0.49	2.98
RDD284863		4.43	0.88	0.49	3.00
RDD284864		4.34	0.84	0.43	2.67
RDD284865					
RDD284866		2.30	0.52	0.32	2.05
RDD284867		6.92	1.03	0.43	2.74
RDD284868		6.11	0.92	0.39	2.35
RDD284869		1.92	0.31	0.12	0.69
RDD284870		5.88	0.83	0.37	2.19



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD  
PO BOX 20  
ZEEHAN TAS 7469

Project: EDGI\_18

Page: 4 - A  
Total # Pages: 9 (A - E)  
Plus Appendix Pages  
Finalized Date: 5-MAR-2025  
Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg 0.02	PUL-QC Pass75um % 0.01	Au-ICP21 Au ppm 0.001	ME-XRF15b Sn % 0.005	ME-MS61r Ag ppm 0.01	ME-MS61r Al % 0.01	ME-MS61r As ppm 0.2	ME-MS61r Ba ppm 10	ME-MS61r Be ppm 0.05	ME-MS61r Bi ppm 0.01	ME-MS61r Ca % 0.01	ME-MS61r Cd ppm 0.02	ME-MS61r Ce ppm 0.01	ME-MS61r Co ppm 0.1	ME-MS61r Cr ppm 1
RDD284871		4.07		0.001	<0.005	0.43	5.26	30.3	80	8.20	0.06	8.18	4.98	44.8	34.4	75
RDD284872		3.94		0.001	<0.005	0.30	5.19	25.8	60	12.95	0.06	9.03	1.78	46.8	35.8	71
RDD284873		3.79		0.002	<0.005	0.46	6.66	23.1	180	2.86	0.21	3.63	3.16	67.9	43.2	117
RDD284874		2.85		0.001	<0.005	0.45	4.51	26.6	60	5.65	0.08	6.48	5.47	52.3	23.0	69
RDD284875		4.27		0.001	<0.005	0.34	6.33	23.9	150	2.68	0.90	4.38	0.93	33.1	37.0	68
RDD284876		2.15		0.038	0.009	0.56	0.56	>10000	10	1.83	8.37	13.00	4.35	5.05	92.2	3
RDD284877		1.68		0.001	<0.005	0.01	0.04	2.3	10	<0.05	0.02	0.02	<0.02	1.38	0.4	7
RDD284878		1.94		<0.001	0.005	0.35	6.76	56.9	190	3.25	0.47	2.47	4.69	51.4	40.0	87
RDD284879		3.80		0.001	<0.005	0.28	6.65	43.2	240	1.62	0.45	6.27	0.42	57.0	48.1	83
RDD284880		5.00		0.001	<0.005	0.20	6.63	13.0	70	0.99	0.09	4.72	0.10	50.4	50.0	251
RDD284881		2.33		0.001	0.005	0.13	5.67	21.1	180	2.62	0.26	7.52	0.15	58.7	30.4	108
RDD284882		4.29		0.001	0.009	0.20	7.00	15.8	270	3.10	0.40	4.01	0.06	78.3	13.2	52
RDD284883		3.87		0.003	0.007	0.16	6.99	20.0	270	2.61	0.41	2.14	0.06	83.1	13.9	52
RDD284884		2.51		0.001	0.012	0.10	7.44	11.8	290	3.28	0.40	1.16	0.06	101.0	7.3	50
RDD284885		0.90	99.0	0.003	0.009	0.93	2.93	88.8	110	1.97	1.17	6.44	13.75	45.4	10.4	29
RDD284886		1.53		<0.001	<0.005	0.01	0.06	1.6	10	<0.05	0.04	0.02	<0.02	1.79	0.3	6
RDD284887		4.78		0.004	0.011	0.41	7.92	21.0	320	4.11	1.09	0.70	1.48	117.5	6.7	97
RDD284888		5.02		<0.001	0.009	0.37	7.42	12.8	310	3.89	0.33	2.09	2.55	115.0	9.9	48
RDD284889		3.56		0.001	0.008	0.22	5.99	23.9	300	3.13	0.35	5.32	2.67	72.8	11.6	36
RDD284890		<0.02			2.63											
RDD284891		0.07		1.655		0.14	7.53	351	690	2.47	0.32	0.90	0.04	82.5	18.6	125
RDD284892		3.67		0.003	0.005	0.21	7.01	2.9	610	4.24	0.38	6.27	<0.02	132.5	11.2	24
RDD284893		2.61		<0.001	0.007	0.05	5.62	4.7	500	2.09	0.18	4.59	<0.02	67.8	14.2	42
RDD284894		5.00		0.004	0.008	0.05	8.05	653	330	2.08	0.63	1.58	0.13	72.4	40.6	198
RDD284895		2.96		0.004	<0.005	0.06	6.14	38.6	150	0.76	2.15	1.01	0.03	29.9	32.8	83
RDD284896		3.59		0.007	0.009	0.06	4.87	72.7	90	0.22	2.72	1.27	0.06	5.00	43.6	90
RDD284897		2.98		0.005	<0.005	0.07	5.06	73.3	100	0.35	3.35	0.94	0.04	32.6	51.0	75
RDD284898		4.49		0.002	0.007	0.04	8.05	14.2	230	1.36	0.32	1.53	<0.02	47.5	31.4	121
RDD284899		3.43		0.001	0.005	<0.01	8.92	3.1	310	1.97	0.04	0.66	<0.02	71.7	29.8	115
RDD284900		3.25		0.001	0.005	<0.01	8.95	2.0	240	1.74	0.06	0.76	<0.02	53.3	29.7	131
RDD284901		3.55		0.001	0.011	<0.01	7.86	37.8	500	1.13	0.11	2.08	<0.02	58.5	49.1	102
RDD284902		3.58		0.001	0.012	<0.01	7.23	172.0	450	1.41	0.26	2.70	<0.02	74.9	158.5	101
RDD284903		2.78		0.001	<0.005	0.16	8.61	16.2	1190	2.22	0.28	1.64	<0.02	76.4	38.7	142
RDD284904		3.33		0.002	0.016	0.32	6.44	29.2	170	2.99	0.77	2.94	0.30	66.6	72.0	163
RDD284905		3.81		0.005	0.092	0.23	7.44	21.2	730	2.46	0.93	1.72	<0.02	66.3	37.3	153
RDD284906		2.91		0.001	0.025	0.16	7.46	12.6	700	2.19	1.33	2.11	<0.02	73.3	32.1	169
RDD284907		4.96		0.001	0.063	0.12	7.87	9.4	690	3.08	1.23	0.96	0.19	71.4	33.7	160
RDD284908		3.84		<0.001	0.047	0.11	8.03	13.7	880	3.13	0.81	2.09	1.25	62.9	32.5	163
RDD284909		3.31		<0.001	0.010	0.05	9.20	25.1	1420	3.29	0.30	1.52	<0.02	72.0	38.2	152
RDD284910		3.05		0.001	0.010	0.16	7.78	23.3	1120	2.86	0.46	1.92	<0.02	72.6	54.8	140



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD  
PO BOX 20  
ZEEHAN TAS 7469

Page: 4 - B  
Total # Pages: 9 (A - E)  
Plus Appendix Pages  
Finalized Date: 5-MAR-2025  
Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Cs	Cu	Fe	Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na
		ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%
		0.05	0.2	0.01	0.05	0.05	0.1	0.005	0.01	0.5	0.2	0.01	5	0.05	0.01
RDD284871		26.8	77.2	10.05	18.10	0.16	3.6	0.111	1.27	21.0	32.5	2.78	14650	0.41	0.38
RDD284872		31.6	102.0	8.90	16.75	0.16	3.8	0.130	1.61	21.3	31.1	2.68	18550	0.50	0.02
RDD284873		21.7	115.0	9.00	21.7	0.21	5.1	0.100	1.11	32.3	41.2	2.51	7270	0.57	1.51
RDD284874		22.4	52.8	10.90	15.80	0.19	3.4	0.090	1.15	21.9	40.6	2.66	35000	0.31	0.09
RDD284875		13.85	168.0	12.85	18.70	0.15	2.9	1.430	0.56	15.4	50.3	2.42	8260	2.56	1.23
RDD284876		1.69	7.1	16.90	4.07	0.16	0.2	1.315	0.10	2.6	13.2	2.42	68300	0.26	0.01
RDD284877		0.08	2.6	0.78	0.21	<0.05	0.4	<0.005	0.02	0.7	1.6	0.01	161	0.52	0.01
RDD284878		22.0	46.7	13.45	22.0	0.26	2.5	2.26	0.70	22.9	65.6	2.81	6030	0.65	0.63
RDD284879		13.30	102.0	8.79	21.0	0.19	4.9	0.665	0.73	25.6	48.2	2.36	3240	0.86	1.65
RDD284880		11.30	197.0	9.81	21.7	0.18	4.6	0.102	0.57	22.2	74.4	3.43	1705	0.98	1.23
RDD284881		27.9	54.1	5.08	15.75	0.15	3.8	0.225	2.37	28.1	36.0	1.76	3410	0.58	0.10
RDD284882		27.8	32.7	3.53	18.35	0.17	4.2	0.475	3.48	36.5	27.6	1.17	1735	0.41	0.04
RDD284883		30.4	31.3	3.87	18.60	0.19	4.4	0.165	3.60	40.3	24.6	1.34	1530	1.07	0.03
RDD284884		26.8	24.2	3.60	20.9	0.25	6.0	0.284	3.70	48.4	20.6	1.15	1460	0.68	0.03
RDD284885		8.23	123.0	13.50	10.35	0.17	1.9	1.425	1.34	22.1	13.4	1.92	66100	0.57	0.02
RDD284886		0.15	2.2	0.49	0.33	0.06	0.4	<0.005	0.02	0.9	1.6	0.02	71	0.37	0.01
RDD284887		24.9	47.9	3.99	22.2	0.24	6.2	0.635	4.01	58.6	20.6	1.04	1270	2.84	0.04
RDD284888		31.9	33.9	4.02	20.8	0.23	6.2	0.191	3.70	55.9	30.1	1.41	2210	0.90	0.03
RDD284889		36.8	56.5	4.71	16.70	0.20	3.6	0.087	2.79	34.9	52.3	2.12	9460	0.62	0.06
RDD284890															
RDD284891		9.82	30.0	4.10	19.90	0.21	4.1	0.069	2.78	41.3	55.8	1.79	418	0.93	0.75
RDD284892		34.4	91.8	4.08	19.10	0.23	8.8	0.077	3.07	68.2	83.9	2.48	4370	0.87	0.31
RDD284893		21.5	35.7	4.23	16.65	0.21	4.3	0.071	2.25	33.1	58.1	3.13	2090	0.73	0.37
RDD284894		18.30	61.5	8.36	23.9	0.33	4.9	0.154	1.67	34.5	59.8	2.60	4040	1.58	1.58
RDD284895		8.36	31.9	5.78	13.40	0.14	2.5	0.056	0.66	12.8	55.3	2.26	983	2.24	2.09
RDD284896		1.09	66.5	4.02	7.99	0.12	1.6	0.094	0.33	1.9	28.0	1.43	973	0.40	2.83
RDD284897		2.53	54.9	4.38	9.12	0.14	1.8	0.067	0.36	12.6	33.7	1.41	555	8.21	2.59
RDD284898		17.75	20.2	10.10	23.5	0.26	4.0	0.244	1.17	21.0	74.5	4.61	1635	0.17	0.90
RDD284899		16.25	0.7	7.98	25.1	0.21	4.4	0.080	1.54	34.8	75.2	4.37	1075	0.13	1.40
RDD284900		12.20	0.8	8.28	23.5	0.38	3.7	0.067	1.01	23.1	86.9	5.21	1505	0.11	1.48
RDD284901		19.50	4.3	7.95	21.4	0.26	4.3	0.412	1.12	26.6	73.8	4.89	1730	0.13	1.69
RDD284902		30.6	5.0	8.18	20.5	0.29	5.5	0.521	1.38	35.7	63.4	4.75	1815	0.18	1.12
RDD284903		26.5	111.5	8.28	24.6	0.29	5.2	0.301	2.17	36.3	61.0	2.50	1920	0.27	1.41
RDD284904		35.2	456	12.70	19.95	0.32	3.8	1.865	1.80	33.9	80.6	2.07	3930	0.20	0.33
RDD284905		31.1	159.5	9.66	21.7	0.24	4.3	1.065	2.08	33.9	67.4	2.31	2920	0.16	0.48
RDD284906		17.85	108.5	10.65	21.7	0.27	4.8	1.750	2.02	37.3	77.0	2.35	3730	0.23	0.03
RDD284907		24.3	160.5	11.10	22.7	0.33	4.7	1.315	2.25	36.0	92.0	2.26	2790	0.24	0.03
RDD284908		33.8	95.1	9.79	22.1	0.26	4.9	0.864	2.53	32.0	86.8	2.21	2430	0.20	0.21
RDD284909		63.3	63.4	8.36	24.4	0.30	3.5	0.351	3.72	34.5	72.8	1.94	1845	0.19	0.69
RDD284910		52.1	184.5	8.76	20.7	0.26	4.6	0.427	2.75	35.6	73.9	2.02	2460	0.36	0.17



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Page: 4 - C

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ni	P	Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti
		ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.2	10	0.5	0.1	0.002	0.01	0.05	0.1	1	0.2	0.2	0.05	0.05	0.01	0.005
RDD284871		60.0	920	424	228	<0.002	0.48	23.8	26.3	<1	9.8	73.2	1.24	<0.05	2.90	1.170
RDD284872		61.2	1060	66.8	322	<0.002	0.63	47.9	25.1	<1	10.9	63.9	1.25	<0.05	3.13	1.150
RDD284873		80.3	1090	417	168.0	<0.002	0.90	11.00	30.2	<1	5.7	77.7	1.61	0.06	5.06	1.360
RDD284874		41.7	660	338	229	<0.002	0.30	27.5	18.6	<1	9.1	48.2	1.02	<0.05	4.84	0.768
RDD284875		49.7	1050	114.0	71.2	0.003	1.12	8.15	35.8	<1	31.5	111.5	0.86	<0.05	2.56	1.060
RDD284876		13.6	150	76.9	14.2	0.003	0.80	56.4	5.5	<1	25.3	95.1	0.05	0.11	0.15	0.074
RDD284877		1.9	10	1.3	0.7	<0.002	0.01	0.21	0.1	<1	0.2	2.6	0.07	<0.05	0.25	0.049
RDD284878		66.7	1120	349	79.9	0.003	0.29	10.80	34.8	<1	35.2	64.3	1.24	<0.05	3.48	1.205
RDD284879		69.1	1240	73.0	87.1	<0.002	0.28	7.99	29.6	1	15.1	122.0	1.59	<0.05	4.43	1.390
RDD284880		166.0	1200	25.0	71.2	0.002	1.90	3.95	32.1	1	2.0	71.3	1.65	<0.05	3.65	1.455
RDD284881		81.1	550	27.6	221	0.002	1.10	4.26	15.0	1	3.1	83.5	0.79	<0.05	7.92	0.503
RDD284882		17.4	440	28.9	239	0.003	1.28	4.53	14.0	1	6.4	46.3	0.84	<0.05	12.50	0.386
RDD284883		24.8	450	24.5	256	0.005	1.60	6.08	13.8	1	3.5	35.4	0.92	0.09	12.85	0.330
RDD284884		19.5	550	15.8	339	0.003	1.04	3.86	15.0	1	6.4	23.1	2.26	0.05	14.15	0.384
RDD284885		20.5	400	543	98.9	0.004	1.84	4.82	5.6	3	16.6	67.7	0.68	<0.05	5.22	0.124
RDD284886		1.0	10	1.4	1.5	0.011	<0.01	0.24	0.2	<1	0.3	3.2	0.07	<0.05	0.29	0.054
RDD284887		27.0	770	129.0	274	0.014	1.94	10.45	14.8	5	15.0	27.9	2.42	0.06	16.35	0.339
RDD284888		15.4	1320	289	363	0.003	0.70	5.55	12.6	1	6.6	42.4	2.97	0.05	15.70	0.344
RDD284889		20.9	450	209	300	0.003	0.46	11.10	11.8	2	9.0	60.6	0.82	0.09	10.95	0.281
RDD284890																
RDD284891		65.9	760	19.8	160.5	<0.002	0.15	332	16.0	<1	3.6	147.0	1.19	<0.05	15.20	0.491
RDD284892		22.8	440	13.8	209	<0.002	0.35	11.00	7.5	<1	5.1	96.3	7.14	0.06	19.10	0.293
RDD284893		29.7	430	8.2	128.0	<0.002	0.12	1.78	13.2	<1	5.3	116.0	1.13	<0.05	9.73	0.517
RDD284894		116.5	1150	6.5	91.5	<0.002	0.17	6.16	30.8	1	7.0	94.5	1.93	0.15	8.06	1.135
RDD284895		52.2	1240	11.8	50.3	<0.002	0.44	2.77	11.6	1	4.2	41.1	0.68	0.65	5.39	0.447
RDD284896		31.7	680	9.8	16.4	<0.002	0.98	2.24	9.2	2	6.9	34.9	0.32	<0.05	2.76	0.324
RDD284897		62.7	910	12.2	24.2	0.002	0.72	2.52	8.5	1	9.1	37.0	0.42	0.19	4.64	0.315
RDD284898		90.2	800	4.5	71.9	<0.002	0.37	4.72	26.2	1	13.9	52.7	1.10	0.12	9.95	0.835
RDD284899		84.4	790	2.8	80.9	0.003	0.01	0.64	26.5	<1	4.3	55.0	1.31	<0.05	12.75	0.718
RDD284900		93.8	780	1.6	32.5	<0.002	0.01	0.59	25.6	<1	3.4	73.6	1.36	0.05	7.97	0.776
RDD284901		79.0	590	3.8	76.5	<0.002	0.02	1.16	30.2	<1	59.7	85.3	1.16	0.05	7.81	0.735
RDD284902		73.8	1290	2.4	98.6	<0.002	0.13	2.41	27.9	1	56.0	105.0	1.65	0.23	7.69	0.675
RDD284903		96.4	930	7.4	162.0	<0.002	0.32	6.30	30.3	1	11.3	125.5	1.76	0.21	10.70	0.977
RDD284904		104.0	850	39.4	222	<0.002	2.68	14.35	23.8	1	79.3	73.2	1.53	0.15	6.86	0.944
RDD284905		93.3	920	17.6	235	<0.002	0.96	15.65	27.3	2	40.0	54.4	1.55	0.17	7.92	0.865
RDD284906		106.5	1120	13.2	137.5	<0.002	0.23	7.83	27.0	1	64.4	37.1	1.70	0.13	8.59	1.065
RDD284907		107.0	930	6.4	160.5	<0.002	0.92	23.6	28.2	1	94.3	25.2	1.61	0.24	8.46	0.906
RDD284908		96.7	950	8.4	203	<0.002	0.54	27.8	27.4	1	96.0	38.4	1.61	0.26	8.68	0.854
RDD284909		82.4	960	5.0	288	<0.002	0.33	12.10	30.8	1	27.2	58.4	1.64	0.11	8.19	0.868
RDD284910		111.5	770	10.0	231	<0.002	1.24	10.35	27.8	1	40.1	101.5	1.57	0.18	10.85	0.895



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 4 - D

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ti	U	V	W	Y	Zn	Zr	Dy	Er	Eu	Gd	Ho	Lu	Nd
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.02	0.1	1	0.1	0.1	2	0.5	0.05	0.03	0.03	0.05	0.01	0.01	0.1
RDD284871		2.37	0.7	207	1.2	24.9	1900	96.0	4.99	2.51	1.99	5.37	0.96	0.29	24.2
RDD284872		3.98	0.8	199	1.0	25.8	1145	105.0	5.06	2.55	1.72	5.61	0.99	0.33	25.3
RDD284873		1.71	1.2	231	0.8	32.1	1330	144.0	6.25	3.35	1.92	6.99	1.32	0.44	32.9
RDD284874		2.25	1.0	135	1.4	21.9	2180	103.0	4.29	2.25	1.62	4.80	0.86	0.31	23.5
RDD284875		0.93	0.5	282	30.0	27.7	472	58.0	5.35	2.97	1.67	5.17	1.13	0.38	17.8
RDD284876		0.25	<0.1	22	5.2	6.2	1555	7.8	1.07	0.46	0.97	1.24	0.20	0.05	3.0
RDD284877		0.11	0.2	2	0.2	0.9	3	13.5	0.17	0.11	<0.03	0.12	0.03	0.02	0.5
RDD284878		1.13	0.7	280	9.3	31.9	1610	58.0	5.65	2.87	1.67	6.25	1.13	0.33	26.3
RDD284879		1.04	1.1	234	1.2	30.5	293	99.0	6.37	3.20	2.09	6.77	1.27	0.41	29.3
RDD284880		1.08	0.8	271	0.7	27.8	90	105.0	5.85	2.95	1.56	6.39	1.16	0.39	26.8
RDD284881		1.85	1.6	99	1.3	25.0	112	125.0	4.47	2.61	1.34	4.81	0.93	0.38	26.3
RDD284882		1.93	2.4	83	1.9	27.8	31	145.0	5.08	3.18	1.26	5.42	1.08	0.49	32.7
RDD284883		2.17	2.8	76	2.3	29.0	38	149.5	5.17	3.11	1.12	5.47	1.08	0.48	35.1
RDD284884		2.43	2.7	84	2.1	33.0	48	216	5.85	3.53	1.13	5.87	1.28	0.56	42.5
RDD284885		0.65	1.1	32	1.4	18.2	4460	70.8	3.16	1.65	1.24	3.47	0.63	0.24	19.4
RDD284886		0.03	0.2	3	0.2	1.0	3	15.9	0.16	0.11	0.03	0.12	0.04	0.02	0.7
RDD284887		1.87	3.7	118	2.5	35.5	431	223	6.35	3.85	1.44	6.76	1.36	0.62	51.7
RDD284888		3.13	2.7	82	1.8	35.1	995	226	6.44	3.57	1.43	7.75	1.34	0.54	48.9
RDD284889		2.56	2.3	62	2.4	26.3	1135	129.5	4.53	2.70	1.00	4.79	0.95	0.43	30.6
RDD284890															
RDD284891		0.81	2.5	108	2.4	20.8	98	142.5	3.59	1.80	1.22	4.76	0.67	0.31	36.9
RDD284892		1.81	3.6	51	1.2	37.1	39	344	6.76	3.84	1.44	7.25	1.39	0.54	50.3
RDD284893		1.09	2.2	93	2.1	27.9	64	157.0	4.89	2.90	1.01	4.89	1.05	0.46	27.7
RDD284894		0.73	1.5	209	2.3	32.9	110	130.0	6.12	3.32	1.53	6.68	1.23	0.46	33.5
RDD284895		0.48	1.3	100	1.0	14.8	59	89.7	2.66	1.49	0.70	2.98	0.54	0.24	13.0
RDD284896		0.37	1.1	67	0.6	8.4	42	55.6	1.66	0.90	0.30	1.49	0.34	0.13	2.9
RDD284897		0.37	1.5	88	0.7	12.0	47	71.7	2.29	1.28	0.63	2.54	0.45	0.20	12.9
RDD284898		0.70	1.5	213	1.7	22.2	96	133.5	4.17	2.40	1.02	4.21	0.85	0.35	21.3
RDD284899		0.57	1.4	186	2.0	24.9	97	125.0	4.73	2.80	1.31	5.07	0.98	0.42	30.0
RDD284900		0.45	1.2	171	1.7	20.0	97	132.5	4.02	2.40	1.12	4.37	0.82	0.36	23.6
RDD284901		0.79	1.2	183	2.1	27.0	86	111.0	4.88	2.83	1.50	4.90	0.99	0.40	25.3
RDD284902		0.98	1.5	147	1.8	37.2	83	129.0	6.70	3.82	2.36	7.10	1.37	0.53	34.8
RDD284903		1.60	1.8	194	2.2	35.8	85	134.0	6.81	3.83	1.80	6.90	1.36	0.52	33.5
RDD284904		2.45	1.4	161	9.0	28.9	272	84.0	5.49	2.81	2.14	6.16	1.07	0.38	30.4
RDD284905		2.40	1.5	178	9.8	30.5	122	110.0	5.71	3.16	2.10	5.94	1.13	0.41	29.1
RDD284906		1.06	1.6	188	12.4	29.2	92	105.0	5.77	3.06	2.31	6.36	1.17	0.40	33.4
RDD284907		1.62	1.5	180	10.6	29.8	88	102.0	5.78	3.20	2.21	6.02	1.14	0.44	31.1
RDD284908		1.94	1.6	183	7.8	31.1	79	113.0	5.74	3.25	2.18	5.84	1.15	0.46	27.7
RDD284909		3.10	1.4	185	2.2	30.0	62	129.0	5.98	3.24	1.79	6.23	1.16	0.39	32.0
RDD284910		2.47	1.8	175	2.8	31.7	62	111.0	6.27	3.34	1.88	6.42	1.22	0.47	31.3



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 4 – E

Total # Pages: 9 (A – E)

Plus Appendix Pages

Finalized Date: 5–MAR–2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Sm	Tb	Tm	Yb
		ppm	ppm	ppm	ppm
		0.03	0.01	0.01	0.03
RDD284871		5.74	0.83	0.33	2.04
RDD284872		6.02	0.86	0.36	2.25
RDD284873		7.37	1.08	0.51	2.89
RDD284874		5.25	0.73	0.33	2.09
RDD284875		4.50	0.86	0.45	2.73
RDD284876		0.92	0.19	0.06	0.33
RDD284877		0.11	0.02	0.02	0.14
RDD284878		6.31	0.97	0.40	2.46
RDD284879		6.87	1.06	0.46	2.74
RDD284880		6.38	0.99	0.42	2.59
RDD284881		5.56	0.74	0.37	2.51
RDD284882		6.35	0.87	0.45	3.08
RDD284883		6.75	0.84	0.47	3.21
RDD284884		7.16	0.94	0.54	3.64
RDD284885		3.87	0.54	0.24	1.54
RDD284886		0.11	0.03	0.02	0.14
RDD284887		8.56	1.04	0.60	3.94
RDD284888		8.98	1.14	0.54	3.45
RDD284889		5.86	0.74	0.42	2.74
RDD284890					
RDD284891		6.81	0.66	0.28	1.92
RDD284892		8.62	1.15	0.57	3.60
RDD284893		5.40	0.79	0.46	3.04
RDD284894		7.35	1.02	0.47	3.06
RDD284895		3.06	0.45	0.23	1.52
RDD284896		1.03	0.26	0.14	0.88
RDD284897		3.01	0.40	0.19	1.22
RDD284898		4.99	0.69	0.35	2.29
RDD284899		6.52	0.80	0.44	2.73
RDD284900		5.37	0.68	0.36	2.25
RDD284901		5.83	0.82	0.42	2.68
RDD284902		8.28	1.14	0.56	3.54
RDD284903		7.79	1.12	0.58	3.66
RDD284904		6.77	0.96	0.39	2.42
RDD284905		6.75	0.94	0.44	2.75
RDD284906		7.35	1.01	0.45	2.66
RDD284907		6.97	1.01	0.47	2.84
RDD284908		6.30	0.95	0.46	3.00
RDD284909		7.14	1.02	0.45	2.79
RDD284910		7.18	1.06	0.49	3.03

\*\*\*\*\* See Appendix Page for comments regarding this certificate \*\*\*\*\*





Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Page: 5 - A

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg 0.02	PUL-QC Pass75um % 0.01	Au-ICP21 Au ppm 0.001	ME-XRF15b Sn % 0.005	ME-MS61r Ag ppm 0.01	ME-MS61r Al % 0.01	ME-MS61r As ppm 0.2	ME-MS61r Ba ppm 10	ME-MS61r Be ppm 0.05	ME-MS61r Bi ppm 0.01	ME-MS61r Ca % 0.01	ME-MS61r Cd ppm 0.02	ME-MS61r Ce ppm 0.01	ME-MS61r Co ppm 0.1	ME-MS61r Cr ppm 1
RDD284911		4.19		0.001	0.033	0.46	8.39	44.9	1360	2.83	1.03	1.43	3.12	73.9	36.0	147
RDD284912		4.32		0.002	0.010	0.05	8.21	52.9	1140	2.47	0.27	3.14	<0.02	79.1	30.9	168
RDD284913		3.47		0.001	0.010	0.04	8.37	94.5	1150	2.33	0.30	2.05	<0.02	79.0	43.0	167
RDD284914		3.10		0.001	0.005	0.06	7.90	9.4	730	1.72	0.31	2.11	0.03	78.8	30.7	144
RDD284915		<0.02			2.52											
RDD284916		0.07		0.002		0.05	6.15	0.6	470	0.89	0.05	2.45	0.06	35.7	9.3	48
RDD284917		3.70		0.002	0.008	0.09	7.41	43.2	760	1.68	0.37	2.61	<0.02	86.3	59.7	165
RDD284918		1.38		0.001	<0.005	0.02	0.08	1.6	10	<0.05	0.02	0.03	<0.02	1.53	0.4	9
RDD284919		5.32	86.0	0.002	<0.005	0.14	7.96	11.0	770	1.72	0.19	1.52	<0.02	69.4	32.3	153
RDD284920		3.73		0.003	0.008	0.09	8.22	3.1	710	1.78	0.18	2.00	0.02	75.6	30.5	169
RDD284921		3.21		0.002	0.005	0.15	9.25	3.4	700	3.32	0.92	0.87	0.02	78.5	30.2	177
RDD284922		3.49		0.001	0.013	0.15	8.33	6.7	400	4.77	0.35	2.79	0.60	76.0	25.8	119
RDD284923		1.77		0.001	0.006	0.07	8.74	3.2	1060	3.23	0.34	0.85	<0.02	65.6	21.3	139
RDD284924		5.15		0.001	0.006	0.13	9.30	7.5	510	3.55	0.33	1.27	0.19	64.2	36.2	155
RDD284925		4.05		0.001	0.009	0.82	8.38	14.4	440	2.65	0.72	3.81	0.50	72.3	20.7	141
RDD284926		3.51		0.001	0.007	0.38	8.56	12.6	570	2.33	0.49	0.97	0.07	69.7	24.8	167
RDD284927		4.32		0.002	0.010	0.16	7.67	105.5	520	2.13	0.47	2.74	<0.02	66.8	90.9	120
RDD284928		3.05		<0.001	0.007	0.03	8.41	22.7	510	1.83	0.20	1.63	<0.02	65.2	19.8	162
RDD284929		1.96		0.003	0.008	0.05	8.40	67.0	480	2.18	1.07	1.79	<0.02	80.0	44.5	109
RDD284930		2.69		0.002	0.009	0.08	8.18	74.2	470	2.15	0.71	1.53	<0.02	86.5	41.3	124
RDD284931		3.16		0.002	0.008	0.04	7.79	64.7	440	1.90	0.41	1.36	<0.02	74.9	32.1	141
RDD284932		3.58		0.002	0.011	0.05	8.17	65.5	360	2.42	0.59	2.54	<0.02	79.2	42.7	152
RDD284933		3.70		0.002	0.011	0.09	8.40	104.0	520	2.36	0.44	1.49	<0.02	75.1	37.9	162
RDD284934		2.36		0.003	0.013	0.08	7.46	116.5	350	2.24	1.35	1.50	<0.02	69.1	43.5	123
RDD284935		2.13		0.017	0.010	0.08	8.00	72.8	390	2.51	2.25	0.97	<0.02	88.6	47.5	116
RDD284936		1.84		0.001	0.011	0.01	9.95	5.6	900	2.69	0.41	1.02	<0.02	74.2	35.5	94
RDD284937		1.60		0.003	0.009	0.09	2.94	16.4	230	0.42	1.71	21.5	0.05	21.2	30.4	48
RDD284938		1.60		0.001	<0.005	0.01	0.08	0.4	10	<0.05	0.02	0.05	<0.02	1.44	0.4	5
RDD284939		1.97		0.002	0.011	0.14	1.90	12.1	60	0.26	1.51	26.1	0.04	15.75	39.0	36
RDD284940		<0.02			2.63											
RDD284941		0.07		0.002		0.10	7.83	1.1	550	2.10	0.03	5.72	0.13	61.0	46.6	148
RDD284942		1.45		0.006	<0.005	0.44	8.74	5.2	480	2.21	0.35	2.41	0.10	58.4	34.3	142
RDD284943		1.86		0.003	0.009	0.14	7.15	37.2	460	2.31	0.59	1.62	<0.02	93.8	19.4	52
RDD284944		1.33		0.002	0.005	0.06	7.63	25.0	560	3.01	0.66	1.37	<0.02	105.5	14.6	63
RDD284945		2.20		0.002	0.011	0.16	4.08	52.9	420	1.60	0.93	6.52	0.06	81.8	10.3	55
RDD284946		1.85		0.001	0.005	0.02	0.88	<0.2	50	0.58	0.02	17.85	0.04	13.50	1.7	5
RDD284947		1.77		0.001	<0.005	0.01	0.26	<0.2	10	0.25	0.01	18.75	0.02	6.26	1.5	2
RDD284948		1.73		0.002	<0.005	0.01	0.05	<0.2	10	<0.05	0.02	0.12	<0.02	1.40	0.3	7
RDD284949		1.93		0.001	0.006	0.03	0.45	<0.2	20	0.36	0.01	19.45	0.04	7.48	1.5	3
RDD284950		1.83		<0.001	0.006	0.01	0.43	<0.2	10	0.38	0.02	19.00	0.04	8.26	1.3	4



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Page: 5 - B

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Cs	Cu	Fe	Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb
		ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm
		0.05	0.2	0.01	0.05	0.05	0.1	0.005	0.01	0.5	0.2	0.01	5	0.05	0.01	0.1
RDD284911		37.0	160.5	8.54	22.4	0.26	5.1	3.82	2.63	36.9	53.5	2.07	2460	0.20	0.75	24.3
RDD284912		41.3	26.6	6.07	22.1	0.26	5.0	0.490	2.15	40.8	40.1	1.82	1525	0.41	1.21	27.5
RDD284913		40.1	51.2	7.48	22.3	0.26	5.0	0.346	2.12	38.8	58.4	2.27	1725	0.90	1.41	27.0
RDD284914		21.1	89.3	7.74	22.9	0.26	5.3	0.123	2.14	37.0	57.4	2.30	1895	0.21	0.97	26.7
RDD284915																
RDD284916		0.66	22.8	2.60	14.20	0.17	1.7	0.024	1.17	20.1	10.8	0.94	485	0.76	2.57	4.6
RDD284917		29.3	142.5	8.74	20.8	0.28	4.6	0.337	1.65	43.9	68.4	2.63	2400	0.16	0.70	24.7
RDD284918		0.23	3.1	0.68	0.38	0.05	0.4	<0.005	0.02	0.8	1.9	0.02	83	0.57	0.01	1.3
RDD284919		25.4	177.5	8.20	22.2	0.24	5.3	0.194	1.87	34.0	61.7	2.50	1665	0.14	0.97	25.8
RDD284920		15.85	103.5	8.05	22.9	0.26	4.9	0.113	1.49	36.2	62.0	2.69	1610	0.16	1.63	26.4
RDD284921		32.2	112.5	9.03	25.6	0.29	5.5	0.168	3.33	37.7	93.3	2.59	3310	0.20	0.21	27.2
RDD284922		31.8	50.1	9.52	22.9	0.29	4.4	0.270	2.36	34.9	134.5	2.21	3490	0.22	0.08	21.3
RDD284923		44.0	36.6	7.91	23.6	0.24	4.8	0.150	3.56	31.1	71.0	1.86	3460	0.20	0.60	23.7
RDD284924		16.15	37.1	8.05	24.7	0.26	5.0	0.153	3.04	29.6	81.6	2.41	1515	0.18	0.04	25.6
RDD284925		9.04	446	9.92	23.6	0.26	4.6	0.988	2.18	36.2	76.5	2.55	4430	0.15	0.03	24.3
RDD284926		18.65	219	8.91	23.6	0.29	5.5	1.195	2.38	34.6	63.1	2.51	2390	0.22	0.45	25.9
RDD284927		38.4	150.0	8.34	21.4	0.26	4.3	0.401	2.01	32.2	61.6	2.40	1880	0.24	0.64	20.5
RDD284928		29.7	29.1	8.06	23.2	0.25	5.0	0.285	1.80	29.8	55.8	2.54	1575	0.25	1.26	25.3
RDD284929		25.7	78.0	7.19	24.5	0.27	4.9	0.249	2.04	38.7	47.7	2.16	1185	0.56	1.20	21.0
RDD284930		26.5	132.0	8.05	25.0	0.26	5.6	0.303	2.17	42.5	48.6	2.22	1175	10.30	1.25	26.3
RDD284931		24.7	101.5	8.35	24.6	0.28	5.4	0.407	2.05	37.0	47.5	2.18	1495	0.66	1.06	26.8
RDD284932		36.7	196.0	8.81	26.4	0.29	5.8	0.267	2.03	38.8	45.9	2.04	1800	1.74	1.06	28.5
RDD284933		22.5	174.0	9.13	26.5	0.26	5.7	0.466	2.22	35.9	50.3	2.05	1475	0.46	1.27	28.6
RDD284934		27.2	199.5	8.43	22.0	0.24	5.1	0.387	1.93	32.2	37.7	1.92	1290	2.43	1.16	26.5
RDD284935		22.5	146.5	8.97	23.0	0.27	4.4	0.369	1.97	40.8	42.8	2.18	1400	0.66	1.00	23.2
RDD284936		12.20	21.0	7.66	25.7	0.30	3.2	0.136	3.13	31.0	42.9	1.89	1445	0.20	1.20	20.7
RDD284937		1.18	235	3.54	7.42	0.11	1.1	0.145	0.34	8.3	10.1	0.68	3450	12.95	1.21	4.3
RDD284938		0.14	2.3	0.57	0.31	<0.05	0.4	<0.005	0.04	0.7	1.4	0.01	71	0.40	0.01	1.3
RDD284939		0.87	347	3.89	4.71	0.09	0.7	0.155	0.12	6.8	9.5	0.61	4170	5.26	0.66	3.1
RDD284940																
RDD284941		1.20	44.7	8.02	21.8	0.20	4.7	0.071	1.70	30.1	12.2	4.65	1150	4.25	2.33	47.9
RDD284942		21.7	951	7.55	20.6	0.19	2.8	0.296	2.08	24.8	72.6	2.25	1705	0.19	1.37	20.4
RDD284943		19.60	66.2	5.24	18.85	0.22	4.3	0.205	3.13	44.3	54.7	2.41	1525	0.90	0.23	17.1
RDD284944		23.8	49.4	3.30	20.1	0.28	5.0	0.096	3.93	50.8	41.2	2.01	788	0.83	0.26	28.6
RDD284945		8.82	60.9	3.88	11.90	0.20	4.4	0.209	2.25	42.2	36.0	4.92	2170	1.37	0.40	44.1
RDD284946		4.24	2.6	1.23	2.49	0.07	1.1	0.065	0.32	6.4	12.0	10.40	1565	<0.05	0.02	7.8
RDD284947		0.83	2.9	0.82	0.84	0.08	0.2	0.024	0.03	2.8	6.7	11.10	870	<0.05	0.02	1.5
RDD284948		0.12	2.3	0.59	0.23	<0.05	0.4	0.005	0.02	0.7	1.7	0.07	78	0.42	0.01	1.4
RDD284949		1.42	3.9	0.95	1.30	0.06	0.4	0.022	0.11	3.3	9.8	11.55	945	<0.05	0.01	2.6
RDD284950		1.02	3.2	0.88	1.24	0.07	0.4	0.031	0.04	3.8	9.2	11.25	1030	<0.05	0.01	1.7



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 5 - C

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ni	P	Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti
		ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.2	10	0.5	0.1	0.002	0.01	0.05	0.1	1	0.2	0.2	0.05	0.05	0.01	0.005
RDD284911		90.0	1140	6.6	185.5	<0.002	0.50	4.85	29.7	1	48.3	104.0	1.67	0.17	10.25	0.944
RDD284912		79.7	960	6.1	216	<0.002	0.15	4.35	29.9	1	56.5	187.0	1.83	0.11	10.00	1.125
RDD284913		111.0	1110	4.8	183.0	0.003	0.16	8.70	30.6	1	40.6	138.5	1.78	0.13	9.48	0.979
RDD284914		89.7	990	5.5	125.0	<0.002	0.07	3.21	28.5	1	5.9	68.5	1.74	0.23	10.70	0.933
RDD284915																
RDD284916		27.9	540	6.7	33.5	<0.002	0.01	0.09	8.6	<1	0.8	404	0.27	<0.05	2.96	0.207
RDD284917		141.5	950	3.9	117.5	<0.002	0.42	4.64	29.8	1	16.0	137.5	1.63	0.13	7.82	1.150
RDD284918		1.6	10	1.3	1.1	<0.002	<0.01	0.22	0.3	<1	0.3	3.2	0.07	<0.05	0.30	0.055
RDD284919		102.0	930	2.3	106.0	<0.002	0.13	3.30	30.3	1	7.9	112.0	1.75	0.12	9.54	1.100
RDD284920		106.5	1080	2.0	80.4	<0.002	0.03	1.81	29.7	1	3.7	108.5	1.72	0.14	8.47	1.090
RDD284921		99.8	1060	13.6	272	<0.002	0.04	3.27	32.8	<1	7.5	53.5	1.79	0.14	11.60	0.933
RDD284922		81.5	860	117.5	310	<0.002	0.07	7.81	29.1	1	47.4	54.7	1.46	0.21	11.20	0.741
RDD284923		87.2	950	7.9	321	<0.002	0.02	5.46	28.7	<1	5.0	54.2	1.62	0.15	11.70	0.801
RDD284924		89.6	1000	19.4	274	<0.002	0.05	5.90	31.0	1	9.9	28.0	1.75	0.21	11.35	0.841
RDD284925		90.0	960	41.2	159.0	<0.002	0.18	7.99	29.1	1	36.7	36.7	1.63	0.20	8.82	0.802
RDD284926		94.3	1000	11.4	151.5	<0.002	0.09	3.30	30.9	1	25.2	35.2	1.78	0.17	9.11	0.832
RDD284927		82.3	730	12.1	147.0	<0.002	0.89	9.96	26.1	1	30.0	90.5	1.43	0.28	9.70	0.686
RDD284928		95.5	980	6.1	118.0	<0.002	0.24	3.46	29.1	1	17.5	86.4	1.67	0.11	9.05	0.864
RDD284929		78.2	670	8.6	129.5	<0.002	0.38	2.95	25.6	1	20.3	96.7	1.55	0.26	16.30	0.831
RDD284930		89.0	720	7.4	124.0	0.005	0.95	5.16	29.2	1	24.4	84.8	1.84	0.16	12.70	1.155
RDD284931		87.2	910	4.6	117.5	<0.002	0.67	4.22	30.3	1	47.7	70.2	1.91	0.12	10.85	1.405
RDD284932		104.0	710	8.9	130.0	0.002	1.78	5.19	31.6	1	26.2	111.5	1.91	0.07	11.10	1.500
RDD284933		110.5	780	8.7	115.5	<0.002	1.33	6.18	35.1	1	54.6	80.6	1.96	0.09	9.16	1.450
RDD284934		84.6	580	5.6	111.0	0.002	1.63	5.67	27.6	1	38.1	76.1	1.64	0.11	9.20	1.190
RDD284935		90.6	670	4.5	104.5	<0.002	0.91	4.22	25.9	1	20.1	52.0	1.49	0.69	14.90	0.802
RDD284936		82.1	1090	4.6	118.0	<0.002	0.04	1.98	31.1	<1	4.8	62.4	1.36	0.09	11.55	0.697
RDD284937		30.5	560	8.0	10.8	0.004	1.27	4.02	10.8	1	4.8	538	0.29	0.05	2.17	0.224
RDD284938		1.2	10	1.1	1.4	0.002	0.01	0.24	0.3	<1	0.3	2.8	0.07	<0.05	0.28	0.051
RDD284939		28.3	930	4.9	4.9	0.002	1.35	1.95	8.1	1	12.5	557	0.20	0.21	1.52	0.158
RDD284940																
RDD284941		146.0	2580	3.4	40.4	<0.002	0.04	0.11	21.6	1	1.9	784	2.98	<0.05	3.33	1.210
RDD284942		86.5	800	5.3	84.4	<0.002	0.17	1.68	27.5	1	7.0	80.4	1.29	0.20	7.15	0.736
RDD284943		29.2	640	7.3	173.0	0.003	2.36	25.1	14.0	2	19.1	51.5	1.05	0.20	13.25	0.295
RDD284944		28.6	800	7.0	215	0.004	1.42	19.20	15.1	1	9.1	65.2	1.75	0.15	14.65	0.361
RDD284945		53.9	990	12.2	121.5	0.002	1.49	3.62	8.4	1	39.4	99.3	2.33	<0.05	8.90	0.286
RDD284946		4.4	470	3.0	22.2	<0.002	<0.01	0.89	1.5	<1	2.8	193.0	0.39	<0.05	2.04	0.054
RDD284947		3.0	210	3.0	1.6	<0.002	<0.01	0.18	0.7	<1	0.7	205	<0.05	<0.05	0.54	0.018
RDD284948		1.0	10	2.2	0.8	<0.002	0.01	0.28	0.2	<1	0.3	3.7	0.06	<0.05	0.26	0.055
RDD284949		2.6	330	3.8	4.9	<0.002	<0.01	0.20	0.9	<1	0.5	212	0.16	<0.05	0.96	0.028
RDD284950		2.0	290	1.4	1.8	<0.002	<0.01	0.14	0.9	<1	0.5	208	0.11	<0.05	0.97	0.026



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 5 - D

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ti	U	V	W	Y	Zn	Zr	Dy	Er	Eu	Gd	Ho	Lu	Nd
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.02	0.1	1	0.1	0.1	2	0.5	0.05	0.03	0.03	0.05	0.01	0.01	0.1
RDD284911		2.05	1.8	194	3.8	33.9	432	124.0	6.61	3.58	2.05	6.78	1.28	0.50	32.5
RDD284912		2.63	2.0	208	3.0	34.3	52	126.0	6.46	3.55	2.13	6.95	1.31	0.49	34.2
RDD284913		1.97	1.7	197	2.1	37.7	68	114.0	7.13	3.92	2.00	7.24	1.41	0.52	34.5
RDD284914		0.85	2.0	180	1.6	35.6	82	147.0	6.86	5.02	1.83	7.05	1.36	0.58	37.4
RDD284915															10.05
RDD284916		0.21	0.7	55	0.2	10.7	35	66.7	1.87	1.01	0.82	2.33	0.37	0.14	17.6
RDD284917		1.24	1.5	198	1.6	33.3	74	105.0	6.51	3.38	1.95	7.16	1.25	0.41	38.7
RDD284918		0.05	0.2	4	0.2	1.0	2	15.8	0.18	0.15	0.03	0.15	0.04	0.02	0.6
RDD284919		0.80	1.8	199	1.7	33.0	83	125.0	6.42	3.60	1.64	6.55	1.26	0.49	31.9
RDD284920		0.60	1.7	194	1.6	33.1	83	124.0	6.48	3.50	1.62	7.23	1.30	0.47	33.2
RDD284921		1.93	1.7	202	2.5	34.2	76	151.0	6.46	3.73	1.87	6.48	1.39	0.53	32.9
RDD284922		2.49	1.5	170	4.2	29.3	306	105.0	5.57	3.18	1.68	5.97	1.14	0.44	31.1
RDD284923		2.65	1.5	183	1.9	28.7	69	102.0	5.32	3.33	1.52	5.47	1.06	0.46	27.7
RDD284924		1.93	1.6	192	3.7	33.1	141	138.0	6.27	3.68	1.52	5.99	1.28	0.52	27.5
RDD284925		1.02	1.4	176	5.1	33.3	285	116.0	6.24	3.42	2.00	6.50	1.27	0.48	31.8
RDD284926		1.17	1.5	186	3.4	32.7	132	123.0	6.32	3.59	1.87	6.32	1.26	0.54	30.3
RDD284927		1.79	1.3	149	2.1	29.3	72	107.0	5.47	3.07	1.67	5.71	1.09	0.42	28.5
RDD284928		1.35	1.6	192	2.6	31.3	58	132.0	5.77	3.41	1.27	5.52	1.20	0.46	27.6
RDD284929		1.36	2.8	174	2.6	30.8	54	170.0	6.14	3.45	1.42	6.47	1.20	0.52	33.6
RDD284930		1.42	2.6	191	3.9	38.6	55	154.0	7.71	4.10	1.74	7.95	1.50	0.54	42.1
RDD284931		1.35	2.2	200	3.4	35.6	59	148.0	7.12	3.80	1.68	7.18	1.40	0.52	34.9
RDD284932		1.69	2.5	216	2.8	33.5	50	151.0	6.46	3.53	1.63	6.69	1.27	0.49	35.0
RDD284933		1.29	2.0	231	2.9	34.6	59	140.0	6.93	3.70	1.83	7.36	1.38	0.50	35.3
RDD284934		1.19	2.1	180	3.2	32.6	53	145.0	6.12	3.34	1.52	6.65	1.24	0.49	31.0
RDD284935		0.97	2.5	150	2.8	30.7	58	164.5	5.95	3.41	1.70	6.29	1.18	0.53	35.5
RDD284936		0.62	1.5	182	2.3	25.8	60	117.5	4.95	2.88	1.37	5.29	1.01	0.39	28.0
RDD284937		0.14	2.1	60	0.6	14.5	30	37.1	2.21	1.32	0.51	2.25	0.45	0.17	9.2
RDD284938		0.05	0.2	3	0.2	0.9	2	14.3	0.15	0.11	0.03	0.12	0.03	0.02	0.6
RDD284939		0.09	1.1	39	0.5	9.3	23	26.9	1.55	0.86	0.45	1.62	0.30	0.12	7.1
RDD284940															1.75
RDD284941		0.15	1.3	197	0.2	20.8	112	210	4.02	1.93	1.85	4.94	0.74	0.23	27.8
RDD284942		0.76	1.1	166	2.0	25.4	74	104.0	4.88	2.62	1.20	4.94	0.94	0.34	24.4
RDD284943		1.34	2.7	75	1.9	33.5	31	149.5	5.69	3.42	1.43	6.19	1.19	0.51	38.5
RDD284944		1.45	3.1	86	2.1	36.5	23	182.0	6.27	3.70	1.46	6.67	1.27	0.56	43.4
RDD284945		0.85	2.2	48	1.4	35.6	47	171.0	5.35	3.30	1.14	5.51	1.10	0.48	33.3
RDD284946		0.14	0.6	11	0.4	7.1	23	56.4	0.97	0.66	0.28	0.98	0.22	0.10	5.5
RDD284947		0.03	0.2	4	0.2	3.2	16	16.0	0.45	0.28	0.16	0.49	0.10	0.04	2.8
RDD284948		0.04	0.2	3	0.2	1.0	2	15.8	0.15	0.12	<0.03	0.12	0.04	0.02	0.5
RDD284949		0.04	0.3	6	0.2	4.1	12	25.5	0.61	0.36	0.17	0.62	0.12	0.05	3.2
RDD284950		0.03	0.3	6	0.2	4.3	14	30.0	0.59	0.38	0.22	0.61	0.13	0.06	3.6



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 5 - E

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Sm	Tb	Tm	Yb
		ppm	ppm	ppm	ppm
		0.03	0.01	0.01	0.03
RDD284911		7.28	1.10	0.51	3.14
RDD284912		7.60	1.11	0.52	3.28
RDD284913		7.83	1.20	0.56	3.41
RDD284914		7.91	1.16	0.55	3.50
RDD284915					
RDD284916		3.31	0.33	0.15	0.95
RDD284917		8.20	1.13	0.45	2.82
RDD284918		0.13	0.03	0.02	0.15
RDD284919		7.25	1.07	0.50	3.24
RDD284920		7.52	1.07	0.52	3.12
RDD284921		7.36	1.07	0.54	3.40
RDD284922		7.04	0.97	0.47	2.81
RDD284923		6.05	0.88	0.46	2.96
RDD284924		6.39	1.02	0.53	3.42
RDD284925		7.14	1.07	0.51	3.07
RDD284926		6.74	1.04	0.52	3.22
RDD284927		6.42	0.93	0.44	2.71
RDD284928		5.99	0.96	0.50	3.13
RDD284929		7.50	1.04	0.51	3.22
RDD284930		8.98	1.30	0.58	3.58
RDD284931		8.09	1.20	0.55	3.39
RDD284932		7.77	1.09	0.54	3.28
RDD284933		8.11	1.18	0.55	3.41
RDD284934		6.94	1.07	0.48	3.08
RDD284935		7.28	1.06	0.50	3.42
RDD284936		5.88	0.86	0.41	2.62
RDD284937		2.24	0.36	0.18	1.15
RDD284938		0.11	0.03	0.02	0.13
RDD284939		1.77	0.26	0.12	0.77
RDD284940					
RDD284941		5.82	0.76	0.27	1.53
RDD284942		5.22	0.82	0.37	2.36
RDD284943		7.32	0.98	0.50	3.40
RDD284944		7.89	1.08	0.56	3.58
RDD284945		6.39	0.86	0.48	3.10
RDD284946		1.07	0.16	0.10	0.61
RDD284947		0.55	0.08	0.04	0.25
RDD284948		0.11	0.02	0.02	0.15
RDD284949		0.73	0.10	0.06	0.35
RDD284950		0.71	0.10	0.06	0.39



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Page: 6 - A

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	WEI-21	PUL-QC	Au-ICP21	ME-XRF15b	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Recvd Wt.	Pass75um	Au	Sn	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr
		kg	%	ppm	%	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm
		0.02	0.01	0.001	0.005	0.01	0.01	0.2	10	0.05	0.01	0.01	0.02	0.01	0.1	1
RDD284951		1.80		0.001	<0.005	<0.01	0.38	<0.2	10	0.35	0.01	20.2	0.02	7.19	1.3	2
RDD284952		1.87		0.002	0.005	0.01	0.39	<0.2	10	0.30	0.01	19.55	0.02	5.55	1.3	2
RDD284953		2.49		0.001	0.011	0.05	3.65	16.8	250	1.30	0.43	10.55	<0.02	47.9	4.0	28
RDD284954		0.53		0.001	0.009	0.11	6.65	6.5	340	2.25	0.37	0.33	0.06	85.1	6.7	66
RDD284955		0.57		0.002	0.007	0.13	6.87	4.8	360	2.19	0.46	0.20	0.07	84.5	6.4	60
RDD284956		2.12	94.0	0.002	0.011	0.04	7.12	2.3	320	2.70	0.10	0.67	<0.02	102.0	6.7	57
RDD284957		1.81		0.003	0.012	0.07	7.12	6.2	320	2.42	0.49	0.28	<0.02	95.0	8.0	57
RDD284958		1.61		0.002	0.008	0.11	6.52	22.5	290	2.28	1.16	0.55	<0.02	87.4	12.1	56
RDD284959		1.74		0.001	0.008	0.07	5.91	8.9	260	2.21	0.26	0.73	<0.02	76.2	5.8	46
RDD284960		1.85		0.001	0.007	0.10	6.99	6.7	300	2.35	0.46	0.44	<0.02	85.8	7.6	53
RDD284961		1.60		0.001	0.006	0.10	6.89	7.8	300	2.45	0.47	1.54	<0.02	94.9	8.1	53
RDD284962		1.59		0.002	0.012	0.08	6.36	4.4	230	2.29	0.48	0.62	<0.02	88.9	12.0	46
RDD284963		1.69		<0.001	0.011	0.07	5.14	5.9	220	1.96	0.49	0.96	<0.02	98.4	5.6	39
RDD284964		1.91		0.001	0.005	0.02	0.34	<0.2	<10	0.26	0.05	20.7	0.04	6.95	1.5	3
RDD284965		<0.02			2.52											
RDD284966		0.07		0.326		0.15	7.21	18.2	80	0.32	0.02	7.66	0.24	11.20	49.1	103
RDD284967		1.87		0.001	<0.005	<0.01	0.34	<0.2	<10	0.26	0.02	20.0	0.03	6.57	1.1	3
RDD284968		1.79		0.001	0.005	<0.01	0.17	<0.2	<10	0.21	0.03	19.95	<0.02	4.66	1.1	2
RDD284969		1.78		0.001	<0.005	0.01	0.16	<0.2	<10	0.25	0.05	20.3	<0.02	4.67	1.2	2
RDD284970		1.82		0.001	<0.005	<0.01	0.14	<0.2	<10	0.26	0.14	19.80	0.02	4.92	1.5	1
RDD284971		2.08		0.001	<0.005	0.01	0.14	0.8	<10	0.30	0.15	20.0	<0.02	6.20	2.1	1
RDD284972		1.18		0.001	<0.005	0.01	0.03	0.3	<10	<0.05	0.01	0.07	<0.02	1.14	0.2	9
RDD284973		1.82		0.001	<0.005	0.01	0.18	<0.2	<10	0.36	0.16	19.60	<0.02	5.62	2.1	2
RDD284974		1.82		0.001	<0.005	0.01	0.16	<0.2	<10	0.22	0.05	20.4	0.02	4.75	1.5	2
RDD284975		1.79		0.001	<0.005	<0.01	0.27	<0.2	<10	0.26	0.07	21.3	<0.02	6.72	1.6	3
RDD284976		1.64		0.001	0.009	0.07	7.67	2.5	300	3.38	0.45	0.55	<0.02	115.5	4.9	80
RDD284977		1.66		0.002	0.009	0.03	7.05	6.1	400	2.65	0.45	0.96	<0.02	106.5	7.4	70
RDD284978		1.65		0.001	0.017	0.03	7.01	3.9	600	2.70	0.10	4.22	<0.02	97.1	3.1	54
RDD284979		1.82		0.001	0.020	0.07	6.15	2.6	660	2.32	0.06	8.08	<0.02	91.5	2.8	39
RDD284980		1.75		0.001	0.025	0.04	5.47	0.2	140	1.67	0.06	11.25	<0.02	84.2	3.4	31
RDD284981		0.79		0.001	0.029	0.03	5.28	<0.2	130	1.31	0.02	10.70	<0.02	83.8	3.2	29
RDD284982		0.92		0.001	0.011	<0.01	7.92	4.9	580	3.07	0.05	3.15	<0.02	114.0	2.3	57
RDD284983		1.57		0.002	0.011	0.03	8.26	63.1	560	3.19	0.20	0.96	0.81	105.5	13.8	60
RDD284984		1.85		0.002	0.008	0.01	7.78	3.6	370	2.78	0.12	0.38	<0.02	91.8	3.8	64
RDD284985		1.96		0.002	0.017	0.11	6.50	8.7	220	2.22	0.35	5.27	<0.02	82.3	7.1	45
RDD284986		2.08		0.002	0.018	0.02	6.18	<0.2	440	1.98	0.05	8.47	<0.02	73.6	3.6	32
RDD284987		1.72		0.001	0.013	0.06	4.92	0.9	390	1.49	0.12	11.90	<0.02	53.7	4.4	26
RDD284988		1.86		0.002	<0.005	0.02	3.51	0.8	70	1.13	0.05	16.90	<0.02	41.1	7.3	18
RDD284989		1.89		0.001	<0.005	0.03	3.69	<0.2	110	1.17	0.12	16.25	<0.02	42.8	5.3	19
RDD284990		<0.02			2.65											



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Page: 6 - B

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Cs	Cu	Fe	Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na
		ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%
		0.05	0.2	0.01	0.05	0.05	0.1	0.005	0.01	0.5	0.2	0.01	5	0.05	0.01
RDD284951		0.87	3.6	0.84	1.10	0.07	0.3	0.024	0.03	3.3	7.0	11.85	790	<0.05	0.01
RDD284952		0.90	3.1	0.73	1.15	0.10	0.3	0.021	0.03	2.6	7.9	11.40	627	<0.05	0.01
RDD284953		10.65	16.8	2.17	9.28	0.13	2.4	0.102	1.92	23.6	28.7	5.72	561	0.42	0.13
RDD284954		11.35	20.9	2.55	17.50	0.18	4.3	0.103	3.52	40.6	19.7	0.88	96	1.69	0.08
RDD284955		11.45	20.4	2.54	17.65	0.20	4.3	0.109	3.64	41.6	18.0	0.71	78	1.91	0.07
RDD284956		16.25	31.1	3.27	18.15	0.21	4.4	0.119	3.25	49.7	33.6	1.43	249	0.83	0.32
RDD284957		12.25	19.8	2.15	18.55	0.21	4.5	0.080	3.52	45.6	16.4	0.62	117	1.03	0.20
RDD284958		10.50	29.7	3.47	17.15	0.20	4.4	0.070	3.06	41.9	23.1	0.84	176	2.12	0.24
RDD284959		10.95	18.8	2.14	15.10	0.17	3.6	0.070	2.69	36.9	17.2	0.81	154	0.93	0.25
RDD284960		14.70	23.0	2.66	18.35	0.21	4.4	0.071	3.46	41.6	19.8	0.93	124	0.64	0.21
RDD284961		14.40	24.3	2.56	17.60	0.24	4.8	0.064	3.15	45.2	23.9	0.89	169	1.46	0.27
RDD284962		18.20	28.8	3.73	16.80	0.22	4.4	0.067	2.98	45.0	45.2	1.84	264	0.83	0.20
RDD284963		19.90	19.3	2.32	12.30	0.17	4.1	0.112	2.54	47.7	33.3	1.51	345	0.76	0.28
RDD284964		2.00	4.6	1.73	1.06	0.09	0.3	0.047	0.08	2.7	7.8	11.45	1195	0.06	0.01
RDD284965															
RDD284966		0.38	175.5	8.05	15.80	0.13	1.6	0.070	0.26	4.0	11.6	3.96	1345	0.69	1.65
RDD284967		0.56	2.0	1.68	0.97	0.07	0.3	0.109	0.02	2.4	8.5	11.40	1260	<0.05	0.01
RDD284968		0.31	2.6	1.85	0.52	0.07	0.1	0.077	0.02	1.7	5.4	11.15	1430	<0.05	0.01
RDD284969		0.15	3.8	2.00	0.54	0.06	0.2	0.119	0.01	1.8	4.9	11.55	1660	<0.05	0.01
RDD284970		0.09	8.2	2.10	0.40	0.05	0.1	0.160	0.01	2.2	3.3	11.15	1710	<0.05	0.01
RDD284971		0.11	16.1	2.74	0.45	0.05	0.1	0.196	0.01	2.5	3.6	11.20	2070	<0.05	0.01
RDD284972		<0.05	2.3	0.65	0.16	<0.05	0.4	<0.005	0.02	0.5	1.2	0.04	78	0.54	0.01
RDD284973		0.15	18.6	3.02	0.52	<0.05	0.1	0.254	<0.01	1.9	4.1	11.20	2150	<0.05	0.01
RDD284974		0.08	13.4	2.31	0.44	<0.05	0.1	0.140	<0.01	1.7	4.0	11.40	1780	<0.05	0.01
RDD284975		0.29	8.8	2.30	0.85	<0.05	0.2	0.133	0.01	2.7	7.8	11.00	1800	<0.05	0.01
RDD284976		18.30	19.3	2.01	19.75	0.23	4.3	0.129	4.52	55.9	37.6	1.22	143	0.19	0.18
RDD284977		23.8	33.6	2.00	18.45	0.22	4.1	0.079	4.63	53.9	30.4	1.51	191	0.34	0.29
RDD284978		23.7	8.8	2.20	17.15	0.23	4.1	0.258	4.65	49.1	32.0	3.28	676	0.25	0.40
RDD284979		18.10	7.4	3.00	13.65	0.17	3.6	0.655	3.98	44.6	60.0	5.85	1650	0.28	0.48
RDD284980		37.0	1.2	4.12	14.60	0.21	3.1	0.872	2.02	40.5	64.6	7.12	2420	0.23	0.28
RDD284981		23.2	1.2	4.02	13.55	0.23	3.0	0.911	2.13	42.0	36.9	6.28	2270	0.15	0.24
RDD284982		18.65	2.3	1.72	18.60	0.27	4.5	0.149	3.63	55.1	30.5	2.07	443	0.33	0.66
RDD284983		16.10	13.8	1.18	20.2	0.25	4.9	0.172	5.28	50.0	26.1	1.04	188	1.03	0.49
RDD284984		16.30	25.2	1.28	20.5	0.21	4.5	0.106	4.04	44.7	25.1	1.01	101	0.40	0.31
RDD284985		13.25	38.0	4.00	17.65	0.21	3.7	0.628	2.39	39.9	50.2	4.36	1185	0.20	0.78
RDD284986		27.0	1.3	4.20	14.60	0.17	3.3	0.817	3.12	35.8	54.1	5.71	1705	0.31	0.75
RDD284987		11.25	2.7	3.33	11.90	0.13	2.8	0.515	2.67	26.1	58.5	6.26	1270	0.16	0.64
RDD284988		17.45	27.9	2.65	9.08	0.11	2.1	0.185	0.98	19.8	56.4	8.18	992	0.11	0.34
RDD284989		21.1	25.3	2.44	9.75	0.11	2.0	0.203	1.30	21.3	44.5	8.59	930	0.08	0.34
RDD284990															



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 6 - C

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ni	P	Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th
		ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.2	10	0.5	0.1	0.002	0.01	0.05	0.1	1	0.2	0.2	0.05	0.05	0.01
RDD284951		2.2	200	0.7	1.5	<0.002	<0.01	0.09	0.9	<1	0.3	183.5	0.05	<0.05	0.66
RDD284952		2.0	230	0.5	1.3	<0.002	<0.01	0.07	0.9	<1	0.3	205	0.06	<0.05	0.64
RDD284953		10.4	510	4.9	127.5	<0.002	0.72	1.22	6.3	1	27.7	134.5	0.56	<0.05	6.17
RDD284954		18.7	460	9.5	174.0	0.003	1.35	2.37	12.3	1	11.7	20.5	0.96	<0.05	12.25
RDD284955		20.1	340	11.8	170.5	0.003	1.37	3.32	12.3	2	9.5	17.4	0.97	<0.05	12.40
RDD284956		14.0	410	4.5	179.5	0.002	1.35	2.59	12.7	1	23.0	37.2	0.90	0.05	12.90
RDD284957		20.1	460	5.8	173.0	0.002	0.94	2.42	12.4	1	10.9	24.2	1.04	<0.05	14.05
RDD284958		24.0	580	8.0	149.5	<0.002	1.51	4.92	11.4	1	12.2	30.5	0.93	0.06	12.80
RDD284959		14.7	940	8.8	135.5	<0.002	1.03	3.27	10.8	1	11.8	42.1	0.75	<0.05	10.90
RDD284960		18.0	660	7.6	177.5	0.002	1.31	2.73	12.8	1	9.1	28.4	0.99	0.06	13.30
RDD284961		21.3	1580	8.2	177.0	0.002	1.23	4.33	12.2	1	11.6	49.5	1.08	<0.05	13.80
RDD284962		20.2	540	5.0	173.0	<0.002	1.87	3.73	10.6	<1	8.2	32.4	1.03	<0.05	13.20
RDD284963		12.4	760	12.0	211	0.002	0.70	3.16	8.3	<1	57.4	39.1	1.06	<0.05	12.00
RDD284964		1.8	840	1.8	6.8	<0.002	0.11	0.18	0.8	<1	1.2	115.0	0.06	<0.05	0.75
RDD284965															
RDD284966		90.6	410	8.3	6.4	0.003	0.19	0.57	45.8	1	0.7	240	0.21	0.06	0.43
RDD284967		1.1	600	0.5	1.1	<0.002	0.02	0.16	0.7	<1	0.9	132.5	0.05	<0.05	0.72
RDD284968		1.1	470	0.5	0.9	<0.002	0.02	0.15	0.4	<1	0.5	131.5	<0.05	<0.05	0.35
RDD284969		0.7	430	<0.5	0.2	<0.002	0.09	0.14	0.4	<1	0.6	134.0	<0.05	<0.05	0.40
RDD284970		0.9	300	<0.5	0.4	<0.002	0.19	0.14	0.4	<1	0.8	129.0	<0.05	<0.05	0.26
RDD284971		1.3	330	0.5	0.3	<0.002	0.27	0.14	0.6	<1	2.1	139.0	<0.05	<0.05	0.30
RDD284972		0.9	10	1.1	0.6	<0.002	<0.01	0.15	0.1	<1	0.4	2.5	0.06	<0.05	0.23
RDD284973		1.2	320	0.5	0.2	<0.002	0.40	0.21	0.7	<1	3.5	136.0	<0.05	<0.05	0.26
RDD284974		0.8	290	<0.5	0.2	<0.002	0.20	0.12	0.4	<1	1.1	132.5	<0.05	<0.05	0.29
RDD284975		1.3	510	0.6	0.6	<0.002	0.22	0.17	0.6	<1	7.2	118.5	<0.05	<0.05	0.54
RDD284976		17.4	1730	9.0	316	<0.002	0.98	1.34	13.7	1	28.4	26.1	0.89	<0.05	16.05
RDD284977		20.2	1890	4.2	317	<0.002	0.74	2.30	13.4	<1	9.4	48.6	0.86	0.06	15.25
RDD284978		16.3	1890	5.5	415	0.002	0.08	1.78	13.3	<1	95.9	100.0	0.81	<0.05	13.80
RDD284979		15.1	1100	30.3	413	<0.002	<0.01	3.09	10.8	<1	135.0	102.5	0.73	<0.05	12.90
RDD284980		16.1	1280	23.1	317	<0.002	<0.01	2.73	10.6	<1	208	101.5	0.66	<0.05	11.65
RDD284981		14.1	1030	6.1	324	<0.002	<0.01	2.22	11.0	<1	223	98.4	0.62	<0.05	10.70
RDD284982		18.8	1100	4.2	368	<0.002	0.01	1.07	17.3	<1	62.7	131.5	0.93	<0.05	16.75
RDD284983		42.7	690	20.8	349	0.009	0.09	2.64	15.6	1	17.4	73.1	0.92	<0.05	16.05
RDD284984		17.8	460	2.7	232	<0.002	0.17	1.34	14.6	1	6.2	27.1	0.88	<0.05	15.40
RDD284985		13.6	550	7.6	228	<0.002	0.36	3.23	13.8	<1	101.5	83.8	0.76	<0.05	12.55
RDD284986		12.7	520	15.4	407	<0.002	0.01	1.40	11.8	<1	95.0	181.0	0.69	<0.05	11.55
RDD284987		15.2	410	13.0	299	<0.002	0.05	1.08	9.5	<1	68.7	104.5	0.54	<0.05	8.34
RDD284988		21.7	360	1.3	59.8	<0.002	0.02	1.43	7.0	<1	9.6	96.7	0.38	<0.05	6.05
RDD284989		12.2	360	1.6	74.1	<0.002	<0.01	0.90	7.5	<1	9.4	102.0	0.38	0.05	6.14
RDD284990															





Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 6 - D

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ti	U	V	W	Y	Zn	Zr	Dy	Er	Eu	Gd	Ho	Lu	Nd	Pr
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.02	0.1	1	0.1	0.1	2	0.5	0.05	0.03	0.03	0.05	0.01	0.01	0.1	0.03
RDD284951		0.02	0.2	5	0.2	3.5	10	11.2	0.54	0.31	0.18	0.59	0.11	0.04	3.1	0.81
RDD284952		0.02	0.2	4	0.2	2.7	9	12.4	0.44	0.26	0.16	0.49	0.08	0.04	2.6	0.64
RDD284953		0.84	1.5	40	1.1	18.6	18	87.4	2.89	1.78	0.78	3.07	0.62	0.26	19.8	5.36
RDD284954		0.92	3.1	81	1.8	29.6	36	152.0	5.22	3.12	1.04	5.32	1.06	0.46	36.3	10.50
RDD284955		0.91	2.5	82	1.9	26.6	36	150.0	4.43	2.83	0.98	4.59	0.94	0.44	33.9	9.93
RDD284956		0.97	2.8	84	2.2	30.9	19	153.0	5.51	3.18	1.47	6.03	1.10	0.47	44.9	12.20
RDD284957		0.83	2.9	79	2.1	29.0	8	156.5	5.08	3.07	1.25	5.48	1.04	0.50	40.7	11.25
RDD284958		0.79	2.9	72	1.9	32.2	11	148.5	5.43	3.27	1.21	5.95	1.12	0.50	36.6	10.65
RDD284959		0.68	2.8	67	1.5	27.2	14	132.0	4.61	2.93	1.17	5.07	0.94	0.41	31.7	9.09
RDD284960		0.92	2.7	78	2.0	28.8	13	151.0	4.94	3.07	1.14	5.29	1.00	0.48	35.0	10.15
RDD284961		0.95	4.6	75	2.4	42.7	14	167.0	6.81	3.98	1.48	7.44	1.38	0.57	42.6	11.40
RDD284962		0.99	3.0	67	2.4	26.0	14	161.5	4.53	2.73	1.04	4.89	0.93	0.45	33.6	10.10
RDD284963		1.34	2.8	54	2.1	30.5	34	142.5	5.29	3.09	1.31	5.29	1.08	0.48	39.8	11.60
RDD284964		0.07	0.5	3	0.2	5.5	10	12.5	0.87	0.48	0.27	1.07	0.18	0.05	4.4	0.98
RDD284965																
RDD284966		0.09	0.1	284	8.0	22.6	102	50.6	3.55	2.33	0.89	3.07	0.79	0.32	7.6	1.54
RDD284967		0.03	0.6	3	0.2	5.6	10	12.1	0.95	0.47	0.30	1.13	0.18	0.05	4.5	0.95
RDD284968		0.02	0.4	2	0.1	4.3	8	6.1	0.74	0.37	0.28	0.86	0.14	0.04	3.2	0.69
RDD284969		0.02	0.8	2	0.2	3.5	8	8.2	0.58	0.28	0.31	0.78	0.11	0.03	3.0	0.65
RDD284970		0.02	0.6	2	0.2	3.3	8	4.7	0.58	0.25	0.37	0.75	0.10	0.03	2.9	0.66
RDD284971		0.02	0.5	2	0.2	6.3	9	5.3	1.12	0.52	0.49	1.36	0.20	0.05	4.2	0.89
RDD284972		0.02	0.2	2	0.2	0.8	<2	12.8	0.13	0.10	<0.03	0.09	0.03	0.02	0.4	0.12
RDD284973		<0.02	0.3	3	0.2	10.4	12	4.2	1.98	0.82	0.54	2.39	0.35	0.08	5.1	1.02
RDD284974		<0.02	0.3	1	0.3	4.1	9	5.4	0.74	0.35	0.41	0.95	0.14	0.03	3.2	0.71
RDD284975		<0.02	0.5	3	0.3	5.1	12	9.1	0.92	0.47	0.37	1.19	0.18	0.05	4.7	1.05
RDD284976		1.52	2.6	70	2.0	40.4	12	155.0	7.19	4.25	1.53	8.14	1.47	0.62	61.1	16.25
RDD284977		1.82	2.3	64	2.0	39.6	9	151.5	7.16	4.25	1.80	8.02	1.47	0.64	57.0	15.10
RDD284978		2.57	2.0	64	1.9	38.6	31	146.5	6.81	4.12	1.81	7.54	1.38	0.60	54.9	14.25
RDD284979		2.53	2.0	53	1.7	35.2	65	131.5	6.28	3.76	1.75	6.78	1.29	0.55	49.8	13.65
RDD284980		2.23	1.9	47	1.5	43.8	85	119.0	6.94	4.10	1.84	7.51	1.46	0.55	46.0	12.40
RDD284981		2.36	1.3	45	1.3	50.7	74	115.0	7.85	4.77	2.06	8.41	1.65	0.64	45.9	12.60
RDD284982		2.32	2.3	67	2.2	55.5	25	153.0	10.05	5.84	2.34	10.70	2.01	0.74	67.5	17.30
RDD284983		2.10	6.5	76	2.3	40.3	216	169.0	7.61	4.52	1.75	8.29	1.55	0.64	56.4	14.90
RDD284984		1.09	4.0	70	2.3	31.0	9	155.0	5.76	3.51	1.21	6.18	1.19	0.54	44.5	12.80
RDD284985		1.49	1.6	60	1.9	33.7	46	133.0	5.93	3.61	1.35	6.36	1.20	0.52	38.3	11.15
RDD284986		2.71	1.5	58	1.3	27.1	100	112.0	4.51	2.76	1.24	4.88	0.93	0.43	34.1	10.20
RDD284987		2.08	4.4	50	1.1	21.1	67	104.0	3.69	2.35	0.85	3.75	0.76	0.34	24.8	6.75
RDD284988		0.45	1.6	34	1.3	16.2	34	74.2	2.77	1.70	0.65	2.95	0.58	0.26	19.3	5.19
RDD284989		0.52	1.2	37	0.7	16.8	37	73.8	2.87	1.78	0.68	2.98	0.61	0.27	20.3	5.54
RDD284990																



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 6 – E

Total # Pages: 9 (A – E)

Plus Appendix Pages

Finalized Date: 5–MAR–2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Sm	Tb	Tm	Yb
		ppm	ppm	ppm	ppm
		0.03	0.01	0.01	0.03
RDD284951		0.66	0.09	0.04	0.27
RDD284952		0.58	0.07	0.04	0.25
RDD284953		3.85	0.50	0.27	1.73
RDD284954		6.99	0.87	0.46	3.06
RDD284955		6.26	0.75	0.43	2.88
RDD284956		7.85	0.94	0.50	3.11
RDD284957		7.26	0.86	0.47	3.14
RDD284958		7.03	0.92	0.48	3.29
RDD284959		6.19	0.78	0.40	2.72
RDD284960		6.73	0.84	0.46	3.19
RDD284961		8.56	1.15	0.58	3.82
RDD284962		5.89	0.76	0.43	2.90
RDD284963		6.77	0.85	0.48	3.08
RDD284964		1.20	0.16	0.07	0.39
RDD284965					
RDD284966		2.39	0.55	0.33	2.15
RDD284967		1.30	0.17	0.06	0.38
RDD284968		0.97	0.13	0.04	0.26
RDD284969		0.86	0.11	0.04	0.22
RDD284970		0.83	0.10	0.03	0.21
RDD284971		1.33	0.20	0.06	0.35
RDD284972		0.08	0.02	0.02	0.13
RDD284973		2.11	0.37	0.10	0.59
RDD284974		0.98	0.14	0.04	0.25
RDD284975		1.19	0.17	0.06	0.35
RDD284976		10.40	1.21	0.59	4.09
RDD284977		9.82	1.21	0.57	4.02
RDD284978		9.26	1.13	0.55	3.80
RDD284979		8.38	1.04	0.51	3.54
RDD284980		8.78	1.15	0.56	3.68
RDD284981		9.11	1.30	0.64	4.15
RDD284982		11.65	1.73	0.78	5.03
RDD284983		9.79	1.28	0.61	4.28
RDD284984		7.65	0.98	0.48	3.54
RDD284985		7.17	0.98	0.49	3.36
RDD284986		6.15	0.75	0.38	2.68
RDD284987		4.64	0.60	0.31	2.36
RDD284988		3.57	0.46	0.24	1.77
RDD284989		3.71	0.46	0.25	1.74
RDD284990					



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Page: 7 - A

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg	PUL-QC Pass75um %	Au-ICP21 Au ppm	ME-XRF15b Sn %	ME-MS61r Ag ppm	ME-MS61r Al %	ME-MS61r As ppm	ME-MS61r Ba ppm	ME-MS61r Be ppm	ME-MS61r Bi ppm	ME-MS61r Ca %	ME-MS61r Cd ppm	ME-MS61r Ce ppm	ME-MS61r Co ppm	ME-MS61r Cr ppm
		0.02	0.01	0.001	0.005	0.01	0.01	0.2	10	0.05	0.01	0.01	0.02	0.01	0.1	1
RDD284991		0.07		0.002		0.08	7.88	1.0	550	2.12	0.01	5.71	0.12	58.3	43.9	150
RDD284992		1.84		0.001	<0.005	0.01	2.55	<0.2	10	0.68	0.05	19.90	<0.02	28.5	4.7	13
RDD284993		1.97		0.001	<0.005	<0.01	2.37	7.7	60	0.94	0.05	21.9	<0.02	29.9	12.4	16
RDD284994		1.84		0.001	0.005	0.01	3.20	0.3	80	0.81	0.05	17.65	<0.02	36.4	7.9	19
RDD284995		1.68	97.0	0.001	<0.005	0.02	4.42	0.6	70	1.63	0.11	14.80	<0.02	53.4	5.5	21
RDD284996		2.18		0.001	0.015	0.03	5.03	2.1	80	1.92	0.11	14.00	<0.02	60.5	5.5	24
RDD284997		1.95		0.001	0.005	0.03	2.73	24.8	50	0.91	0.12	22.0	<0.02	38.0	5.3	15
RDD284998		1.77		0.001	0.018	0.03	3.06	0.5	100	1.34	0.49	25.3	<0.02	37.0	2.2	16
RDD284999		1.91		0.001	0.031	0.06	4.63	10.4	60	2.43	1.22	15.55	<0.02	52.4	2.9	24
RDD285000		1.85		0.001	0.010	0.04	3.50	1.1	90	1.00	0.21	16.45	<0.02	43.3	4.3	17
RDD285001		1.75		0.001	<0.005	0.08	1.57	<0.2	20	0.52	0.08	19.20	<0.02	23.1	2.6	9
RDD285002		1.33		0.001	<0.005	<0.01	1.77	<0.2	10	0.50	0.14	18.35	<0.02	22.6	2.2	9
RDD285003		2.34		0.004	0.031	0.22	4.01	719	80	4.42	10.85	10.35	<0.02	56.6	18.2	22
RDD285004		1.52		0.002	<0.005	0.02	0.07	1.2	10	<0.05	0.04	0.13	<0.02	1.66	0.3	10
RDD285005		1.93		0.003	0.038	0.12	3.82	95.8	90	2.73	0.99	7.52	<0.02	62.7	9.6	21
RDD285006		1.91		0.002	0.008	0.15	5.37	19.1	210	2.37	1.86	0.63	<0.02	82.8	11.6	46
RDD285007		1.80		0.003	0.006	0.23	5.44	12.6	200	2.39	0.29	0.84	<0.02	82.1	7.6	44
RDD285008		1.71		0.003	0.006	0.20	4.79	14.0	180	1.84	0.28	1.39	0.03	78.8	6.9	39
RDD285009		1.74		0.002	0.009	0.14	5.42	9.8	180	2.05	0.26	1.41	<0.02	83.0	8.7	41
RDD285010		0.66		0.012	<0.005	0.12	4.36	313	110	2.21	0.31	3.01	0.18	74.9	8.9	34
RDD285011		1.03		0.002	<0.005	0.09	4.58	23.8	140	2.12	0.40	2.24	<0.02	78.5	8.3	34
RDD285012		1.77		0.001	0.008	0.10	5.18	8.8	200	1.93	0.62	0.42	0.06	86.7	11.6	42
RDD285013		1.90		0.001	<0.005	0.03	0.26	<0.2	<10	0.20	0.08	21.6	0.04	6.00	2.0	3
RDD285014		2.17		0.001	<0.005	<0.01	0.14	<0.2	<10	0.17	0.02	20.6	0.02	4.83	1.1	2
RDD285015		<0.02			1.160											
RDD285016		0.07		0.002		0.01	7.58	1.2	510	2.05	0.02	5.52	0.13	60.4	44.6	141
RDD285017		1.57		0.001	<0.005	<0.01	0.14	<0.2	<10	0.21	0.05	21.5	0.02	5.47	1.1	2
RDD285018		1.89		0.001	<0.005	<0.01	0.17	0.8	<10	0.19	0.06	21.9	0.02	5.09	1.4	2
RDD285019		1.36		0.001	<0.005	<0.01	0.21	0.8	<10	0.18	0.10	20.9	0.02	5.33	2.1	3
RDD285020		1.43		0.002	<0.005	0.02	1.40	4.6	80	0.51	0.11	0.75	<0.02	31.3	1.9	17
RDD285021		2.21		0.001	0.009	0.02	0.57	1.9	20	0.26	0.15	12.50	<0.02	15.85	2.6	6
RDD285022		1.29		0.001	0.009	0.06	0.58	3.4	10	0.28	0.22	10.40	<0.02	16.00	11.8	9
RDD285023		1.17		0.001	<0.005	0.07	0.08	3.1	10	<0.05	0.08	0.22	0.04	2.41	0.5	13
RDD285024		1.25		0.001	<0.005	0.02	0.59	1.3	30	0.27	0.03	2.24	<0.02	19.90	1.1	12
RDD285025		1.41		0.001	<0.005	<0.01	0.34	0.9	<10	0.23	0.01	20.4	<0.02	9.42	1.5	4
RDD285026		1.96		0.001	<0.005	0.01	1.74	<0.2	20	0.73	0.02	20.8	0.02	32.7	2.1	14
RDD285027		1.79		0.001	<0.005	0.02	2.94	0.2	70	1.02	0.06	18.15	0.02	51.1	2.9	27
RDD285028		1.13		0.002	<0.005	0.01	1.88	<0.2	30	0.82	0.13	19.65	0.04	30.8	5.5	15
RDD285029		2.08		0.001	0.009	0.01	7.16	9.5	420	2.75	0.10	2.69	<0.02	105.5	5.7	62
RDD285030		0.77		0.001	0.017	0.18	6.20	1.7	50	2.24	0.41	12.55	<0.02	94.6	2.2	31



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Page: 7 - B

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Cs	Cu	Fe	Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Nb
		ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
		0.05	0.2	0.01	0.05	0.05	0.1	0.005	0.01	0.5	0.2	0.01	5	0.05	0.01
RDD284991		1.08	43.6	8.10	21.9	0.17	4.8	0.068	1.70	28.9	12.5	4.68	1155	4.28	2.34
RDD284992		4.67	17.6	2.03	6.44	0.09	1.4	0.279	0.09	13.8	52.3	8.40	1135	0.06	0.07
RDD284993		8.19	4.6	1.51	6.06	0.10	1.3	0.234	0.67	14.5	22.2	6.26	1075	0.07	0.47
RDD284994		24.9	9.7	2.24	8.68	0.11	1.8	0.195	1.62	17.5	47.3	7.51	1055	0.09	0.27
RDD284995		23.7	12.7	2.60	11.20	0.12	2.5	0.208	1.31	26.5	50.7	7.86	1100	0.11	0.60
RDD284996		11.55	14.8	3.12	13.00	0.13	2.7	0.419	1.36	29.7	69.4	7.17	1510	0.14	0.11
RDD284997		21.7	26.2	2.55	6.94	0.10	1.6	0.261	1.15	18.6	33.4	5.22	1565	0.07	0.11
RDD284998		8.56	10.0	3.30	7.24	0.11	1.4	2.77	1.23	17.7	19.0	1.75	4720	0.09	0.28
RDD284999		14.15	15.4	4.89	11.45	0.15	2.1	4.01	1.26	25.2	42.8	4.85	7010	0.09	0.05
RDD285000		32.3	18.2	4.19	8.79	0.09	2.0	0.633	1.44	21.2	54.0	6.65	2810	0.09	0.06
RDD285001		15.10	3.8	5.13	4.33	0.10	0.9	0.428	0.51	10.8	14.9	8.55	4690	<0.05	0.02
RDD285002		14.05	1.5	4.59	4.82	0.09	1.0	0.589	0.41	10.4	13.9	8.18	5420	<0.05	0.02
RDD285003		51.8	104.0	10.65	11.65	0.15	2.4	3.48	0.98	29.2	73.4	4.46	5530	0.18	0.05
RDD285004		0.14	2.8	0.53	0.25	<0.05	0.6	0.024	0.03	0.8	1.9	0.05	90	0.49	0.01
RDD285005		24.8	99.5	9.84	10.95	0.16	2.9	3.10	1.11	33.6	55.1	5.85	4000	0.16	0.10
RDD285006		17.70	34.4	3.27	13.50	0.19	4.1	0.379	2.68	41.2	32.2	1.05	237	0.75	0.07
RDD285007		10.05	16.4	2.37	13.95	0.19	4.0	0.134	2.62	40.5	25.9	0.77	202	0.59	0.06
RDD285008		6.87	12.7	2.96	12.30	0.18	3.6	0.091	2.33	37.2	20.9	0.54	204	0.75	0.05
RDD285009		10.80	14.4	2.23	14.85	0.12	3.8	0.064	2.58	41.4	24.0	0.76	265	0.58	0.05
RDD285010		17.30	18.7	2.26	12.60	0.12	3.1	0.140	1.80	36.7	43.5	1.06	536	0.67	0.03
RDD285011		15.60	21.9	2.65	13.20	0.16	3.2	0.048	2.04	36.1	30.3	0.74	290	0.59	0.03
RDD285012		13.35	16.9	2.32	14.30	0.13	4.0	0.067	2.53	42.8	39.0	1.69	173	0.69	0.11
RDD285013		0.47	4.5	2.41	0.79	0.05	0.2	0.087	0.02	2.3	6.0	10.05	1755	0.08	0.01
RDD285014		0.28	1.5	2.04	0.36	<0.05	0.1	0.104	0.01	1.6	2.7	10.95	1640	0.05	0.01
RDD285015															
RDD285016		1.16	40.4	7.88	22.3	0.16	4.6	0.068	1.64	29.3	11.8	4.47	1120	4.09	2.28
RDD285017		0.18	1.8	1.88	0.34	<0.05	0.1	0.080	0.01	2.2	2.8	11.35	1430	<0.05	0.01
RDD285018		0.22	2.3	1.96	0.49	<0.05	0.2	0.076	0.01	1.8	3.8	11.80	1255	0.05	0.01
RDD285019		1.04	3.3	2.14	0.57	<0.05	0.2	0.065	0.03	1.9	3.9	11.20	1440	<0.05	0.01
RDD285020		7.36	4.6	1.05	3.37	0.06	1.5	0.054	0.85	17.6	13.0	0.97	284	0.44	0.07
RDD285021		1.83	14.1	2.07	1.70	<0.05	0.7	0.314	0.16	8.0	12.4	6.85	1335	0.11	0.03
RDD285022		1.24	85.2	4.26	2.80	0.05	0.7	0.617	0.09	7.7	11.2	5.80	1280	0.20	0.03
RDD285023		0.15	3.7	0.57	0.37	<0.05	0.9	0.110	0.02	1.2	2.0	0.11	91	0.57	0.01
RDD285024		2.54	7.6	1.41	1.74	0.05	0.4	0.271	0.22	10.7	9.6	2.07	506	0.37	0.03
RDD285025		1.72	1.8	1.76	0.88	0.05	0.3	0.083	0.05	3.9	9.6	10.90	1350	<0.05	0.01
RDD285026		6.23	4.5	2.16	4.49	0.06	1.3	0.054	0.29	15.3	26.1	10.45	1305	0.05	0.02
RDD285027		18.90	2.8	1.80	7.91	0.09	2.3	0.108	1.14	24.6	39.1	9.03	822	0.07	0.03
RDD285028		11.95	14.4	2.29	5.48	0.08	1.4	0.114	0.70	14.6	24.1	10.35	1050	0.12	0.04
RDD285029		19.75	19.2	1.90	19.65	0.22	4.0	0.117	3.60	51.7	28.1	1.84	230	0.26	0.43
RDD285030		48.0	1.4	3.31	14.60	0.19	3.6	0.581	1.82	45.8	30.8	4.90	1975	0.55	0.33



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 7 - C

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ni	P	Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th
		ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.2	10	0.5	0.1	0.002	0.01	0.05	0.1	1	0.2	0.2	0.05	0.05	0.01
RDD284991		147.0	2590	3.6	40.4	<0.002	0.04	0.09	20.6	<1	1.7	789	2.99	<0.05	3.50
RDD284992		8.2	310	1.1	4.2	<0.002	0.06	1.07	5.1	<1	1.1	102.5	0.25	0.05	4.19
RDD284993		10.2	320	0.9	33.6	<0.002	0.01	0.64	4.8	<1	4.3	139.5	0.24	0.06	4.18
RDD284994		9.8	390	0.8	82.8	<0.002	0.08	1.19	6.7	<1	11.2	95.2	0.36	<0.05	5.70
RDD284995		10.2	450	1.3	110.5	<0.002	0.12	1.74	8.5	<1	26.9	118.0	0.48	0.06	7.64
RDD284996		11.6	500	9.8	183.5	<0.002	0.13	3.78	9.5	<1	83.8	99.3	0.53	<0.05	8.78
RDD284997		8.6	290	4.0	144.0	<0.002	0.51	1.34	5.4	<1	30.7	133.0	0.29	<0.05	4.79
RDD284998		9.5	360	2.0	167.5	<0.002	0.18	2.80	5.9	<1	164.0	181.5	0.32	<0.05	5.33
RDD284999		9.2	440	4.5	242	<0.002	0.12	3.45	8.7	<1	253	57.2	0.54	<0.05	8.20
RDD285000		9.4	330	2.7	208	<0.002	0.41	2.00	6.9	<1	78.8	81.4	0.43	<0.05	6.17
RDD285001		6.0	230	0.7	43.0	<0.002	0.07	0.52	3.0	<1	4.8	99.0	0.17	<0.05	2.74
RDD285002		4.4	220	0.6	49.4	<0.002	0.07	0.49	3.5	<1	7.2	97.5	0.20	<0.05	3.10
RDD285003		7.7	390	8.9	216	<0.002	2.46	7.99	6.9	2	168.5	111.0	0.55	0.24	7.36
RDD285004		0.9	10	3.5	1.5	<0.002	0.01	0.21	0.2	<1	0.5	3.4	0.08	<0.05	0.34
RDD285005		6.3	1220	9.0	245	<0.002	2.52	7.47	5.6	1	254	47.1	0.77	<0.05	8.37
RDD285006		18.1	700	10.3	204	<0.002	1.65	4.13	8.1	<1	14.8	16.0	0.88	<0.05	12.80
RDD285007		13.6	320	12.0	152.5	<0.002	1.69	5.24	8.0	<1	9.4	13.8	0.98	<0.05	12.50
RDD285008		13.3	350	11.6	125.5	<0.002	2.65	5.84	7.0	<1	3.7	16.5	0.80	<0.05	11.90
RDD285009		14.0	880	7.6	159.0	0.003	1.20	6.62	8.9	<1	5.0	14.6	0.94	<0.05	12.05
RDD285010		11.0	450	25.0	178.5	0.004	0.46	28.3	7.3	<1	12.2	16.0	0.78	<0.05	9.76
RDD285011		13.6	5710	7.8	172.0	0.002	0.70	11.10	8.9	<1	5.7	17.0	0.73	<0.05	10.20
RDD285012		15.8	750	12.8	136.0	0.003	0.85	2.01	8.3	1	8.1	19.6	1.01	<0.05	12.50
RDD285013		2.1	320	4.6	1.3	0.002	0.40	0.26	0.7	<1	2.2	106.0	<0.05	<0.05	0.54
RDD285014		1.5	190	0.5	0.5	<0.002	<0.01	0.26	0.7	<1	0.7	118.5	<0.05	<0.05	0.27
RDD285015															
RDD285016		139.5	2460	3.3	36.8	0.003	0.04	0.10	20.1	<1	1.8	760	2.82	<0.05	3.50
RDD285017		1.5	200	<0.5	0.4	0.002	<0.01	0.19	0.3	<1	0.4	119.5	<0.05	<0.05	0.28
RDD285018		1.8	410	<0.5	0.4	0.002	0.02	0.15	0.5	<1	0.3	132.0	<0.05	<0.05	0.44
RDD285019		2.7	490	<0.5	4.2	<0.002	0.07	0.19	0.6	<1	0.9	118.5	<0.05	<0.05	0.52
RDD285020		4.1	1000	3.4	86.8	0.002	0.06	0.51	1.6	<1	11.1	16.8	0.27	<0.05	3.69
RDD285021		1.9	830	2.7	17.0	<0.002	0.29	0.76	1.1	<1	36.4	47.4	0.14	<0.05	1.73
RDD285022		4.6	1940	1.8	7.6	<0.002	1.36	0.82	1.1	1	64.3	18.3	0.16	<0.05	1.75
RDD285023		1.2	30	15.5	1.3	<0.002	0.01	0.33	0.4	<1	1.1	4.1	0.08	<0.05	0.51
RDD285024		2.7	3150	4.2	22.4	<0.002	0.02	0.65	0.8	<1	34.4	10.1	0.07	<0.05	2.45
RDD285025		1.9	1030	0.5	5.7	<0.002	<0.01	0.29	0.7	<1	10.0	96.6	0.07	<0.05	0.88
RDD285026		4.1	1580	0.5	15.6	<0.002	0.03	0.88	3.4	<1	2.2	116.0	0.28	<0.05	3.76
RDD285027		8.6	1920	2.2	78.9	<0.002	<0.01	2.45	6.1	<1	7.4	99.5	0.50	<0.05	6.63
RDD285028		11.2	1110	1.3	54.4	<0.002	0.10	0.85	5.1	<1	10.2	118.0	0.29	<0.05	4.04
RDD285029		19.9	1830	4.5	237	<0.002	0.22	1.70	14.3	<1	21.1	71.2	0.89	<0.05	14.95
RDD285030		10.8	1190	24.5	373	0.002	<0.01	1.74	12.8	<1	113.0	92.5	0.76	<0.05	13.35



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 7 - D

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ti	U	V	W	Y	Zn	Zr	Dy	Er	Eu	Gd	Ho	Lu	Nd	Pr
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.02	0.1	1	0.1	0.1	2	0.5	0.05	0.03	0.03	0.05	0.01	0.01	0.1	0.03
RDD284991		0.14	1.4	197	0.2	19.4	112	207	4.04	1.91	1.86	4.89	0.75	0.23	28.1	7.38
RDD284992		0.05	1.1	24	0.8	13.6	23	51.8	2.19	1.35	0.46	2.36	0.46	0.20	14.0	3.65
RDD284993		0.25	1.8	24	1.2	13.4	21	49.2	2.21	1.31	0.61	2.40	0.47	0.20	14.7	3.95
RDD284994		0.75	0.9	30	0.6	16.1	32	65.7	2.63	1.68	0.60	2.82	0.57	0.25	17.6	4.61
RDD284995		0.97	1.1	43	1.8	19.6	45	89.7	3.48	2.06	0.86	3.68	0.72	0.31	25.0	6.89
RDD284996		1.37	1.2	49	1.4	21.7	103	90.0	3.76	2.31	1.02	4.05	0.77	0.34	29.2	7.91
RDD284997		1.23	0.9	26	0.6	14.0	35	55.9	2.33	1.41	0.62	2.54	0.47	0.21	17.8	4.83
RDD284998		1.47	1.0	29	0.9	14.8	44	48.6	2.51	1.51	0.56	2.73	0.52	0.22	17.9	4.72
RDD284999		1.68	1.2	46	1.5	20.9	75	70.7	3.46	2.34	0.99	3.69	0.74	0.36	24.5	6.60
RDD285000		1.72	1.1	33	1.0	16.8	47	71.0	2.81	1.67	0.81	3.03	0.58	0.26	20.3	5.49
RDD285001		0.38	0.9	16	0.5	9.0	26	34.3	1.54	0.88	0.68	2.09	0.30	0.12	12.0	3.11
RDD285002		0.45	0.7	17	0.7	11.1	25	37.4	1.87	1.09	0.63	2.08	0.36	0.15	11.8	3.00
RDD285003		1.87	1.5	34	5.7	20.0	96	80.3	3.38	2.07	1.78	3.93	0.71	0.29	25.0	6.97
RDD285004		0.04	0.2	4	0.2	1.4	4	21.6	0.26	0.19	0.03	0.32	0.07	0.03	0.6	0.17
RDD285005		2.49	1.8	31	5.6	22.7	94	101.0	4.06	2.31	1.53	4.66	0.81	0.31	27.2	7.58
RDD285006		1.46	2.6	58	2.2	20.0	9	137.5	3.69	2.37	0.93	4.03	0.77	0.40	32.6	10.35
RDD285007		0.83	2.3	57	1.9	19.4	5	142.5	3.49	2.24	0.87	3.83	0.76	0.39	33.9	10.70
RDD285008		0.68	2.1	50	1.6	19.8	15	126.0	3.55	2.20	0.89	4.04	0.73	0.35	32.8	10.35
RDD285009		0.94	2.3	57	2.8	23.1	7	139.0	4.28	2.70	0.94	4.49	0.89	0.43	31.6	9.41
RDD285010		1.16	1.9	44	4.2	21.8	89	113.5	3.88	2.30	0.75	4.20	0.81	0.36	29.7	8.94
RDD285011		1.15	3.9	48	3.3	35.2	7	118.0	7.16	3.57	1.32	9.44	1.35	0.45	37.6	9.99
RDD285012		0.67	2.3	56	1.9	21.7	21	139.5	4.05	2.58	0.72	4.31	0.84	0.40	32.2	9.85
RDD285013		<0.02	0.2	3	0.2	6.4	16	9.6	1.21	0.56	0.38	1.38	0.23	0.06	4.0	0.87
RDD285014		<0.02	0.2	2	0.1	7.0	14	5.9	1.33	0.56	0.34	1.54	0.23	0.05	3.6	0.78
RDD285015																
RDD285016		0.11	1.2	189	0.2	20.2	108	204	4.32	1.99	1.78	5.33	0.79	0.22	27.4	7.30
RDD285017		<0.02	0.1	1	0.1	4.1	12	5.7	0.77	0.33	0.32	0.99	0.13	0.03	3.3	0.75
RDD285018		<0.02	0.2	2	0.1	4.5	12	9.8	0.84	0.39	0.28	1.06	0.16	0.04	3.4	0.74
RDD285019		0.03	0.2	3	0.2	4.9	11	10.8	0.95	0.42	0.32	1.18	0.17	0.05	3.5	0.77
RDD285020		0.59	0.7	12	0.6	6.0	9	46.1	1.21	0.67	0.39	1.56	0.24	0.11	10.9	3.25
RDD285021		0.12	0.5	5	0.6	7.0	19	27.1	1.28	0.70	0.44	1.51	0.24	0.09	6.9	1.79
RDD285022		0.06	0.6	5	0.5	8.9	23	26.6	1.43	0.83	0.39	1.73	0.30	0.13	7.3	1.80
RDD285023		<0.02	0.3	5	0.4	1.9	19	31.6	0.33	0.24	0.05	0.24	0.07	0.04	1.0	0.26
RDD285024		0.14	1.2	4	0.4	7.9	17	16.9	1.41	0.78	0.41	1.81	0.28	0.11	8.8	2.24
RDD285025		0.04	0.4	3	0.2	5.7	12	14.1	0.97	0.53	0.30	1.16	0.20	0.07	4.6	1.12
RDD285026		0.09	0.9	13	0.4	17.1	16	52.2	2.89	1.68	0.64	3.19	0.59	0.22	15.7	3.89
RDD285027		0.44	1.5	22	0.8	26.5	27	83.1	4.30	2.65	0.87	4.60	0.92	0.36	24.3	6.16
RDD285028		0.34	2.5	16	0.6	18.0	19	52.0	3.04	1.79	0.76	3.30	0.60	0.25	15.2	3.78
RDD285029		1.54	2.1	61	1.9	43.5	19	148.5	7.87	4.47	1.64	8.58	1.60	0.64	53.3	13.90
RDD285030		2.55	1.7	55	90.5	37.9	100	129.5	6.90	3.94	1.60	7.60	1.41	0.53	47.8	12.55



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 7 – E

Total # Pages: 9 (A – E)

Plus Appendix Pages

Finalized Date: 5–MAR–2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Sm	Tb	Tm	Yb
		ppm	ppm	ppm	ppm
		0.03	0.01	0.01	0.03
RDD284991		5.57	0.72	0.23	1.56
RDD284992		2.73	0.37	0.18	1.31
RDD284993		2.87	0.36	0.18	1.27
RDD284994		3.46	0.44	0.23	1.64
RDD284995		4.66	0.59	0.29	2.05
RDD284996		5.29	0.63	0.32	2.22
RDD284997		3.24	0.39	0.19	1.33
RDD284998		3.40	0.42	0.21	1.41
RDD284999		4.53	0.58	0.33	2.27
RDD285000		3.84	0.47	0.24	1.71
RDD285001		2.59	0.28	0.11	0.79
RDD285002		2.47	0.32	0.14	0.97
RDD285003		4.78	0.60	0.28	1.90
RDD285004		0.14	0.06	0.03	0.20
RDD285005		5.46	0.70	0.30	2.09
RDD285006		5.05	0.63	0.34	2.55
RDD285007		5.38	0.59	0.34	2.47
RDD285008		5.48	0.62	0.31	2.28
RDD285009		5.52	0.70	0.41	2.71
RDD285010		5.53	0.64	0.35	2.26
RDD285011		9.53	1.34	0.48	3.26
RDD285012		5.66	0.66	0.38	2.59
RDD285013		1.31	0.22	0.08	0.47
RDD285014		1.42	0.25	0.07	0.42
RDD285015					
RDD285016		5.83	0.78	0.26	1.54
RDD285017		0.97	0.14	0.04	0.24
RDD285018		1.04	0.16	0.05	0.29
RDD285019		1.13	0.17	0.06	0.33
RDD285020		1.95	0.22	0.10	0.66
RDD285021		1.66	0.22	0.09	0.60
RDD285022		1.86	0.25	0.12	0.80
RDD285023		0.21	0.05	0.04	0.28
RDD285024		2.00	0.25	0.11	0.70
RDD285025		1.20	0.17	0.07	0.44
RDD285026		3.40	0.48	0.23	1.43
RDD285027		5.03	0.71	0.38	2.34
RDD285028		3.41	0.50	0.26	1.65
RDD285029		10.20	1.29	0.66	4.17
RDD285030		9.13	1.14	0.56	3.55



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD  
PO BOX 20  
ZEEHAN TAS 7469

Page: 8 - A  
Total # Pages: 9 (A - E)  
Plus Appendix Pages  
Finalized Date: 5-MAR-2025  
Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg 0.02	PUL-QC Pass75um % 0.01	Au-ICP21 Au ppm 0.001	ME-XRF15b Sn % 0.005	ME-MS61r Ag ppm 0.01	ME-MS61r Al % 0.01	ME-MS61r As ppm 0.2	ME-MS61r Ba ppm 10	ME-MS61r Be ppm 0.05	ME-MS61r Bi ppm 0.01	ME-MS61r Ca % 0.01	ME-MS61r Cd ppm 0.02	ME-MS61r Ce ppm 0.01	ME-MS61r Co ppm 0.1	ME-MS61r Cr ppm 1
RDD285031		1.93	93.0	0.001	0.024	0.02	5.32	27.7	30	1.57	0.11	12.65	<0.02	79.2	4.7	28
RDD285032		2.32		0.001	0.029	0.05	5.59	17.2	60	1.76	0.31	12.25	0.10	91.7	3.3	28
RDD285033		1.49	99.0	0.001	0.010	<0.01	7.58	3.1	300	3.04	0.12	2.08	0.02	107.5	2.9	55
RDD285034		1.97	97.0	0.002	0.008	<0.01	7.80	4.0	310	3.30	0.17	0.87	<0.02	106.5	3.3	58
RDD285035		2.55	87.0	0.001	0.011	<0.01	7.48	5.5	330	3.37	0.11	1.05	<0.02	93.8	3.8	59
RDD285036		1.92		0.001	0.026	0.04	4.44	2.8	80	1.52	0.37	16.55	<0.02	53.7	4.2	20
RDD285037		1.29	94.0	<0.001	0.006	0.02	2.51	0.9	20	0.42	0.15	21.5	<0.02	34.6	4.0	12
RDD285038		2.06		<0.001	0.012	0.02	5.07	1.9	40	0.76	0.07	7.19	<0.02	78.2	7.1	21
RDD285039		2.27		0.001	<0.005	0.01	2.06	0.5	40	0.44	0.12	17.65	0.03	33.9	3.1	10
RDD285040		<0.02			1.120											
RDD285041		0.07		0.004		0.04	5.98	0.7	440	0.87	0.05	2.39	0.05	37.3	9.7	47
RDD285042		1.94		0.001	<0.005	0.01	2.90	3.0	40	0.54	0.07	13.85	<0.02	37.8	4.9	12
RDD285043		1.94	96.0	0.001	<0.005	0.01	1.86	0.2	10	0.30	0.06	16.30	0.02	33.0	3.8	9
RDD285044		2.02		0.001	<0.005	0.01	3.28	<0.2	10	0.39	0.04	14.45	0.02	53.2	6.3	13
RDD285045		1.99		0.001	<0.005	0.01	2.25	2.0	10	0.33	0.16	17.05	<0.02	34.0	4.4	8
RDD285046		1.67		<0.001	<0.005	0.01	2.26	0.3	10	0.36	0.07	16.00	<0.02	31.5	4.5	10
RDD285047		2.23		<0.001	<0.005	0.03	2.84	7.7	20	0.43	0.19	14.60	<0.02	44.9	7.6	14
RDD285048		1.38		0.001	<0.005	0.02	0.08	2.0	10	<0.05	0.04	0.30	<0.02	1.70	0.4	5
RDD285049		1.88		0.001	0.005	0.02	3.45	6.1	40	0.66	0.75	12.15	<0.02	52.3	7.9	16
RDD285050		1.32		0.001	0.007	0.02	3.10	1.6	20	0.55	0.25	12.85	<0.02	42.1	9.3	13
RDD285051		1.80		0.001	0.023	0.11	4.16	7.1	30	0.79	0.36	12.55	<0.02	60.5	5.3	18
RDD285052		1.93		0.001	0.019	0.05	4.33	1.4	20	0.84	0.32	14.85	<0.02	55.3	2.0	19
RDD285053		2.56		0.003	0.013	0.03	3.14	1.4	60	0.67	0.35	15.80	<0.02	44.9	2.8	13
RDD285054		2.42		0.001	0.007	0.02	2.88	1.9	90	0.50	0.26	16.50	<0.02	39.0	5.1	13
RDD285055		2.54		0.001	0.017	0.05	3.82	4.6	60	1.26	0.37	15.65	<0.02	55.5	6.5	17
RDD285056		1.59		0.002	0.010	0.08	7.48	41.5	390	3.11	0.23	2.28	<0.02	110.0	9.6	89
RDD285057		1.69		0.001	0.022	0.02	4.69	24.1	80	0.94	0.14	8.41	<0.02	66.4	5.8	26
RDD285058		2.11		0.001	0.019	0.21	5.79	8.0	20	1.81	0.77	14.65	2.53	68.9	3.1	26
RDD285059		1.78		0.001	0.014	0.12	5.89	1.9	20	1.62	0.27	13.80	0.33	63.1	3.0	25
RDD285060		1.81		0.001	0.014	0.05	5.52	1.8	40	2.11	0.18	12.90	0.28	39.5	2.3	25
RDD285061		2.39		<0.001	0.013	0.03	6.77	1.6	30	3.18	0.11	13.05	<0.02	73.1	2.2	29
RDD285062		1.33		0.001	0.028	0.03	5.72	4.6	300	1.91	0.16	6.40	<0.02	82.0	8.3	36
RDD285063		1.81		0.001	0.021	0.05	5.97	4.9	180	2.18	0.13	6.63	<0.02	78.5	8.1	35
RDD285064		1.67		0.001	0.021	0.08	5.70	4.3	220	2.07	0.73	5.84	<0.02	74.0	19.6	32
RDD285065		<0.02			2.50											
RDD285066		0.07		0.002		0.04	8.06	2.0	550	2.05	0.02	5.77	0.13	57.3	45.2	146
RDD285067		1.79		<0.001	0.016	<0.01	5.03	21.8	80	1.34	0.11	8.61	<0.02	83.9	5.5	27
RDD285068		2.06		<0.001	0.020	0.07	4.94	51.5	50	1.23	0.49	8.94	<0.02	58.3	12.2	33
RDD285069		1.87		0.001	0.006	0.08	4.18	5.1	20	0.65	0.25	8.80	0.07	38.7	12.2	15
RDD285070		1.02		0.001	0.014	0.11	4.44	3.2	20	0.75	0.21	8.89	<0.02	46.9	9.9	17





Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Page: 8 - B

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Cs	Cu	Fe	Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb
		ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm
		0.05	0.2	0.01	0.05	0.05	0.1	0.005	0.01	0.5	0.2	0.01	5	0.05	0.01	0.1
RDD285031		16.45	2.6	3.94	14.25	0.15	3.0	0.768	1.26	38.9	47.3	6.39	2080	0.61	0.14	9.4
RDD285032		24.2	4.8	4.09	13.70	0.20	3.1	0.994	1.58	44.2	41.6	6.02	2060	0.19	0.27	9.9
RDD285033		14.20	15.2	1.68	19.55	0.20	4.0	0.095	2.90	51.0	27.7	1.46	203	0.25	0.73	12.8
RDD285034		16.60	53.2	1.84	22.2	0.20	4.1	0.169	4.01	51.8	29.7	1.27	174	0.69	0.36	13.1
RDD285035		15.85	31.0	2.13	20.7	0.17	4.0	0.148	3.57	46.4	31.0	1.30	178	0.22	0.47	12.9
RDD285036		25.2	23.4	4.19	11.70	0.11	2.4	0.911	1.36	26.1	47.7	4.98	2370	0.18	0.16	7.1
RDD285037		11.10	6.1	3.31	5.51	0.07	1.3	0.326	0.38	16.0	39.1	5.42	2100	<0.05	0.28	3.6
RDD285038		50.4	2.8	5.51	13.95	0.15	2.8	0.395	1.52	36.7	53.7	9.66	1595	0.11	0.34	9.0
RDD285039		17.60	7.9	4.55	4.95	0.08	1.2	0.183	0.56	15.0	14.8	8.08	3170	0.09	0.17	3.5
RDD285040																
RDD285041		0.63	21.3	2.55	14.00	0.10	1.7	0.024	1.16	19.6	10.3	0.91	473	0.69	2.56	4.8
RDD285042		20.3	5.0	5.78	8.35	0.09	1.6	0.105	0.60	17.7	17.4	9.16	3440	0.08	0.21	4.8
RDD285043		3.88	1.6	4.61	5.96	0.07	1.1	0.123	0.09	14.1	12.0	9.46	3910	0.05	0.14	3.3
RDD285044		9.31	1.2	4.93	10.35	0.09	2.0	0.205	0.22	23.9	18.6	9.99	2560	0.07	0.36	6.0
RDD285045		6.49	3.0	4.19	6.37	0.06	1.3	0.242	0.19	16.0	12.7	10.10	2730	0.05	0.18	3.5
RDD285046		6.13	1.4	4.05	6.95	0.06	1.3	0.113	0.18	14.8	10.4	10.10	3440	0.05	0.11	3.9
RDD285047		25.6	11.1	5.11	8.27	0.10	1.6	0.232	0.78	18.3	12.4	10.45	2560	0.08	0.13	4.5
RDD285048		0.23	2.5	0.67	0.35	<0.05	0.4	0.014	0.02	0.9	1.5	0.18	119	0.40	0.01	1.1
RDD285049		44.5	4.1	4.65	8.93	0.11	2.4	0.101	1.52	21.8	18.8	10.05	1805	0.12	0.24	6.2
RDD285050		29.9	10.0	4.77	8.45	0.12	2.2	0.240	0.81	18.2	14.4	10.75	1795	0.15	0.15	7.2
RDD285051		20.5	16.9	4.31	10.35	0.12	2.9	0.695	0.97	29.3	52.5	8.97	1780	0.15	0.08	10.8
RDD285052		7.68	1.2	3.57	10.65	0.11	2.7	0.861	0.52	26.6	48.2	7.05	1890	0.12	0.05	11.1
RDD285053		30.4	5.0	3.94	7.80	0.12	2.3	0.577	1.26	19.9	24.9	8.60	2810	0.05	0.13	8.7
RDD285054		46.4	10.1	2.92	7.87	0.09	2.1	0.232	1.40	17.0	30.1	9.03	1880	0.11	0.12	7.6
RDD285055		22.3	15.4	3.72	9.70	0.12	3.0	0.984	1.02	27.5	44.7	7.93	2930	0.38	0.10	10.2
RDD285056		19.05	12.3	1.65	19.00	0.25	6.2	0.041	3.66	56.1	23.7	1.46	301	1.05	0.72	34.1
RDD285057		12.30	1.7	4.82	11.75	0.16	3.7	1.300	1.46	32.5	12.4	7.58	2020	0.45	0.61	19.0
RDD285058		8.35	1.4	4.93	15.80	0.12	3.9	1.870	0.95	33.9	32.5	4.81	3260	0.13	0.70	24.0
RDD285059		10.90	1.6	4.53	15.85	0.13	3.9	1.200	0.99	29.7	33.9	4.63	2930	0.17	0.72	18.0
RDD285060		19.40	0.9	3.83	12.45	0.09	3.8	1.420	1.15	16.9	21.5	5.93	2400	1.05	0.47	15.9
RDD285061		21.3	1.1	3.82	15.85	0.13	4.4	1.480	1.16	35.6	23.6	4.31	2660	3.25	0.83	20.9
RDD285062		7.49	28.2	3.56	14.05	0.17	4.1	0.489	2.55	40.2	4.3	4.51	1105	0.77	0.63	14.4
RDD285063		7.41	27.1	3.38	15.60	0.19	4.3	0.362	2.00	37.5	3.4	4.48	1015	0.74	0.56	15.6
RDD285064		9.33	80.1	5.86	14.50	0.16	3.8	0.360	2.22	36.1	4.9	4.11	897	0.91	0.53	15.2
RDD285065																
RDD285066		1.09	43.7	8.25	22.0	0.21	4.9	0.065	1.69	29.6	12.1	4.76	1130	4.26	2.37	46.2
RDD285067		22.7	4.1	4.16	13.00	0.16	3.9	0.994	2.20	41.7	12.2	7.66	1715	0.49	0.22	20.4
RDD285068		32.7	45.9	5.13	14.00	0.09	3.4	1.245	1.19	29.6	27.2	9.33	1715	1.60	0.17	16.3
RDD285069		13.40	54.4	5.84	13.60	0.10	2.8	0.857	0.54	16.1	64.3	12.10	1285	0.13	0.06	11.7
RDD285070		22.8	45.7	5.80	13.35	0.13	2.9	0.914	0.71	21.3	99.8	11.30	1380	0.20	0.05	13.6



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 8 - C

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ni	P	Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th
		ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.2	10	0.5	0.1	0.002	0.01	0.05	0.1	1	0.2	0.2	0.05	0.05	0.01
RDD285031		17.1	1070	3.7	244	<0.002	0.02	2.96	10.2	<1	191.0	53.8	0.61	<0.05	10.85
RDD285032		12.9	1100	5.9	313	0.002	0.06	2.47	11.9	<1	198.5	68.9	0.63	<0.05	11.60
RDD285033		16.1	750	4.2	180.0	<0.002	0.08	1.18	15.1	<1	17.2	58.2	0.81	<0.05	15.20
RDD285034		21.1	560	3.0	220	<0.002	0.23	3.26	15.1	1	8.9	27.5	0.84	0.07	15.90
RDD285035		15.6	300	3.7	204	<0.002	0.67	2.38	14.4	1	8.7	32.8	0.83	<0.05	14.95
RDD285036		11.4	430	4.4	226	<0.002	0.29	2.86	9.4	<1	195.5	96.0	0.49	<0.05	8.31
RDD285037		6.0	280	3.3	68.6	<0.002	0.10	1.30	5.5	<1	39.3	113.5	0.24	<0.05	4.18
RDD285038		13.4	460	2.0	315	<0.002	0.04	1.28	9.3	<1	76.1	31.8	0.59	<0.05	9.36
RDD285039		7.0	240	1.9	71.3	<0.002	0.03	0.82	4.1	<1	14.7	137.0	0.23	<0.05	3.73
RDD285040															
RDD285041		26.5	530	6.4	32.5	<0.002	<0.01	0.09	8.5	<1	0.8	395	0.24	<0.05	2.91
RDD285042		12.1	300	1.1	69.0	<0.002	0.02	0.71	6.1	<1	10.0	64.9	0.32	<0.05	5.13
RDD285043		7.8	270	0.8	8.3	<0.002	<0.01	0.56	3.9	<1	2.8	74.5	0.22	<0.05	3.66
RDD285044		11.8	430	0.9	24.2	<0.002	0.01	0.91	6.3	<1	3.8	78.7	0.40	<0.05	6.40
RDD285045		6.9	260	1.8	15.6	<0.002	0.16	1.91	4.3	<1	8.6	69.6	0.24	<0.05	4.05
RDD285046		7.1	260	0.6	20.2	<0.002	0.01	0.80	4.9	<1	6.4	62.2	0.27	<0.05	4.24
RDD285047		7.7	350	3.5	83.2	<0.002	0.72	1.70	6.0	<1	16.5	49.8	0.32	<0.05	5.12
RDD285048		1.1	10	3.0	1.2	<0.002	<0.01	0.25	0.2	<1	0.5	3.5	0.06	<0.05	0.34
RDD285049		11.9	300	1.4	133.5	<0.002	0.18	1.98	5.2	<1	10.6	66.8	0.45	<0.05	6.77
RDD285050		8.2	260	1.2	158.5	<0.002	0.29	1.35	5.1	<1	49.5	36.3	0.51	<0.05	6.40
RDD285051		7.2	310	9.0	244	<0.002	0.36	3.02	6.8	1	180.0	22.7	0.74	<0.05	8.72
RDD285052		5.6	310	3.9	130.5	<0.002	<0.01	1.81	7.3	<1	152.5	21.1	0.76	<0.05	8.48
RDD285053		6.2	240	2.2	203	<0.002	0.11	1.52	5.0	<1	102.0	57.2	0.56	<0.05	6.64
RDD285054		6.5	220	3.5	172.5	<0.002	0.26	1.60	5.1	<1	51.7	62.9	0.50	<0.05	5.99
RDD285055		11.6	260	4.8	212	<0.002	0.33	2.13	6.4	<1	133.0	57.8	0.70	<0.05	7.93
RDD285056		36.5	490	4.4	267	0.020	0.24	1.85	10.9	1	31.6	70.2	2.31	<0.05	16.90
RDD285057		26.3	400	3.0	302	0.003	0.01	2.05	8.6	<1	200	65.0	1.44	<0.05	10.10
RDD285058		20.4	400	31.6	206	<0.002	0.04	1.12	9.4	<1	169.5	80.3	1.25	<0.05	11.05
RDD285059		21.5	390	10.2	232	<0.002	0.01	1.06	10.2	<1	124.0	98.3	1.37	<0.05	11.55
RDD285060		14.4	370	8.2	265	0.002	<0.01	1.04	9.8	<1	114.0	80.6	1.11	<0.05	10.50
RDD285061		17.8	510	5.8	282	0.012	0.01	0.94	11.4	<1	169.5	95.4	1.53	<0.05	15.40
RDD285062		22.0	450	2.9	305	<0.002	0.50	1.27	10.2	<1	212	75.2	1.04	<0.05	11.50
RDD285063		20.7	440	2.9	221	<0.002	0.54	1.06	11.0	<1	218	82.7	1.12	0.05	11.85
RDD285064		42.7	410	4.0	258	<0.002	1.94	0.99	10.5	1	157.0	79.3	1.08	0.05	11.00
RDD285065															
RDD285066		141.5	2610	3.6	34.5	<0.002	0.04	0.10	19.2	<1	2.0	795	2.88	<0.05	3.81
RDD285067		21.8	410	3.0	451	0.002	0.04	1.81	9.1	<1	147.5	69.0	1.06	<0.05	10.55
RDD285068		18.5	360	6.4	270	0.007	0.77	1.81	8.0	1	207	52.3	1.07	<0.05	9.68
RDD285069		8.2	280	3.9	120.0	<0.002	1.10	1.40	6.8	1	76.0	15.5	0.81	<0.05	8.16
RDD285070		11.0	320	21.1	167.0	<0.002	1.12	3.55	7.5	1	154.5	12.6	0.89	<0.05	7.73



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Page: 8 - D

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

Project: EDGI\_18

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ti	U	V	W	Y	Zn	Zr	Dy	Er	Eu	Gd	Ho	Lu	Nd	Pr
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.02	0.1	1	0.1	0.1	2	0.5	0.05	0.03	0.03	0.05	0.01	0.01	0.1	0.03
RDD285031		1.68	2.2	43	3.1	38.9	59	111.5	6.89	3.95	1.56	7.45	1.41	0.52	41.3	10.65
RDD285032		2.14	2.5	47	1.8	50.5	137	113.5	8.44	4.83	1.77	9.12	1.73	0.61	49.2	12.35
RDD285033		0.96	3.3	65	2.0	41.1	17	146.0	7.78	4.28	1.75	9.02	1.57	0.57	55.5	13.95
RDD285034		1.07	2.0	73	2.0	33.9	20	147.0	6.81	3.80	1.61	7.76	1.35	0.55	51.0	13.65
RDD285035		1.00	1.7	67	2.0	27.4	13	144.5	5.21	3.11	1.14	5.54	1.08	0.48	41.3	11.40
RDD285036		1.54	1.2	43	2.5	21.3	57	87.1	3.85	2.24	1.09	4.10	0.78	0.32	24.1	6.73
RDD285037		0.50	0.8	22	0.6	15.9	42	50.1	2.92	1.57	0.84	3.42	0.58	0.21	16.6	4.15
RDD285038		2.65	1.2	51	0.9	20.2	82	100.5	3.60	2.20	1.15	4.47	0.74	0.35	35.3	9.70
RDD285039		0.58	0.8	20	0.6	13.4	38	46.2	2.30	1.24	0.75	2.80	0.46	0.16	16.1	4.16
RDD285040																
RDD285041		0.17	0.6	53	0.2	10.8	34	64.2	1.94	1.08	0.82	2.50	0.39	0.14	18.0	4.76
RDD285042		0.68	0.9	28	0.6	17.3	44	59.7	2.96	1.65	0.86	3.48	0.58	0.23	18.5	4.63
RDD285043		0.08	0.9	19	0.5	16.7	31	43.8	2.90	1.36	1.19	4.13	0.52	0.17	18.5	4.36
RDD285044		0.21	1.2	30	0.7	20.3	51	73.9	3.53	1.85	1.50	4.78	0.67	0.25	25.8	6.86
RDD285045		0.15	0.8	21	0.5	13.8	38	46.1	2.33	1.25	1.16	3.26	0.46	0.17	16.3	4.20
RDD285046		0.19	0.8	22	0.5	15.2	32	51.1	2.64	1.39	0.94	3.26	0.51	0.19	15.3	3.88
RDD285047		0.79	1.2	27	0.8	18.2	41	55.7	3.17	1.63	0.88	3.84	0.57	0.21	24.0	5.46
RDD285048		0.05	0.2	3	0.2	1.1	3	13.8	0.19	0.11	0.04	0.15	0.03	0.03	0.8	0.21
RDD285049		1.18	3.4	30	0.9	16.2	39	80.3	2.94	1.70	0.78	3.70	0.56	0.25	27.1	6.22
RDD285050		1.30	2.3	26	0.8	17.2	40	78.1	2.95	1.71	0.67	3.13	0.59	0.25	20.3	4.77
RDD285051		1.56	1.4	34	1.1	23.2	68	94.2	3.88	2.37	0.79	4.01	0.75	0.32	28.1	6.82
RDD285052		0.65	1.4	33	1.6	22.3	49	93.3	3.63	2.18	0.81	3.62	0.73	0.29	26.1	6.25
RDD285053		1.43	1.5	25	0.9	17.7	46	77.3	3.08	1.78	0.80	3.33	0.58	0.25	22.4	5.23
RDD285054		1.44	1.9	26	1.1	16.6	46	78.3	2.72	1.68	0.55	2.73	0.53	0.25	18.5	4.38
RDD285055		1.41	3.8	31	1.3	21.8	57	101.5	3.66	2.21	0.82	3.67	0.71	0.32	26.1	6.26
RDD285056		1.56	8.7	100	2.2	35.8	12	206	6.05	3.55	1.21	6.36	1.19	0.53	49.5	12.30
RDD285057		1.82	2.2	60	1.1	29.4	140	123.0	4.69	2.81	1.10	4.67	0.92	0.40	30.6	7.37
RDD285058		1.30	2.0	60	1.3	27.4	788	136.5	4.60	2.72	0.95	4.41	0.90	0.38	29.5	7.41
RDD285059		1.36	2.0	58	1.5	28.8	238	132.5	4.63	2.81	0.91	4.34	0.92	0.40	29.3	7.03
RDD285060		1.54	1.8	59	1.4	25.3	170	129.0	4.13	2.74	0.75	3.55	0.84	0.41	19.3	4.50
RDD285061		1.62	2.2	68	3.6	32.7	160	150.5	5.22	3.17	1.05	4.96	1.04	0.49	32.5	8.02
RDD285062		1.61	1.8	58	1.6	31.6	64	139.0	5.16	3.03	1.11	5.09	1.00	0.43	36.0	8.91
RDD285063		1.15	1.9	58	2.0	33.0	36	145.5	5.21	3.21	1.05	5.20	1.05	0.46	35.4	8.58
RDD285064		1.48	1.7	56	1.9	29.7	36	134.0	4.93	2.86	0.97	4.73	0.95	0.41	33.1	8.14
RDD285065																
RDD285066		0.14	1.2	196	0.2	18.8	112	203	3.82	1.81	1.71	4.75	0.69	0.21	28.5	6.55
RDD285067		2.67	1.9	58	1.6	28.2	63	135.0	4.73	2.72	1.01	4.60	0.90	0.39	35.0	8.90
RDD285068		1.56	3.6	62	1.3	25.3	117	117.0	4.38	2.59	0.85	4.22	0.86	0.37	26.9	6.51
RDD285069		0.83	6.8	35	1.3	20.1	106	97.0	3.30	1.92	0.51	3.31	0.67	0.29	20.2	4.54
RDD285070		1.45	6.1	36	0.9	25.0	68	100.0	4.02	2.36	0.52	4.01	0.82	0.34	23.7	5.46



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 8 – E

Total # Pages: 9 (A – E)

Plus Appendix Pages

Finalized Date: 5–MAR–2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Sm	Tb	Tm	Yb
		ppm	ppm	ppm	ppm
		0.03	0.01	0.01	0.03
RDD285031		8.47	1.13	0.55	3.41
RDD285032		9.78	1.39	0.67	4.12
RDD285033		10.85	1.34	0.62	3.87
RDD285034		9.74	1.15	0.56	3.65
RDD285035		7.36	0.84	0.47	3.10
RDD285036		4.98	0.61	0.33	2.16
RDD285037		3.73	0.50	0.23	1.37
RDD285038		6.69	0.62	0.33	2.21
RDD285039		3.46	0.39	0.18	1.08
RDD285040					
RDD285041		3.31	0.35	0.15	0.97
RDD285042		4.14	0.50	0.23	1.49
RDD285043		4.62	0.55	0.18	1.12
RDD285044		5.80	0.66	0.26	1.64
RDD285045		3.88	0.44	0.17	1.11
RDD285046		3.66	0.46	0.20	1.27
RDD285047		5.14	0.53	0.25	1.55
RDD285048		0.18	0.04	0.02	0.14
RDD285049		5.52	0.51	0.27	1.65
RDD285050		4.21	0.48	0.26	1.69
RDD285051		5.22	0.60	0.35	2.20
RDD285052		5.06	0.56	0.34	2.16
RDD285053		4.27	0.48	0.29	1.69
RDD285054		3.60	0.41	0.25	1.65
RDD285055		4.74	0.56	0.33	2.18
RDD285056		8.48	0.97	0.57	3.58
RDD285057		5.69	0.72	0.44	2.68
RDD285058		5.50	0.68	0.43	2.69
RDD285059		5.46	0.70	0.44	2.71
RDD285060		4.11	0.58	0.43	2.85
RDD285061		6.17	0.79	0.53	3.30
RDD285062		6.46	0.78	0.48	2.93
RDD285063		6.56	0.79	0.51	3.05
RDD285064		5.99	0.72	0.45	2.86
RDD285065					
RDD285066		5.67	0.68	0.27	1.44
RDD285067		5.93	0.71	0.43	2.71
RDD285068		5.33	0.67	0.41	2.50
RDD285069		4.38	0.50	0.31	2.00
RDD285070		4.85	0.62	0.38	2.44

Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane OLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

[www.alsglobal.com/geochemistry](http://www.alsglobal.com/geochemistry)

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: **BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD**

PO BOX 20

**ZEEHAN TAS 7469**

Page: 9 – A

Total # Pages: 9 (A – E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

Project: EDGI\_18

**CERTIFICATE OF ANALYSIS    AD25025626**

[illegible]





Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD

PO BOX 20

ZEEHAN TAS 7469

Project: EDGI\_18

Page: 9 - C

Total # Pages: 9 (A - E)

Plus Appendix Pages

Finalized Date: 5-MAR-2025

Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Ni	P	Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti
		ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.2	10	0.5	0.1	0.002	0.01	0.05	0.1	1	0.2	0.2	0.05	0.05	0.01	0.005
RDD285071		36.8	430	4.3	256	0.014	0.15	1.87	10.2	1	133.5	75.8	1.46	<0.05	12.55	0.351
RDD285072		25.3	390	2.3	233	<0.002	0.95	2.29	8.3	1	33.9	44.1	2.17	<0.05	11.65	0.321
RDD285073		34.9	410	1.7	169.0	<0.002	3.75	1.66	10.4	1	3.9	22.8	1.11	0.19	11.20	0.336
RDD285074		19.8	430	0.8	93.5	<0.002	0.52	0.58	9.7	1	2.5	7.8	0.81	0.07	9.81	0.329
RDD285075		25.8	430	1.6	150.0	<0.002	1.73	1.08	10.6	1	2.9	35.1	0.94	0.11	11.05	0.349
RDD285076		19.7	450	1.3	141.0	<0.002	0.45	0.81	10.8	<1	3.6	20.6	0.92	<0.05	10.55	0.356
RDD285077		21.0	480	2.2	284	<0.002	0.08	2.16	10.6	<1	67.7	81.5	0.93	<0.05	10.45	0.386
RDD285078		3.6	370	1.2	4.8	<0.002	0.26	0.53	1.8	<1	6.1	110.5	0.26	0.05	2.09	0.053
RDD285079		2.7	350	1.0	3.3	<0.002	0.05	0.56	1.4	<1	4.3	109.0	0.21	<0.05	1.58	0.040
RDD285080		1.8	530	0.6	0.7	<0.002	0.01	0.29	0.5	<1	1.3	100.5	0.07	<0.05	0.61	0.012
RDD285081		1.4	560	0.5	0.6	<0.002	0.01	0.17	0.5	<1	2.5	89.6	0.05	<0.05	0.59	0.012
RDD285082		1.8	580	0.8	0.5	<0.002	0.28	0.21	0.5	<1	2.3	88.6	0.06	<0.05	0.60	0.013
RDD285083		1.8	550	<0.5	0.5	<0.002	0.01	0.28	0.6	<1	1.8	94.1	0.07	<0.05	0.68	0.014
RDD285084		1.7	540	<0.5	0.2	<0.002	<0.01	0.19	0.6	1	1.5	98.9	<0.05	<0.05	0.51	0.010
RDD285085		2.4	470	<0.5	0.1	<0.002	0.08	0.25	0.5	1	2.2	85.1	0.05	<0.05	0.51	0.013
RDD285086		3.3	720	<0.5	0.2	<0.002	<0.01	0.18	0.9	1	2.0	92.2	0.12	<0.05	0.94	0.019
RDD285087		3.2	730	<0.5	0.9	<0.002	0.14	0.21	1.0	1	5.1	96.6	0.14	<0.05	1.26	0.029
RDD285088		3.1	650	<0.5	2.7	<0.002	0.16	0.30	0.8	1	6.8	95.5	0.11	<0.05	0.91	0.020
RDD285089		20.9	910	9.4	378	0.002	0.22	2.61	9.8	1	102.5	48.4	2.93	<0.05	14.60	0.277
RDD285090																

\*\*\*\*\* See Appendix Page for comments regarding this certificate \*\*\*\*\*



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane OLD 4053

Phone: +61 7 3243 7222 Fax: +61 7 3243 7218

[www.alsglobal.com/geochemistry](http://www.alsglobal.com/geochemistry)

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation

No: 825, Corporate Site No: 23001.

**TO: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD**

PO BOX 20

**ZEEHAN TAS 7469**

Project: EDGI\_18

Page: 9 – E

**Total # Pages: 9 (A – E)**

**Plus Appendix Pages**

Finalized Date: 5-MAR-2025

Account: BLUMINJV

**CERTIFICATE OF ANALYSIS    AD25025626**

Sample Description	Method Analyte Units LOD	ME-MS61r	ME-MS61r	ME-MS61r	ME-MS61r
		Sm	Tb	Tm	Yb
		ppm	ppm	ppm	ppm
		0.03	0.01	0.01	0.03
RDD285071		7.70	0.90	0.55	3.38
RDD285072		6.93	0.80	0.47	2.90
RDD285073		5.43	0.60	0.36	2.31
RDD285074		5.79	0.57	0.33	2.12
RDD285075		5.39	0.57	0.36	2.39
RDD285076		5.13	0.63	0.40	2.40
RDD285077		5.43	0.68	0.44	2.83
RDD285078		1.83	0.22	0.11	0.69
RDD285079		1.25	0.16	0.11	0.63
RDD285080		0.94	0.14	0.09	0.53
RDD285081		0.98	0.14	0.08	0.48
RDD285082		0.98	0.15	0.08	0.46
RDD285083		1.10	0.17	0.11	0.63
RDD285084		1.05	0.16	0.09	0.57
RDD285085		0.90	0.13	0.07	0.45
RDD285086		1.14	0.16	0.08	0.55
RDD285087		1.23	0.19	0.10	0.61
RDD285088		1.30	0.19	0.09	0.59
RDD285089		8.69	1.01	0.52	3.47
RDD285090					



Australian Laboratory Services Pty. Ltd.

32 Shand Street  
Stafford  
Brisbane QLD 4053  
Phone: +61 7 3243 7222 Fax: +61 7 3243 7218  
www.alsglobal.com/geochemistry

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation  
No: 825, Corporate Site No: 23001.

To: BLUESTONE MINES TASMANIA JOINT VENTURE PTY LTD  
PO BOX 20  
ZEEHAN TAS 7469

Project: EDGL\_18

Page: Appendix 1  
Total # Appendix Pages: 1  
Finalized Date: 5-MAR-2025  
Account: BLUMINJV

## CERTIFICATE OF ANALYSIS AD25025626

### CERTIFICATE COMMENTS

#### ANALYTICAL COMMENTS

Applies to Method:

REEs may not be totally soluble in this method.  
ME-MS61r

#### ACCREDITATION COMMENTS

Applies to Method:

NATA Accreditation covers the performance of this service but does not cover the performance of ALS Perth Sample Preparation. Corporate Accreditation No: 825, Corporate Site No: 23001. The Technical Signatory is Wendy Wong, Senior QC Chemist  
Au-ICP21

#### LABORATORY ADDRESSES

Applies to Method:

Processed at ALS Perth located at 29 & 31 Denninup Way, Malaga, Australia. Processed at ALS Perth Sample Preparation at 19 Integrity Way, Wangara, WA, Australia  
Au-ICP21 ME-MS61r

Applies to Method:

Processed at ALS Adelaide located at Unit 1, 1 Burma Road, Pooraka, Adelaide, SA, Australia.  
BAG-01 BAG-21 CRU-21 LEV-01  
LOG-22 LOG-24 OA-HSUL10 PUL-23  
PUL-QC SPL-21 WEI-21

Applies to Method:

Processed at ALS Brisbane located at 32 Shand Street, Stafford, Brisbane, QLD, Australia. Processed at ALS Brisbane Sample Preparation at 23 Pineapple Street, Zillmere, QLD, 4034, Australia  
ME-XRF15b